

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

**SAE**

**AMS 4029H**

Issued 15 AUG 1958

Revised 1 JAN 1992

Superseding AMS 4029G

Submitted for recognition as an American National Standard

ALUMINUM ALLOY SHEET AND PLATE  
4.5Cu - 0.85Si - 0.80Mn - 0.50Mg (2014; -T6 Sheet, -T651 Plate)  
Solution and Precipitation Heat Treated

UNS A92014

## 1. SCOPE:

### 1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate.

### 1.2 Application:

These products are used typically for structural parts of good strength, but usage is not limited to such applications.

### 1.3 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2202 Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM 2202 Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2355 Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4029H

SAE

AMS 4029H

## 2.1 SAE Publications (continued):

MAM 2355 Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

AMS 2811 Identification, Aluminum and Magnesium Alloy Wrought Products  
 ARP823 Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

## 2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6088 Heat Treatment of Aluminum Alloys

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355:

TABLE 1 - Composition

Element	min	max
Copper	3.9	5.0
Silicon	0.50	1.2
Manganese	0.40	1.2
Magnesium	0.20	0.8
Iron	--	0.7
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

## 3.2 Condition:

The product shall be supplied in the following condition; heat treatments shall be performed in accordance with MIL-H-6088:

AMS 4029H

SAE

AMS 4029H

3.2.1 Sheet: Solution and precipitation heat treated.

3.2.2 Plate: Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%, and precipitation heat treated.

3.2.2.1 Plate shall receive no further straightening operations after stretching.

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as specified in Table 2 and 3.3.1.1.

TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.020 to 0.039, incl	64.0	57.0	6
Over 0.039 to 0.249, incl	66.0	58.0	7
Over 0.249 to 0.499, incl	67.0	59.0	7
Over 0.499 to 1.000, incl	67.0	59.0	6
Over 1.000 to 2.000, incl	67.0	59.0	4
Over 2.000 to 2.500, incl	65.0	58.0	2
Over 2.500 to 3.000, incl	63.0	57.0	2
Over 3.000 to 4.000, incl	59.0	55.0	1

TABLE 2B - Minimum Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.51 to 0.99, incl	441	393	6
Over 0.99 to 6.32, incl	455	400	7
Over 6.32 to 12.67, incl	462	407	7
Over 12.67 to 25.40, incl	462	407	6
Over 25.40 to 50.80, incl	462	407	4
Over 50.80 to 63.50, incl	448	400	2
Over 63.50 to 76.20, incl	434	393	2
Over 76.20 to 101.60, incl	407	379	1

AMS 4029H

SAE

AMS 4029H

3.3.1.1 Tensile property requirements for product under 0.020 inch (0.51 mm) or over 4.000 inches (101.60 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.020 to 0.499 inch (0.51 to 12.67 mm), inclusive, in nominal thickness shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Requirements

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.020 to 0.039, incl	0.51 to 0.99, incl	5
Over 0.039 to 0.050, incl	Over 0.99 to 1.27, incl	6
Over 0.050 to 0.124, incl	Over 1.27 to 3.15, incl	8
Over 0.124 to 0.249, incl	Over 3.15 to 6.32, incl	10
Over 0.249 to 0.499, incl	Over 6.32 to 12.67, incl	12

3.3.2.1 Bending requirements for product under 0.020 inch (0.51 mm) or over 0.499 inch (12.67 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

#### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

#### 3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

(R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.