

Aluminum Alloy, Sheet and Plate
6.3Cu - 0.30Mn - 0.18Zr - 0.10V - 0.06Ti (2219-0)
Annealed

(Composition similar to UNS A92219)

RATIONALE

AMS 4031G is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application

These products have been used typically for parts requiring high strength up to 600 °F (316 °C), but usage is not limited to such application. These products are well suited for cryogenic applications and where welding is required.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials
AS 1990	Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium-Products

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, or www.ansi.org.

ANSI 35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI 35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	--	0.20
Iron	--	0.30
Copper	5.8	6.8
Manganese	0.20	0.40
Magnesium	--	0.02
Zinc	--	0.10
Titanium	0.02	0.10
Vanadium	0.05	0.15
Zirconium	0.10	0.25
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Annealed in accordance with AMS 2772.

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS 2355 on the mill produced size.

3.3.1 As Annealed

3.3.1.1 Tensile Properties

Shall be as specified in Table 2 for product 0.020 to 2.000 inches (0.51 to 50.80 mm), inclusive, in nominal thickness.

TABLE 2 - TENSILE PROPERTIES

Property	Value
Tensile Strength, max	32.0 ksi (221 MPa)
Yield Strength at 0.2% Offset, max	16.0 ksi (110 MPa)
Elongation in 2 Inches (50.8 mm) or 4D, min	12%

3.3.1.2 Bending

Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - BENDING PARAMETERS

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.020 to 0.250, incl	0.51 to 6.35, incl	4
Over 0.250 to 0.750, incl	Over 6.35 to 19.05, incl	6
Over 0.750 to 1.000, incl	Over 19.05 to 25.40, incl	8

3.3.2 After Solution and Precipitation Heat Treatment

The product, as received by purchaser, shall have the following properties after solution and precipitation heat treatment to the -T62 condition (See AS 1990) in accordance with AMS 2772:

3.3.2.1 Tensile Properties

Shall be as specified in Table 4.

TABLE 4A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.020 to 0.039, incl	54.0	36.0	6
Over 0.039 to 0.249, incl	54.0	36.0	7
Over 0.249 to 1.000, incl	54.0	36.0	8
Over 1.000 to 2.000, incl	54.0	36.0	7

TABLE 4B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.51 to 0.99, incl	372	248	6
Over 0.99 to 6.32, incl	372	248	7
Over 6.32 to 25.40, incl	372	248	8
Over 25.40 to 50.80, incl	372	248	7

3.3.2.2 Bending

Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 5 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 5 - BENDING PARAMETERS

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.020 to 0.062, incl	0.51 to 1.57, incl	8
Over 0.062 to 0.250, incl	Over 1.57 to 6.35, incl	12
Over 0.250 to 0.499, incl	Over 6.35 to 12.67, incl	16

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties as annealed (3.3.1.1), properties after solution and precipitation heat treatment (3.3.2), and tolerances (3.5) are acceptance tests and except for composition shall be performed on each lot.

4.2.2 Periodic Tests

Bending (3.3.1.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS 2355.

4.4 Reports

The vendor of product shall furnish with each shipment a report stating that the product conforms to the composition and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements and, when performed, to the periodic test requirements. This report shall include the purchase order number, inspection lot number(s), AMS 4031G, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2355.