

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4032C

Issued 12-5-39
Canceled 4-1-43
Revised 4-1-46

ALUMINUM ALLOY SHEET AND PLATE Copper Manganese Magnesium (17S-T)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **COMPOSITION:**

Copper	3.50 - 4.50
Manganese	0.40 - 1.00
Magnesium	0.20 - 0.80
Iron	1.00 max
Silicon	0.80 max
Chromium	0.25 max
Titanium	0.15 max
Zinc	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

3. **CONDITION:** (a) Solution heat treated, conforming to the following physical properties. Test specimens shall conform to ASTM E-8, except from sheet less than 3/4 inch wide, and shall be cut across the direction of rolling except from sheet less than 9 inches wide. Elongation requirements apply only to sheet 3/4 inch and over in width.

Thickness Inch	Tensile Strength psi min	Yield Strength (0.2% Offset) or at Extension Indicated		Elongation % in 2 in. min	Bend Factor
		psi min	Extension Under Load inch in 2 in. min		
0.010 - 0.020, incl.	58,000	34,000	0.0105	15	3
0.021 - 0.040, incl.	58,000	34,000	0.0105	17	3
0.041 - 0.128, incl.	58,000	34,000	0.0105	18	4
0.129 - 0.249, incl.	58,000	34,000	0.0105	15	6
0.250 - 0.500, incl.	58,000	34,000	0.0105	12	8
0.501 - 1.000, incl.	58,000	34,000	0.0105	10	-

(b) Sheet or plate up to and including 0.500 inch thick shall withstand, without cracking, bending at room temperature through an angle of 180° around a diameter equal to the bend factor shown above times the nominal thickness of the sheet or plate, with axis of bend parallel to direction of rolling.

4. **QUALITY:** (a) Sheet and plate shall be uniform in quality and condition, clean, sound, and free from foreign material and from internal and external defects detrimental to fabrication or to the appearance and performance of parts. Sheet or plate revealing defects during fabrication shall be subject to rejection.

(b) Sheet or plate and parts made therefrom shall be subjected to inspection by any method which reveal defects.

Approved and practices recommended, are advisory only. Their use is not guaranteed. The SAE standard or recommended practice, and no commitment is made by SAE to investigate or consider any claims or damages which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents.