



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 4034B

Superseding AMS 4034A

Issued 6-30-60

Revised 11-1-67

ALUMINUM ALLOY PLATE, ALCLAD 4.4Cu - 1.5Mg - 0.60Mn (Alclad 2024-T351) Stress-Relief Stretched

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for machined parts subject to excessive warpage during machining due to residual stresses, and for structural parts of good strength which are required to exhibit maximum corrosion resistance. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.

3. COMPOSITION:

	Core (2024)			(Cladding 1230)	
	min	max		min	max
Copper	3.8	4.9	Iron + Silicon	--	0.7
Magnesium	1.2	1.8	Copper	--	0.10
Manganese	0.30	0.9	Zinc	--	0.10
Iron	--	0.50	Manganese	--	0.05
Silicon	--	0.50	Other Impurities, each	--	0.05
Zinc	--	0.25	Aluminum, by difference	99.30	--
Chromium	--	0.10			
Other Impurities, each	--	0.05			
Other Impurities, total	--	0.15			
Aluminum	remainder				

- 4. CONDITION:** Solution heat treated and stress-relieved by stretching.
 - 4.1** Material shall be stretched in the solution heat treated condition to produce a nominal permanent set of 2%, but not less than 1-1/2% nor more than 3%.
 - 4.2** Material shall receive no further straightening operations after stretching.
- 5. TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.
 - 5.1 Cladding Thickness:** After rolling, the average cladding thickness shall be as shown. Routine measurements are not required.

Total Thickness of Composite Product Inches	Cladding Thickness Per Side % of Total Thickness	
	min	max
0.250 to 0.499, incl	1.2	--
Over 0.499	1.2	3.0

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standards or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2 Tensile Properties:

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (See 5.2.1)		Elongation, % in 2 in. or 4D, min
		psi, min	Extension Under Load in. in 2 in.	
0.250 to 0.499, incl	63,000	40,000	0.0118	12
Over 0.499 to 1.000, incl	62,000	41,000	0.0118	8
Over 1.000 to 1.500, incl	62,000	41,000	0.0118	7
Over 1.500 to 2.000, incl	61,000	41,000	0.0118	6
Over 2.000 to 3.000, incl	60,000	41,000	0.0118	4
Over 3.000 to 4.000, incl	56,000	40,000	0.0116	4

5.2.1 Extension under load is based upon the following values of E:

Nominal Thickness Inches	E
0.250 to 0.499, incl	10,200,000
Over 0.499	10,500,000

5.2.2 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

9. IDENTIFICATION: Unless otherwise specified, each plate shall be marked on one face, in the respective location indicated below, with "1-1/2% Alclad 2024" and temper, AMS 4034, manufacturer's identification, and nominal thickness in inches. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling.

9.1 Flat Plate Under 6 In. Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet.