

# AERONAUTICAL MATERIAL SPECIFICATIONS

## AMS 4036

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-61  
Revised

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD ONE SIDE  
4.5Cu - 1.5Mg - 0.6Mn (Alclad one side 2024; -T3 Sheet, -T4 Plate)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for structural use including chemically milled parts.
3. COMPOSITION:

Core		Cladding	
Copper	3.8 - 4.9	Iron + Silicon	0.7 max
Magnesium	1.2 - 1.8	Copper	0.10 max
Manganese	0.30 - 0.9	Zinc	0.10 max
Iron	0.50 max	Manganese	0.05 max
Silicon	0.50 max	Other Impurities, each	0.05 max
Zinc	0.25 max	Aluminum, by difference	99.30 min
Chromium	0.10 max		
Other Impurities, each	0.05 max		
Other Impurities, total	0.15 max		
Aluminum	remainder		

4. CONDITION: Solution heat treated and leveled.

5. TECHNICAL REQUIREMENTS:

- 5.1 Cladding Thickness: After rolling, the average cladding thickness on the clad side shall be as shown. Routine measurements are not required.

Total Thickness of Composite Product Inch	Cladding Thickness % of Total Thickness, min
0.062 and under	4.0
Over 0.062 to 0.187, incl	2.0
Over 0.187 to 0.499, incl	1.2

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2 Tensile Properties: Test specimens shall conform to ASTM E8-57T except from material less than 3/4 in. wide, and shall be cut across the direction of rolling except from material less than 9 in. wide. Elongation requirements apply only to material 3/4 in. and over in width.

Nominal Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (See 5.2.1)		Elongation % in 2 in., min
		psi, min	Extension Under Load in. in 2 in.	
0.010 to 0.020, incl	61,000	40,000	0.0124	12
Over 0.020 to 0.062, incl	61,000	40,000	0.0124	15
Over 0.062 to 0.187, incl	63,000	41,000	0.0122	15
Over 0.187 to 0.499, incl	63,000	40,000	0.0120	12

5.2.1 Extension under load is based upon the following values of E:

Nominal Thickness Inch	E
0.062 and under	9,500,000
Over 0.062 to 0.499, incl	10,000,000

5.2.2 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

5.3 Bending: Material 0.249 in. and under in thickness shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to direction of rolling. The bare (unclad) surface shall be on the outside of the bend.

Nominal Thickness Inch	Bend Factor
0.040 and under	4
Over 0.040 to 0.124, incl	5
Over 0.124 to 0.249, incl	8

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2202 as applicable. Thickness tolerances shall conform to Table II.