

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

**SAE**

**AMS 4036H**

Issued 15 JAN 1961

Revised 1 OCT 1993

Superseding AMS 4036G

Submitted for recognition as an American National Standard

## ALUMINUM ALLOY SHEET AND PLATE, ALCLAD ONE SIDE

4.4Cu - 1.5Mg - 0.60Mn

Alclad One Side 2024 and 1-1/2% Alclad One Side 2024-T3 Sheet;  
1-1/2% Alclad One Side 2024-T351 Plate UNS A82024

### 1. SCOPE:

#### 1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate clad on one side with a different aluminum alloy.

#### 1.2 Application:

These products have been used typically for structural components including chemically-milled parts, but usage is not limited to such applications.

- 1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

### 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAENORM.COM Click to view the full PDF of AMS4036H

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4036H

SAE

AMS 4036H

## 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2202	Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate
MAM 2202	Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units
AMS 2811	Identification, Aluminum and Magnesium Alloy Wrought Products
ARP823	Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6088 Heat Treatment of Aluminum Alloys

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall conform to the percentages by weight shown in Tables 1 and 2, determined in accordance with AMS 2355 or MAM 2355.

AMS 4036H

SAE

AMS 4036H

TABLE 1 - Composition, Core (2024)

Element	Min	Max
Copper	3.8	4.9
Magnesium	1.2	1.8
Manganese	0.30	0.9
Iron	--	0.50
Silicon	--	0.50
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

TABLE 2 - Composition, Cladding (1230)

Element	Min	Max
Iron + Silicon	--	0.70
Copper	--	0.10
Zinc	--	0.10
Manganese	--	0.05
Magnesium	--	0.05
Vanadium	--	0.05
Titanium	--	0.03
Other Impurities, each	--	0.03
Aluminum, by difference	99.30	--

### 3.2 Condition:

The product shall be supplied in the following condition:

- 3.2.1 Sheet: Solution heat treated in accordance with MIL-H-6088 and cold worked.
- 3.2.2 Plate: Solution heat treated in accordance with MIL-H-6088 and stretched to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%.
- 3.2.2.1 Plate shall receive no further straightening operations after stretching.

AMS 4036H

SAE

AMS 4036H

## 3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

## 3.3.1 Tensile Properties: Shall be as specified in Table 3.

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.010 to 0.020, incl	61.0	40.0	12
Over 0.020 to 0.062, incl	61.0	40.0	15
Over 0.062 to 0.128, incl	62.0	41.0	15
Over 0.128 to 0.249, incl	63.0	41.0	15
Over 0.249 to 0.499, incl	63.0	41.0	12

TABLE 3B - Minimum Tensile Properties, SI Units

Nominal Thickness mm	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.25 to 0.51, incl	421	276	12
Over 0.51 to 1.57, incl	421	276	15
Over 1.57 to 3.25, incl	427	283	15
Over 3.25 to 6.32, incl	434	283	15
Over 6.32 to 12.67, incl	434	283	12

3.3.2 Bending: Product 0.010 to 0.249 inch (0.25 to 6.32 mm), inclusive, in nominal thickness shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor specified in Table 4 times the nominal thickness of the product with axis of bend parallel to the direction of rolling. The bare (unclad) surface shall be on the outside of the bend.

AMS 4036H

SAE

AMS 4036H

TABLE 4 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness mm	Bend Factor
0.010 to 0.040, incl	0.25 to 1.02, incl	4
Over 0.040 to 0.124, incl	Over 1.02 to 3.15, incl	5
Over 0.124 to 0.249, incl	Over 3.15 to 6.32, incl	8

3.3.3 Cladding Thickness: After rolling, the average cladding thickness shall be as specified in Table 5.

TABLE 5 - Cladding Thickness

Nominal Thickness Inch	Nominal Thickness mm	Cladding Thickness Per Side % of Thickness Min
0.010 to 0.062, incl	0.25 to 1.57, incl	4.0
Over 0.062 to 0.187, incl	Over 1.57 to 4.75, incl	2.0
Over 0.187 to 0.499, incl	Over 4.75 to 12.67, incl	1.2

### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

(R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.