

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4041F

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 11-1-41
Revised 8.15.58

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD 4.5Cu - 1.5Mg - 0.6Mn (Alclad 2024; -T3 Sheet, -T4 Plate)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for structural parts of good strength which are required to exhibit maximum corrosion resistance.
3. **COMPOSITION:**

	Core		Cladding
Copper	3.8 - 4.9	Iron + Silicon	0.7 max
Magnesium	1.2 - 1.8	Copper	0.10 max
Manganese	0.30 - 0.9	Zinc	0.10 max
Iron	0.50 max	Manganese	0.05 max
Silicon	0.50 max	Other Impurities, each	0.05 max
Zinc	0.25 max	Other Impurities, total	0.15 max
Chromium	0.10 max	Aluminum, by difference	99.30 min
Other Impurities, each	0.05 max		
Other Impurities, total	0.15 max		
Aluminum	remainder		

4. **CONDITION:**

- 4.1 **Sheet:** Solution heat treated and stretcher leveled.
- 4.2 **Plate:** Solution heat treated.

5. **TECHNICAL REQUIREMENTS:**

- 5.1 **Cladding Thickness:** After rolling, the average cladding thickness shall be as shown. Routine measurements are not required.

Total Thickness of Composite Product Inches	Cladding Thickness Per Side % of Total Thickness	
	min	max
0.062 and under	4.0	--
Over 0.062 to 0.187, incl	2.0	--
Over 0.187 to 0.499, incl	1.2	--
Over 0.499	1.2	3.0

- 5.2 **Tensile Properties:** Test specimens shall conform to ASTM E8-54T except from material less than 3/4 in. wide, and shall be cut across the direction of rolling except from material less than 9 in. wide. Elongation requirements apply only to material 3/4 in. and over in width.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against infringement of patents."

Ø Nominal Thickness Inches	Yield Strength at 0.2% Offset or at Extension Indicated (See 5.2.1)		Elongation % in 2 in. min
	Tensile Strength psi, min	Extension Under Load in. in 2 in.	
0.008 to 0.009, incl	58,000	39,000	10
Over 0.009 to 0.020, incl	59,000	39,000	12
Over 0.020 to 0.062, incl	59,000	39,000	15
Over 0.062 to 0.128, incl	62,000	40,000	15
Over 0.128 to 0.187, incl	62,000	40,000	13
Over 0.187 to 0.249, incl	63,000	41,000	13
Over 0.249 to 0.499, incl	63,000	40,000	11
Over 0.499 to 1.000, incl	62,000	40,000	8
Over 1.000 to 1.500, incl	60,000	40,000	7
Over 1.500 to 2.000, incl	60,000	40,000	6
Over 2.000 to 3.000, incl	56,000	40,000	4

5.2.1 Extension under load is based upon the following values of E:

Nominal Thickness Inches	E
0.062 and under	9,500,000
Over 0.062 to 0.499, incl	10,000,000
Over 0.499	10,600,000

5.2.2 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.

5.3 Bending: Material 0.249 in. and under in thickness shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to direction of rolling.

Nominal Thickness Inch	Bend Factor
0.010 to 0.040, incl	4
Over 0.040 to 0.124, incl	5
Over 0.124 to 0.249, incl	8

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest Issue of AMS 2202 as applicable. Thickness tolerances shall conform to Table II.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.