



# AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

## AMS 4045D

Superseding AMS 4045C

Issued 6-1-49

Revised 11-1-67

### ALUMINUM ALLOY SHEET AND PLATE 5.6Zn - 2.5Mg - 1.6Cu - 0.30Cr (7075-T6)

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for structural parts which will be painted or otherwise protected from corrosion. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.
- 3. COMPOSITION:**

	min	max
Zinc	5.1	6.1
Magnesium	2.1	2.9
Copper	1.2	2.0
Chromium	0.18	0.40
Iron	--	0.7
Silicon	--	0.50
Manganese	--	0.30
Titanium	--	0.20
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 4. CONDITION:** Solution and precipitation heat treated.
- 5. TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

#### 5.1 Tensile Properties:

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,300,000)		Elongation % in 2 in. or 4D, min
		psi, min	in. in 2 in.	
0.015 to 0.039, incl	76,000	65,000	0.0166	7
Over 0.039 to 0.499, incl	77,000	66,000	0.0168	8
Over 0.499 to 1.000, incl	77,000	66,000	0.0168	6
Over 1.000 to 2.000, incl	77,000	66,000	0.0168	4
Over 2.000 to 2.500, incl	73,000	62,000	0.0160	3
Over 2.500 to 3.000, incl	70,000	60,000	0.0157	3
Over 3.000 to 3.500, incl	70,000	57,000	0.0151	3
Over 3.500 to 4.000, incl	67,000	53,000	0.0143	2

- 5.1.1** When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard, recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.1.2 Tensile properties of plate over 4.000 in. in thickness shall be as agreed upon by purchaser and vendor.
- 5.2 Bending: Material shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the material with axis of bend parallel to direction of rolling.

Nominal Thickness Inch	Bend Factor
0.015 to 0.020, incl	7
Over 0.020 to 0.062, incl	8
Over 0.062 to 0.091, incl	9
Over 0.091 to 0.125, incl	10
Over 0.125 to 0.249, incl	11
Over 0.249 to 0.499, incl	14

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202. Flatness tolerances for material over 3.000 in. thick shall be as agreed upon by purchaser and vendor.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.
- 8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
9. IDENTIFICATION: Unless otherwise specified, each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4045 or applicable Federal or Military specification designation, inspection lot number, manufacturer's identification, and nominal thickness in inches. An inspection lot shall be material of the same alloy, temper, section, and size traceable to a heat treatment lot or lots and subjected to inspection at one time. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling.
- 9.1 Flat Sheet and Plate Under 6 In. Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet. The inspection lot number may appear in the row marking or may appear at only one location on the piece.
- 9.2 Flat Sheet and Plate 0.375 In. and Under Thick, 6 - 60 In., Incl, Wide, and 36 - 200 In., Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft, the rows being spaced approximately 6 in. on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness in inches. The other rows shall show the alloy number and temper and AMS 4045 or applicable Federal or Military specification designation. The inspection lot number may be included in the rows with the alloy, temper, and specification designations or may appear at only one location on each piece.