

SAE-AMS4049

## ADOPTION NOTICE

SAE-AMS4049, "Sheet and Plate, Alclad, 5.6ZN 2.5MG 1.6CU 0.23CR, Solution and Precipitation Heat Treated," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, Attn: DISC-E, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

## Custodians:

Army - MR

Navy - AS

Air Force - 11

Adopting Activity

DLA - IS

FSC 9535

DISTRIBUTION STATEMENT A. Approved for public release;  
distribution is unlimited.

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 4049H

Issued 10-1-51  
Revised 4-1-87

Superseding AMS 4049G

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD  
5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (Alclad 7075; -T6 Sheet - T651 Plate)  
Solution and Precipitation Heat Treated

UNS A97075

## 1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of sheet and plate.
- 1.2 Application: Primarily for structural use, including machined parts subject to excessive warpage during machining. Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

### 2.1.1 Aerospace Material Specifications:

- AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate  
MAM 2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate
- AMS 2350 - Standards and Test Methods  
AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings  
MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

**2.1.2 Aerospace Recommended Practices:**

ARP 823 - Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

**2.2 U.S. Government Publications:** Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.**2.2.1 Military Specifications:**

MIL-H-6088 - Heat Treatment of Aluminum Alloys

**2.2.2 Military Standards:**

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

**3. TECHNICAL REQUIREMENTS:****3.1 Composition:** Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	Core (7075)			Cladding (7072)	
	min	max		min	max
Zinc	5.1	6.1	Zinc	0.8	1.3
Magnesium	2.1	2.9	Silicon + Iron	--	0.7
Copper	1.2	2.0	Magnesium	--	0.10
Chromium	0.18	0.28	Copper	--	0.10
Iron	--	0.50	Manganese	--	0.10
Silicon	--	0.40	Other Impurities, each	--	0.05
Manganese	--	0.30	Other Impurities, total	--	0.15
Titanium	--	0.20	Aluminum	remainder	
Other Impurities, each	--	0.05			
Other Impurities, total	--	0.15			
Aluminum	remainder				

**3.2 Condition:** The product shall be supplied in the following condition; heat treatments shall be performed in accordance with MIL-H-6088:

**3.2.1 Sheet:** Solution and precipitation heat treated.

**3.2.2 Plate:** Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%, and precipitation heat treated.

**3.2.2.1 Plate** shall receive no further straightening operations after stretching.

**3.3 Properties:** The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.  
Ø

TABLE I

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
0.008 to 0.011, incl	68,000	58,000	5
Over 0.011 to 0.039, incl	71,000	61,000	8
Over 0.039 to 0.062, incl	72,000	62,000	9
Over 0.062 to 0.187, incl	74,000	64,000	9
Over 0.187 to 0.249, incl	76,000	65,000	9
Over 0.249 to 0.499, incl	75,000	65,000	9
Over 0.499 to 1.000, incl	78,000	68,000	7
Over 1.000 to 2.000, incl	77,000	67,000	6
Over 2.000 to 2.500, incl	76,000	64,000	5
Over 2.500 to 3.000, incl	72,000	61,000	5
Over 3.000 to 3.500, incl	71,000	58,000	5
Over 3.500 to 4.000, incl	67,000	54,000	3

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation %, min	
			in 50 mm	in 5D
0.20 to 0.28, incl	470	400	5	--
Over 0.28 to 0.98, incl	490	420	8	--
Over 0.98 to 1.55, incl	495	430	9	--
Over 1.55 to 4.75, incl	510	440	9	--
Over 4.75 to 6.25, incl	525	450	9	--
Over 6.25 to 12.50, incl	515	450	9	--
Over 12.50 to 25.00, incl	540	470	--	6
Over 25.00 to 50.00, incl	530	460	--	5
Over 50.00 to 62.50, incl	525	440	--	4
Over 62.50 to 75.00, incl	495	420	--	4
Over 75.00 to 87.50, incl	490	400	--	4
Over 87.50 to 100.00, incl	460	370	--	2

3.3.1.1 Tensile property requirements for plate over 4.000 in. (100.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.008 to 0.499 in. (0.20 to 12.50 mm), incl, in nominal thickness shall withstand, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inch	Millimetres	
0.008 to 0.020, incl	0.20 to 0.50, incl	6
Over 0.020 to 0.063, incl	Over 0.50 to 1.58, incl	7
Over 0.063 to 0.091, incl	Over 1.58 to 2.28, incl	8
Over 0.091 to 0.125, incl	Over 2.28 to 3.12, incl	9
Over 0.125 to 0.249, incl	Over 3.12 to 6.25, incl	10
Over 0.249 to 0.499, incl	Over 6.25 to 12.50, incl	12

3.3.2.1 Bending requirements for product over 0.499 in. (12.50 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.3 Cladding Thickness: After rolling, the average cladding thickness per side shall be as follows:

Total Thickness of Composite Product		Cladding Thickness Per Side % of Total Thickness	
Inches	Millimetres	min	max
0.008 to 0.062, incl	0.20 to 1.55, incl	3.2	--
Over 0.062 to 0.187, incl	Over 1.55 to 4.75, incl	2.0	--
Over 0.187 to 0.499, incl	Over 4.75 to 12.50, incl	1.2	--
Over 0.499 to 4.000, incl	Over 12.50 to 100.00, incl	1.2	3.0

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for bending (3.3.2) and cladding thickness (3.3.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4049H, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4049H, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4049H or applicable Federal specification designation, inspection lot number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.

5.1.1 Flat Sheet and Plate Under 6 In. (150 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm). The inspection lot number may appear in the row marking or may appear at only one location on each piece.

5.1.2 Flat Sheet and Plate 0.375 In. (9.50 mm) and Under Thick, 6 - 60 In. (150 - 1500 mm), Incl, Wide, and 36 - 200 In. (900 - 5000 mm), Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced approximately 6 in. (150 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the alloy number and temper and AMS 4049 or applicable Federal specification designation. The inspection lot number may be included in the rows with the alloy number, temper, and specification designations or may appear at only one location on each piece.