

# AEROSPACE MATERIAL SPECIFICATION



AMS 4051F

Issued MAR 1955  
Revised APR 1985  
Noncurrent APR 1986  
Reaf. Noncur. OCT 2000

Superseding AMS 4051E

Aluminum Alloy Sheet and Plate, Alclad  
6.8Zn - 2.8Mg - 2.0Cu - 0.23Cr (Alclad 7178-0)  
Annealed

## NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April 11, 1986. It is recommended, therefore, that this specification not be specified for new designs.

SAENORM.COM : Click to view the full PDF of AMS4051f

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

**1. SCOPE:****1.1 Form:**

This specification covers an aluminum alloy in the form of sheet and plate.

**1.2 Application:**

Primarily for structural use, including machine tapered parts. Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP 823 recommends practices to minimize such conditions.

**2. APPLICABLE DOCUMENTS:**

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

AMS 2202	Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate
MAM 2202	Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate
AMS 2350	Standards and Test Methods
AMS 2355	Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings
MAM 2355	Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units
AMS 2770	Heat Treatment of Aluminum Alloy Parts

**2.1.2 Aerospace Recommended Practices:**

ARP 823	Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products
---------	--

**2.2 U.S. Government Publications:**

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

## 2.2.1 Military Specifications:

MIL-H-6088 Heat Treatment of Aluminum Alloys

## 2.2.2 Military Standards:

MIL-STD-649 Aluminum and Magnesium Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

## Core (7178)

	min		max
Zinc	6.3	-	7.3
Magnesium	2.4	-	3.1
Copper	1.6	-	2.4
Chromium	0.18	-	0.28
Iron	--		0.50
Silicon	--		0.40
Manganese	--		0.30
Titanium	--		0.20
Other Impurities, each	--		0.05
Other Impurities, total	--		0.15
Aluminum	remainder		

## Cladding (7072)

	min		max
Zinc	0.8	-	1.3
Silicon + Iron	--		0.7
Copper	--		0.10
Magnesium	--		0.10
Manganese	--		0.10
Other Impurities, each	--		0.05
Other Impurities, total	--		0.15
Aluminum	remainder		

## 3.2 Condition:

Annealed in accordance with MIL- H-6088.

## 3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

## 3.3.1 As Annealed:

## 3.3.1.1 Tensile Properties:

TABLE I

Nominal Thickness Inch	Tensile Strength psi, max	Yield Strength at 0.2% Offset psi, max	Elongation in 2 in. or 4D %, min
0.015 to 0.062, incl	36,000	20,000	10
Over 0.062 to 0.187, incl	38,000	20,000	10
Over 0.187 to 0.500, incl	40,000	21,000	10
0.500	40,000	--	10

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, max	Yield Strength at 0.2% Offset MPa, max	Elongation in 50 mm or 4D %, min
Over 0.40 to 1.60, incl	250	140	10
Over 1.60 to 4.00, incl	265	140	10
Over 4.00 to 12.50, incl	275	145	10
Over 12.50 to 12.70, incl	275	--	10

3.3.1.1.1 Tensile property requirements for plate over 0.500 in. (12.70 mm) thick shall be as agreed upon by purchaser and vendor.

3.3.2 After Solution and Precipitation Heat Treatment: The product, as received by purchaser, shall have the following properties after solution and precipitation heat treatment in accordance with AMS 2770 to the -T62 temper.

## 3.3.2.1 Tensile Properties:

TABLE II

Nominal Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
0.015 to 0.044, incl	76,000	66,000	7
Over 0.044 to 0.062, incl	78,000	68,000	8
Over 0.062 to 0.187, incl	80,000	70,000	8
Over 0.187 to 0.500, incl	82,000	71,000	8
0.500	84,000	73,000	6

TABLE II (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D %, min
Over 0.40 to 1.20, incl	525	455	7
Over 1.20 to 1.60, incl	540	470	8
Over 1.60 to 4.00, incl	550	480	8
Over 4.00 to 12.50, incl	565	490	8
Over 12.50 to 12.70, incl	580	505	6

3.3.2.1.1 Tensile property requirements for plate over 0.500 in. (12.70 mm) thick shall be as agreed upon by purchaser and vendor.

3.3.3 Cladding Thickness: After rolling, the average cladding thickness shall conform to the requirements shown in Table III.

TABLE III

Nominal Thickness		Cladding Thickness per side % of Total Thickness	
Inches	Millimetres	min	max
0.015 to 0.062, incl	0.40 to 1.60, incl	3.2	-
Over 0.062 to 0.187, incl	Over 1.60 to 4.00, incl	2	-
Over 0.187 to 0.500, excl	Over 4.00 to 12.50, incl	1.2	-
0.500	Over 12.50 to 12.70, incl	1.2	3

## 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties as annealed (3.3.1.1) and after solution and precipitation heat treatment (3.3.2.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for cladding thickness (3.3.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling:

Shall be in accordance with AMS 2355 or MAM 2355.

### 4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and to the other technical requirements of this specification. This report shall include the purchase order number, AMS 4051F, size, and quantity.

4.4.2 The vendor of finished or semi-finished shall furnish with each shipment a report showing the purchase order number, AMS 4051F, contractor or other direct supplier of material, part number, and quantity. When material not making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.