



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

## AMS 4058C

Superseding AMS 4058B

Issued 1-15-60

Revised 5-1-68

### ALUMINUM ALLOY SHEET 4.4Mg - 0.65Mn - 0.15Cr (5083-H343)

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for parts requiring little forming and where welding and good resistance to corrosion are important. Excessive cold work or prolonged heating in the temperature range of 150 - 300 F (66 - 149 C) may cause susceptibility to stress corrosion.
- 3. COMPOSITION:**

	min	max
Magnesium	4.0	4.9
Manganese	0.30	1.0
Chromium	0.05	0.25
Iron	--	0.40
Silicon	--	0.40
Zinc	--	0.25
Titanium	--	0.15
Copper	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 4. CONDITION:** Strain-hardened half hard and then stabilized.
- 5. TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

**5.1 Tensile Properties:**

Nominal Thickness Inch	Tensile Strength psi	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,200,000)		Elongation, % in 2 in. min
		psi	Extension Under Load in. in 2 in.	
0.051 to 0.125, incl	50,000 - 59,000	39,000 - 49,000	0.0116 - 0.0136	6
Over 0.125 to 0.249, incl	50,000 - 59,000	39,000 - 49,000	0.0116 - 0.0136	8

- 5.1.1** If sizes other than those shown are ordered, tensile property requirements shall be as agreed upon by purchaser and vendor.
- 5.1.2** When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.
- 6. QUALITY:** Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

SAE Technical Board rules provide that: "All technical reports, including standards, applications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."