



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

SPECIFICATION

AMS 4062F

Superseding AMS 4062E

Issued 11-1-45

Revised 1-15-76

UNS A91100

ALUMINUM TUBING, SEAMLESS, DRAWN, ROUND (1100-H14)

1. SCOPE:

- 1.1 Form: This specification covers aluminum in the form of seamless, drawn, round tubing.
- 1.2 Application: Primarily for parts and assemblies, such as brackets, conduits, and low-pressure lines, where good weldability and resistance to corrosion are required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2203 - Tolerances, Aluminum Alloy Drawn Tubing
- AMS 2350 - Standards and Test Methods
- AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

- 2.2 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120

2.2.1 Military Standards:

- MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
Aluminum (by difference)	99.00	--
Copper	0.05	0.20
Iron + Silicon	--	1.0
Zinc	--	0.10
Manganese	--	0.05
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15

- 3.2 Condition: Strain hardened.

- 3.3 Properties: The product shall conform to the following requirements:

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard in any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3.3.1 Tensile Properties: Shall be as follows for tubing having nominal wall thickness of 0.014 - 0.500 in. ϕ (0.36 - 12.70 mm), incl, determined in accordance with AMS 2355:

Tensile Strength, min 16,000 psi (110 MPa)

3.3.2 Flattening: Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to 6 times the nominal wall thickness.

3.3.2.1 If tubing does not pass the flattening test of 3.3.2, a section of tube not less than 1/2 in. (12.7 mm) in length and embracing 1/3 to 1/2 the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 deg (3.14 rad) around a diameter equal to 4 times the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

3.3.3 Flarability: Tubing with nominal OD of 0.375 in. (9.52 mm) and under shall withstand being double-flared and tubing with nominal OD over 0.375 in. (9.52 mm) shall withstand being single-flared without formation of cracks or other visible defects. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered steel pin having 74 deg (1.29 rad) included angle to produce a flare having the permanent expanded OD not less than specified in Table I.

TABLE I

Nominal OD Inches	Expanded OD Inches	Nominal OD Inches	Expanded OD Inches
0.125	0.224	1.000	1.187
0.188	0.302	1.250	1.500
0.250	0.359	1.500	1.721
0.312	0.421	1.750	2.106
0.375	0.484	2.000	2.356
0.500	0.656	2.500	2.856
0.625	0.781	3.000	3.356
0.750	0.937		

TABLE I (SI)

Nominal OD Millimetres	Expanded OD Millimetres	Nominal OD Millimetres	Expanded OD Millimetres
3.18	5.69	25.40	30.15
4.78	7.67	31.75	38.10
6.35	9.12	38.10	43.71
7.92	10.69	44.45	53.49
9.52	12.29	50.80	59.84
12.70	16.66	63.50	72.54
15.88	19.84	76.20	85.24
19.05	23.80		

3.3.3.1 Tubing with nominal OD between any two standard sizes given in 3.3.3 shall take the same percentage flare as shown for the larger of the two sizes.

3.3.3.2 Tubing with nominal OD greater than 3.000 in. (76.20 mm) or less than 0.125 in. (3.18 mm) shall have flarability as agreed upon by purchaser and vendor.

3.4 Quality: Tubing shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2203.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile property (3.3.1), and tolerance (3.5) requirements are classified as acceptance or routine control tests.

4.2.2 Qualification Tests: Tests to determine conformance to flattening (3.3.2) and flarability (3.3.5) requirements are classified as qualification or periodic control tests.

4.2.2.1 For direct U. S. Military procurement, qualification test material and supporting test data shall be submitted to the cognizant qualification agency as directed by the request for procurement, the procuring activity, or the contracting officer.

4.3 Sampling: Shall be in accordance with AMS 2355, and the following:

4.3.1 Specimens for flaring may be cut from any portion of the tube or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded except for sizes 0.375 in. (9.52 mm) and under.

4.4 Reports:

4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report stating that the tubing conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows: