

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 4064D

Issued MAY 1968
Revised NOV 1995

Superseding AMS 4064C

ALUMINUM ALLOY, CLAD TWO SIDES SHEET
1.25Mn - 0.12Cu (No. 12-0 Brazing Sheet)
Annealed

UNS A83003

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of clad sheet.

1.2 Application:

This sheet has been used typically for brazed assemblies which are not subject to heat treatment after joining, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2202 Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM 2202 Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

AMS 2811 Identification, Aluminum and Magnesium Alloy Wrought Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1995 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

AMS 4064D

SAE

AMS 4064D

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1 and Table 2, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition, Core (3003)

Element	min	max
Manganese	1.0	1.5
Copper	0.05	0.20
Iron	--	0.7
Silicon	--	0.6
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

TABLE 2 - Composition, Cladding (4343)

Element	min	max
Silicon	6.8	8.2
Iron	--	0.8
Copper	--	0.25
Zinc	--	0.20
Manganese	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Annealed.

AMS 4064D

SAE

AMS 4064D

3.3 Properties:

Sheet shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as shown in Table 3.

TABLE 3A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi, max	Elongation in 2 inches or 4D %, min
0.006 to 0.007, incl	20.0	12
Over 0.007 to 0.012, incl	20.0	15
Over 0.012 to 0.031, incl	20.0	18
Over 0.031 to 0.050, incl	20.0	20
Over 0.050 to 0.249, incl	20.0	23

TABLE 3B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa, max	Elongation in 50.8 mm or 4D %, min
0.15 to 0.18, incl	138	12
Over 0.18 to 0.30, incl	138	15
Over 0.30 to 0.79, incl	138	18
Over 0.79 to 1.27, incl	138	20
Over 1.27 to 6.32, incl	138	23

3.3.2 Bending: Sheet shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.3.3 Cladding: Shall be applied to both faces of the core.

3.3.3.1 Cladding Thickness: After rolling, the average cladding thickness shall be as shown in Table 4.

TABLE 4 - Average Cladding Thickness

Total Thickness of Composite Product Inch	Total Thickness of Composite Product Millimeters	Cladding Thickness Per Side % of Total Thickness
Up to 0.063, incl	Up to 1.60, incl	8 to 12
Over 0.063 to 0.250, excl	Over 1.60 to 6.35, excl	4 to 6

AMS 4064D

SAE

AMS 4064D

3.4 Quality:

Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the sheet.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

4. QUALITY ASSURANCE PROVISIONS:**4.1 Responsibility for Inspection:**

The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are (R) acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests: Bending (3.3.2) and cladding thickness (3.3.3.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

(R) Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

(R) The vendor of clad sheet shall furnish with each shipment a report stating that the sheet conforms to the chemical composition and showing the results of tests on each inspection lot to determine conformance to the other acceptance test requirements and, when performed, to the periodic test requirements. This report shall include the purchase order number, inspection lot number, AMS 4064D, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:**5.1 Identification:**

(R) Shall be in accordance with AMS 2811.