

Issued	1968-05
Revised	2008-01
Reaffirmed	2013-05
Superseding AMS4064E	

Aluminum Alloy, Clad Two Sides Sheet
1.25Mn - 0.12Cu (No. 12-0 Brazing Sheet)
Annealed

(Compositions similar to UNS A83003)

RATIONALE

AMS4064F has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of clad sheet.

1.2 Application

This sheet has been used typically for brazed assemblies which are not subject to heat treatment after joining, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4064F>**

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1 and Table 2, determined in accordance with AMS 2355.

TABLE 1 - COMPOSITION, CORE (3003)

Element	min	max
Silicon	--	0.6
Iron	--	0.7
Copper	0.05	0.20
Manganese	1.0	1.5
Zinc	--	0.10
Other elements, each	--	0.05
Other elements, total	--	0.15
Aluminum	remainder	

TABLE 2 - COMPOSITION, CLADDING (4343)

Element	min	max
Silicon	6.8	8.2
Iron	--	0.8
Copper	--	0.25
Manganese	--	0.10
Zinc	--	0.20
Other elements, each	--	0.05
Other elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Annealed (See 8.5).

3.3 Properties

Sheet shall conform to the following requirements, determined on the mill produced size in accordance with AMS 2355.

3.3.1 Tensile Properties

Shall be as shown in Table 3.

TABLE 3A - TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inch	Tensile Strength ksi, max	Elongation in 2 inches or 4D %, min
0.006 to 0.007, incl	20.0	12
Over 0.007 to 0.012, incl	20.0	15
Over 0.012 to 0.031, incl	20.0	18
Over 0.031 to 0.050, incl	20.0	20
Over 0.050 to 0.249, incl	20.0	23

TABLE 3B - TENSILE PROPERTIES, SI UNITS

Nominal Thickness Millimeters	Tensile Strength MPa, max	Elongation in 50.8 mm or 4D %, min
0.15 to 0.18, incl	138	12
Over 0.18 to 0.30, incl	138	15
Over 0.30 to 0.79, incl	138	18
Over 0.79 to 1.27, incl	138	20
Over 1.27 to 6.32, incl	138	23

3.3.2 Bending

Sheet shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.3.3 Cladding

Shall be applied to both faces of the core.

3.3.3.1 Cladding Thickness

After rolling, the average cladding thickness shall be as shown in Table 4.

TABLE 4 - AVERAGE CLADDING THICKNESS

Total Thickness of Composite Product Inch	Total Thickness of Composite Product Millimeters	Average Cladding Thickness Per Side % of Total Thickness
Up to 0.063, incl	Up to 1.60, incl	8 to 12
Over 0.063 to 0.250, excl	Over 1.60 to 6.35, excl	4 to 6

3.4 Quality

Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the sheet.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests

Bending (3.3.2) and cladding thickness (3.3.3.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS 2355.

4.4 Reports

The vendor of clad sheet shall furnish with each shipment a report stating that the sheet conforms to the composition and showing the results of tests on each inspection lot to determine conformance to the other acceptance test requirements and, when performed, to the periodic test requirements. This report shall include the purchase order number, inspection lot number, AMS 4064F, size, and quantity. This report shall also identify the producer, the product form, and the size of the mill product.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with ASTM B 666/B 666M.

5.2 Packaging

5.2.1 Product shall be protected from damage during storage and shipment by a method determined by vendor unless specified by purchaser. Examples of typical protective methods include but are not limited to interleaving with paper or oiling of the surfaces.

5.2.2 Sheet shall be prepared for shipment in accordance with ASTM B 660 and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the sheet to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A vendor shall include this specification number and its revision letter in all quotations and when acknowledging purchase orders.