

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 4067G

Issued 1 JUN 1942
Revised 1 OCT 1993

Superseding AMS 4067F

Submitted for recognition as an American National Standard

ALUMINUM ALLOY, DRAWN ROUND SEAMLESS TUBING
1.25Mn - 0.12Cu (3003-H14)
Strain Hardened

UNS A93003

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of seamless drawn tubing.

1.2 Application:

This tubing has been used typically for parts, such as brackets, conduits, and low-pressure lines, requiring good weldability and resistance to corrosion, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2203	Tolerances, Aluminum Alloy Drawn Tubing
MAM 2203	Tolerances, Metric, Aluminum Alloy Drawn Tubing
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled Forged, or Flash Welded Rings, Metric (SI) Units
AMS 2811	Identification, Aluminum and Magnesium Alloy Wrought Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4067G

SAE

AMS 4067G

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	Min	Max
Manganese	1.0	1.5
Copper	0.05	0.20
Iron	--	0.7
Silicon	--	0.6
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Strain hardened to H14 temper.

3.3 Properties:

Tubing shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as specified in Table 2 and 3.3.1.1.
(R)3.3.1.1 Tensile property requirements for tubing under 0.010 inch (0.25 mm) or over 0.500 inch (12.70 mm) in nominal wall thickness shall be as agreed upon by purchaser and vendor.
(R)

AMS 4067G

SAE

AMS 4067G

(R) TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

Nominal Wall Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D, % Strip	Elongation in 2 Inches or 4D, % Full Section
0.010 to 0.024, incl	20.0	17.0	--	3
Over 0.024 to 0.049, incl	20.0	17.0	3	5
Over 0.049 to 0.259, incl	20.0	17.0	4	8
Over 0.259 to 0.500, incl	20.0	17.0	--	--

(R) TABLE 2B - Minimum Tensile Properties, SI Units

Nominal Wall Thickness mm	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %, Strip	Elongation in 50.8 mm or 4D %, Full Section
0.25 to 0.61, incl	138	117	--	3
Over 0.61 to 1.24, incl	138	117	3	5
Over 1.24 to 6.58, incl	138	117	4	8
Over 6.58 to 12.70, incl	138	117	--	--

3.3.2 Flattening: Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to six times the nominal wall thickness.

3.3.2.1 If tubing does not pass the flattening test of 3.3.2, a section of tube not less than 0.500 inch (12.70 mm) in length and embracing one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to four times the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with ID of tube on inside of bend.

3.3.3 Flareability: Specimens as in 4.3.1 from tubing 0.375 inch (9.52 mm) and under in nominal OD shall withstand being double-flared (see 8.2) and from tubing over 0.375 inch (9.52 mm) in nominal OD shall withstand being single-flared without formation of cracks or other visible defects by being forced axially, at room temperature, with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than that specified in Table 3.

AMS 40676

SAE

AMS 40676

TABLE 3A - Flarability, Parameters, Inch/Pound Units

Nominal OD Inches	Expanded OD Inches	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781	2.500	2.856
		3.000	3.356

TABLE 3B - Flarability, Parameters, SI Units

Nominal OD mm	Expanded OD mm	Nominal OD mm	Expanded OD mm
3.18	5.08	19.05	23.80
4.78	7.67	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84	63.50	72.54
		76.20	85.24

3.3.3.1 Tubing with nominal OD between any two standard sizes shown in Table 3 shall take the same percentage flare as that for the next larger standard size.

3.3.3.2 Flarability requirements for tubing under 0.125 inch (3.18 mm) or over 3.000 inches (76.20 mm) in nominal OD shall be as agreed upon by purchaser and vendor.

3.4 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Detrimental surface imperfections include, but are not limited to, cracks, (R) splits, seams, inclusions, or severe crosshatching (surface breaks) that cannot be removed by light manual or machine polishing using 180 grit or finer abrasive.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2203 or MAM 2203.