

ALUMINUM ALLOY TUBING, SEAMLESS, DRAWN
6.3Cu - 0.30Mn - 0.18Zr - 0.10V - 0.06Ti (2219-T351)

UNS A92219

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of seamless, drawn, round tubing 0.500 in. (12.50 mm) and over in OD with wall thickness of 0.029 - 0.500 in. (0.75 - 12.50 mm).
- 1.2 Application: Primarily for structures requiring good fusion weldability and a combination of good strength and resistance to stress-corrosion cracking after precipitation heat treatment.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2203 - Tolerances, Aluminum Alloy Drawn Tubing
- MAM 2203 - Tolerances, Metric, Aluminum Alloy Drawn Tubing
- AMS 2350 - Standards and Test Methods
- AMS 2355 - Quality Assurance Sampling and Testing of Aluminum and Magnesium Alloys, Wrought Products (Except Forgings) and Flash Welded Rings
- MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forgings) and Flash Welded Rings

- 2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
Copper	5.8	6.8
Manganese	0.20	0.40
Zirconium	0.10	0.25
Vanadium	0.05	0.15
Titanium	0.02	0.10
Iron	--	0.30
Silicon	--	0.20
Zinc	--	0.10
Magnesium	--	0.02
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition: Solution heat treated and stress relieved by stretching to produce a permanent set of 1/2 - 3%; solution heat treatment shall be performed in accordance with MIL-H-6088.

3.3 Properties: Tubing shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties:

3.3.1.1 As Solution Heat Treated and Stress-Relieved: Shall be as specified in Table I:

TABLE I

Nominal Wall Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. %, min	
			Strip	Full Section
0.029 to 0.049, incl	45,000	26,000	--	12
Over 0.049 to 0.500, incl	45,000	26,000	12	14

3.3.1.1 (Continued):

TABLE I (SI)

Nominal Wall Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm %, min	
			Strip	Full Section
0.74 to 1.24, incl	310	179	--	12
Over 1.24 to 12.70, incl	310	179	12	14

3.3.2 After Precipitation Heat Treatment: Tubing precipitation heat treated in accordance with MIL-H-6088 shall have properties as specified in Table II:

TABLE II

Nominal Wall Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. %, min	
			Strip	Full Section
0.029 to 0.049, incl	60,000	42,000	--	6
Over 0.049 to 0.500, incl	60,000	42,000	6	8

TABLE II (SI)

Nominal Wall Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm %, min	
			Strip	Full Section
0.75 to 1.25, incl	415	290	--	6
Over 1.25 to 12.50, incl	415	290	6	8

3.4 Quality: Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2203 or MIL 2203.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.
- 4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.
- 4.4 Reports:
- 4.4.1 The vendor of tubing shall furnish with each shipment a report stating that the tubing conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4068A, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4068A, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification and shall include in the report either a statement that the tubing conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.
5. PREPARATION FOR DELIVERY:
- 5.1 Identification: Straight tubes shall be marked in a row of characters recurring at intervals not greater than 3 ft (900 mm) with the alloy number and temper, AMS 4068, and manufacturer's identification. The inspection lot number shall be included in the row marking or shall be marked near one end. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the tubing or its performance.
- 5.2 Packaging:
- 5.2.1 Tubing shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the tubing to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-649, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Tubing not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.