



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 1000

**AMS 4071G**  
Superseding AMS 4071F

Issued 5-1-45  
Revised 11-1-68

## ALUMINUM ALLOY TUBING, HYDRAULIC, SEAMLESS, DRAWN, ROUND 2.5Mg - 0.25Cr (5052-0)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for aircraft hydraulic systems up to 1500 psi operating pressure.
3. **COMPOSITION:**

	min	max
Magnesium	2.2	- 2.8
Chromium	0.15	- 0.35
Iron + Silicon	--	0.45
Zinc	--	0.10
Manganese	--	0.10
Copper	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

4. **CONDITION:** Annealed, then drawn if required to meet dimensional tolerances.
  - 4.1 Unless otherwise specified, tubing shall be supplied unground.
5. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.
  - 5.1 **Tensile Properties:** The following requirements apply to tubing having nominal wall thickness of  $\phi$  0.010 to 0.450 in., inclusive:

Tensile Strength psi	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10, 100, 000)	
	psi	Extension Under Load in. in 2 in.
25,000 min	10,000 min	0.0060
35,000 max	20,000 min	0.0080

- 5.1.1 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.
- 5.2 **Flattening:** Tubing having nominal wall thickness less than 10% of the nominal OD shall be capable of withstanding, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to 3 times the nominal wall thickness.

SAE Technical Board rules provide that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2.1 If tubing does not pass the flattening test of 5.2, a section of the tube not less than 1/2 in. in length and embracing 1/3 to 1/2 the circumference of the tube shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

5.3 Flarability: Tubing with nominal OD of 0.375 in. and under shall be capable of being double-flared and tubing with nominal OD over 0.375 in. shall be capable of being single-flared without formation of cracks or other visible defects. Specimens for flaring may be cut from any portion of the tube, or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded except for sizes 0.375 in. and under. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg included angle, to produce a flare having the permanent expanded OD specified in the following table:

Nominal OD Inches	Expanded OD Inches, min	Nominal OD Inches	Expanded OD Inches, min
0.125	0.200	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781	2.500	2.856
		3.000	3.356

5.3.1 Tubing with intermediate nominal OD shall take the same percentage flare as that for the next larger OD.

5.3.2 Tubing with nominal OD greater than 3.000 in. or less than 0.125 in. shall have flarability as agreed upon by purchaser and vendor.

5.4 Hydraulic Strength: Each length of tubing shall be capable of withstanding an internal hydrostatic pressure (P), based on the following formula, without developing leaks and without an increase in mean diameter of more than 0.2%.

$$P = S \frac{D^2 - d^2}{D^2 + d^2}$$

where, S = Minimum yield strength from 5.1.  
 D = Maximum OD (nominal OD plus tolerance) inches.  
 d = Maximum ID (computed as D minus twice the minimum permissible wall thickness) inch.

5.4.1 Mean diameter is the average of two diameters at right angles to each other in the same transverse plane; measurements before and after testing should be taken at substantially the same location.

## 6. QUALITY:

6.1 Tubing shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. A polished and etched cross-section of a tube shall show no evidence of cracks, seams, or folds when examined at a magnification of 100 diameters.

6.1.1 Detrimental imperfections include, but are not limited to, any cracks, splits, seams, inclusions, or  $\emptyset$  severe crosshatching (surface breaks) that cannot be removed by lightly hand-sanding, using 180 grit or finer sandpaper.