

# AEROSPACE MATERIAL SPECIFICATION

**SAE** AMS4078

REV. J

Issued 1967-04  
Revised 2011-10

Superseding AMS4078H

Aluminum Alloy Sheet and Plate  
5.6Zn – 2.5Mg-1.6Cu-0.23Cr  
7075: (-T73 Sheet, -T7351 Plate)  
Solution Heat Treated and Overaged  
(Composition similar to UNS A97075)

## RATIONALE

AMS4078J adds tensile strength values for sheet to Table 2 and corrects the metric equivalent for conductivity in 3.3.2.1.

### 1. SCOPE

#### 1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate.

#### 1.2 Application

This product has been used typically for parts requiring high strength and resistance to stress-corrosion cracking, but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970, [www.sae.org](http://www.sae.org).

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS1990 Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS4078J>**

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B 666/B 666M Identification Marking of Aluminum Products

## 2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, [www.ansi.org](http://www.ansi.org).

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	--	0.40
Iron	--	0.50
Copper	1.2	2.0
Manganese	--	0.30
Magnesium	2.1	2.9
Chromium	0.18	0.28
Zinc	5.1	6.1
Titanium	--	0.20
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

### 3.2 Condition

3.2.1 Sheet - Solution heat treated, and precipitation heat treated to T73 temper (See AS1990). Heat treatment shall be performed in accordance with AMS2772.

3.2.2 Plate - Solution heat treated, stretched to produce a nominal permanent set of 2%, but not less than 1-1/2% nor more than 3%, and precipitation heat treated to T7351 temper (See AS1990). Heat treatment shall be performed in accordance with AMS2772.

3.2.2.1 Plate shall receive no straightening operations after stretching.

### 3.3 Properties

Sheet and plate shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size:

#### 3.3.1 Tensile Properties

Shall be as specified in Table 2.

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Over 0.039 to 0.249, incl	67.0	56.0	8
Over 0.250 to 1.000, incl	69.0	57.0	7
Over 1.000 to 2.000, incl	69.0	57.0	6
Over 2.000 to 2.500, incl	66.0	52.0	6
Over 2.500 to 3.000, incl	64.0	49.0	6
Over 3.000 to 3.500, incl	63.0	49.0	6
Over 3.500 to 4.000, incl	61.0	48.0	6

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Over 0.991 to 6.32, incl	462	386	8
Over 6.35 to 25.40, incl	476	393	7
Over 25.40 to 50.80, incl	476	393	6
Over 50.80 to 63.50, incl	455	359	6
Over 63.50 to 76.20, incl	441	338	6
Over 76.20 to 88.90, incl	434	338	6
Over 88.90 to 101.60, incl	421	331	6

#### 3.3.2 Corrosion Resistance

Resistance to stress corrosion cracking and to exfoliation-corrosion shall be acceptable if the product conforms to 3.3.2.1 or 3.3.2.2.

- 3.3.2.1 If electrical conductivity is not lower than 40.0% IACS (International Annealed Copper Standard) (23.2 MS/m), determined on the surface of specimens used for tensile testing.
- 3.3.2.2 If electrical conductivity is 38.0 to 39.9% (22.0 to 23.1 MS/m) inclusive, and yield strength does not exceed the specified minimum by more than 11.9 ksi (82 MPa).
- 3.3.2.3 If the requirements of 3.3.2.1 or 3.3.2.2 are not met, the product may be given additional precipitation heat treatment or re-heat treated. If, after such treatment, all specified properties are met, the product is acceptable.
- 3.3.2.4 If the conductivity is below 38.0% IACS (22.0 MS/m), the product is not acceptable and must be reprocessed, regardless of tensile properties.

### 3.3.3 Stress-Corrosion Resistance

Specimens cut from plate 0.750 inches (19.05 mm) and over in nominal thickness shall show no evidence of stress-corrosion cracking when stressed in the short-transverse direction to 75% of the applicable minimum yield strength specified in 3.3.1.

### 3.4 Quality

Sheet and plate, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the plate.

3.4.1 When specified, each plate 0.500 inch (12.70 mm) and over in nominal thickness shall be ultrasonically inspected in accordance with ASTM B 594 and shall meet the requirements of 3.4.1.1 as applicable.

3.4.1.1 Plates weighing 2000 pounds (907 kg) and under shall meet the requirements for ultrasonic class shown in Table 3.

TABLE 3 - ULTRASONIC CLASS

Nominal Thickness Inches	Nominal Thickness Millimeters	Ultrasonic Class
Over 0.500 to 1.500, excl	Over 12.70 to 38.10, excl	B
Over 1.500 to 3.000, incl	Over 38.10 to 76.20, incl	A
Over 3.000 to 4.000, incl	Over 76.20 to 101.60, incl	B

### 3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The vendor of sheet and plate shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the plate conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), conductivity (3.3.2), tolerances (3.5), and, when specified, ultrasonic soundness (3.4.1) are acceptance tests and, except for composition, shall be performed on each lot.

#### 4.2.2 Periodic Tests

Stress-corrosion resistance (3.3.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling and Testing

Shall be in accordance with AMS2355.