

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4083

Issued 11-1-48

Revised

ALUMINUM ALLOY TUBING

1.0Mg - 0.6Si - 0.25Cu - 0.25Cr (61S-T6)
Hydraulic

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

Magnesium	0.80 - 1.20
Silicon	0.40 - 0.80
Copper	0.15 - 0.40
Chromium	0.15 - 0.35
Iron	0.70 max
Zinc	0.20 max
Manganese	0.15 max
Titanium	0.15 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

3. CONDITION:

3.1 Solution and precipitation heat treated.

3.2 Unless otherwise specified, tubing shall be supplied unground.

4. TECHNICAL REQUIREMENTS:

4.1 Physical Properties: Tubing shall conform to the following requirements:

Nominal OD Inches	Nominal Wall Thickness Inch	Tensile Strength psi. min	Yield Strength at 0.2% offset or at extension indicated		Elongation Under Load Inch in 2 in. % in 2 in., min
			psi. min	psi. min	
1/4 to 2, incl	0.025 - 0.049	42,000	35,000	0.0110	8
1/4 to 2, incl	0.050 - 0.500	42,000	35,000	0.0110	10

4.2 Flattening: Tubing shall be capable of being flattened sidewise under a gradually applied load, without cracking, to an outside dimension eight times the wall thickness while under load.

4.3 Hydraulic Strength: Each length of tubing shall be capable of withstanding an internal hydrostatic pressure (P), calculated according to the following formula, without developing leaks and without an increase in mean diameter of more than 0.2%:

$$P = \frac{1.9tS}{D-t}$$

SAE Technical Board rules provides that: "All technical reports, including standards, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

where:

P = test pressure in pounds per square inch,

t = minimum wall thickness (nominal wall thickness minus maximum negative tolerance) in inches,

S = minimum yield strength from 4.1, and

D = nominal OD of tube in inches.

Note: Mean diameter is the average of two diameters at right angles to each other in the same transverse plane; measurements before and after testing should be taken at substantially the same location.

5. QUALITY:

5.1 Tubing shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. A polished and etched cross section of a tube shall show no evidence of cracks, seams, or folds when examined at a magnification of 100 diameters.

5.2 Cleanliness of Tubing: Tubing shall be free from grease or other foreign matter and shall have a good workmanlike finish. No metallic flakes or particles shall be collected by a clean white cloth when it is drawn through the length of the bore of a test sample. The presence of metallic flakes or particles on the cloth will be cause for rejection. Discoloration of the cloth, without the presence of flakes or grit, will not be cause for rejection.

6. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2203 as applicable. Diameter and wall thickness tolerances shall be as specified below:

6.1 Diameter: Table I, Columns headed "Mean Diameter", and "Individual Diameter" for Heat Treatable Alloys.

6.2 Wall Thickness: Table II, Columns headed "Mean Wall Thickness" and "Individual Wall Thickness" for Heat Treatable Alloys.

7. REPORTS:

7.1 Unless otherwise specified, the vendor of tubing shall furnish with each shipment three copies of a notarized report stating that the physical properties and chemical composition of the tubing conform to the requirements specified. This report shall include the purchase order number, material specification number, size, and quantity.

7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a notarized report showing the purchase order number, material specification number, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report, a certification that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.