



AEROSPACE MATERIAL SPECIFICATION	AMS4087	REV. H
	Issued 1945-11 Revised 2006-09 Reaffirmed 2015-05 Superseding AMS4087G	
Aluminum Alloy Tubing, Seamless, Drawn (2024-0) Reinstate Composition Annealed (Composition similar to UNS A92024)		

RATIONALE

AMS4087H has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of seamless, drawn tubing.

1.2 Application

These parts have been used typically for parts requiring a high-strength, non-weldable alloy. Parts are usually solution heat treated and aged before use, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged or Flash Welded Rings
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials
AS 4330	Standard Dimensions for, Design Standard Tubing, Flared
AS 33583	Standard Dimensions for Tubing End Double Flare

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4087H>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Product
 ASTM B 666/B 666M Identification Marking of Aluminum Products

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355:

TABLE 1 - COMPOSITION

Element	min	max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Annealed.

3.3 Properties

Tubing shall conform to the following requirements, determined in accordance with AMS 2355 on the mill produced size.

3.3.1 As Annealed

3.3.1.1 Tensile Properties

Shall be as shown in Table 2 for tubing having nominal wall thickness of 0.18 to 0.500 inch (0.46 to 12.70 mm) inclusive.

TABLE 2 - AS ANNEALED, MAXIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	32.0 ksi (221 MPa)
Yield Strength at 0.2% Offset	15.0 ksi (103 MPa)

3.3.1.2 Flattening

Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to the flattening factor shown in Table 3 times the nominal wall thickness.

TABLE 3 - FLATTENING FACTOR

Nominal Wall Thickness Inch	Nominal Wall Thickness Millimeters	Factor
Up to 0.049, incl	Up to 1.24, incl	3
Over 0.049	Over 1.24	4

3.3.1.2.1 Retesting Procedure

If tubing does not pass the flattening test of 3.3.1.2, a section of tube not less than 1/2 inch (12.7 mm) in length and including one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

TABLE 4 - BENDING FACTOR

Nominal Wall Thickness Inch	Nominal Wall Thickness Millimeters	Factor
Up to 0.049, incl	Up to 1.24, incl	1
Over 0.049	Over 1.24	2

3.3.1.3 Flarability

Tubing of 0.375 inch (9.52 mm) and under in nominal OD shall withstand double-flaring and tubing over 0.375 inch (9.52 mm) in nominal OD shall withstand single-flaring without formation of cracks or other visible defects by being forced axially, at room temperature, with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than specified in Table 5. (See 8.2.1.)

TABLE 5A - FLARABILITY, INCH/POUND UNITS

Nominal OD Inch	Expanded OD Inch	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781	2.500	2.856
		3.000	3.356

TABLE 5B - FLARABILITY, SI UNITS

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
3.18	5.08	19.05	23.80
4.78	7.67	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84	63.50	72.54
		76.20	85.24

3.3.1.3.1 Tubing with nominal OD between any two standard sizes shown in 3.3.1.3 shall take the same percentage flare as shown for the larger of the two sizes.

3.3.2 After Solution Heat Treatment and Aging

Tubing as received by purchaser, after solution heat treatment in accordance with AMS 2772 and aging for not less than 4 days at room temperature to the T42 Temper, shall have the following properties:

3.3.2.1 Tensile Properties

Shall be as specified in Table 6.

TABLE 6A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Wall Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D % Cut Out Specimen	Elongation in 2 Inches or 4D % Full Section Specimen
0.018 to 0.024, incl	64.0	40.0	--	10
Over 0.024 to 0.049, incl	64.0	40.0	10	12
Over 0.049 to 0.259, incl	64.0	40.0	10	14
Over 0.259 to 0.500, incl	64.0	40.0	12	16

TABLE 6B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Wall Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D % Cut Out Specimen	Elongation in 50.8 mm or 4D % Full Section Specimen
0.46 to 0.61, incl	441	276	--	10
Over 0.61 to 1.24, incl	441	276	10	12
Over 1.24 to 6.58, incl	441	276	10	14
Over 6.58 to 12.70, incl	441	276	12	16

3.4 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Detrimental imperfections include, but are not limited to, cracks, splits, seams, inclusions, or severe crosshatching (surface breaks) that cannot be removed by lightly hand-sanding, using 180 grit or finer sandpaper.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties as annealed (3.3.1.1) and after solution heat treatment and aging (3.3.2), quality (3.4), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot of tubing.