

# AERONAUTICAL MATERIAL SPECIFICATIONS

**AMS 4088E**

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-1-42  
Revised 1-15-57

## ALUMINUM ALLOY TUBING, SEAMLESS, DRAWN 4.5Cu - 1.5Mg - 0.6Mn (2024-T3)

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Parts and assemblies such as brackets where high strength, non-weldable material is required.
- 3. COMPOSITION:**

Copper	3.8 - 4.9
Magnesium	1.2 - 1.8
Manganese	0.30 - 0.9
Iron	0.50 max
Silicon	0.50 max
Zinc	0.25 max
Chromium	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

- 4. CONDITION:** Solution heat treated.

### 5. TECHNICAL REQUIREMENTS:

#### 5.1 Tensile Properties:

Nominal Wall Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 9,900,000)		Elongation % in 2 in. min	
		psi, min	in. in 2 in.	Strip	Full Section
0.018 to 0.024, incl	64,000	42,000	0.0120	--	10
Over 0.024 to 0.049, incl	64,000	42,000	0.0120	10	12
Over 0.049 to 0.259, incl	64,000	42,000	0.0120	10	14
Over 0.259 to 0.500, incl	64,000	42,000	0.0120	12	16

- 5.1.1** When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.
- 5.2 Flattening:** Tubing having nominal wall thickness less than 10% of the nominal OD shall be capable of withstanding, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to 8 times the nominal wall thickness.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."