



AEROSPACE MATERIAL SPECIFICATION	AMS4088™	REV. L
	Issued 1942-01 Reaffirmed 2015-05 Revised 2022-04 Superseding AMS4088K	
Aluminum Alloy, Drawn, Seamless Tubing 4.4Cu - 1.5Mg - 0.60Mn (2024-T3) Solution Heat Treated and Cold Worked (Composition similar to UNS A92024)		

RATIONALE

AMS4088L results from a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (3.3.2, 3.6, 4.4.1, 5.1.1, 8.5), revisions to update applicable documents (Section 2, 3.2, 8.2) and ordering information (8.6), and allow use of the immediate prior revision of this specification (8.4).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of seamless, drawn tubing 0.018 to 0.500 inch (0.46 to 12.70 mm) in nominal wall thickness (see 8.6).

1.2 Application

This tubing has been used typically for parts requiring a high-strength alloy and part is not welded, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), or www.sae.org.

AMS2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloy Wrought Products, (Except Forging Stock), and Rolled, Forged or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS7766 Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4088L/>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM B660 Packaging/Packing of Aluminum and Magnesium Product

ASTM B666/B666M Identification Marking of Aluminum Products

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1/H35.1M Standard Alloy and Temper Designation System for Aluminum

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Solution heat treated in accordance with AMS2772 and cold worked (refer to ANSI H35.1/H35.1M).

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size.

3.3.1 Tensile Properties

Shall be as specified in Table 2.

Table 2A - Minimum tensile properties, inch/pound units

Nominal Wall Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D % Cut Out Specimen	Elongation in 2 Inches or 4D % Full Section Specimen
0.018 to 0.024, incl	64.0	42.0	--	10
Over 0.024 to 0.049, incl	64.0	42.0	10	12
Over 0.049 to 0.259, incl	64.0	42.0	10	14
Over 0.259 to 0.500, incl	64.0	42.0	12	16

Table 2B - Minimum tensile properties, SI units

Nominal Wall Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D % Cut Out Specimen	Elongation in 50.8 mm or 4D % Full Section Specimen
0.46 to 0.61, incl	441	290	--	10
Over 0.61 to 1.24, incl	441	290	10	12
Over 1.24 to 6.58, incl	441	290	10	14
Over 6.58 to 12.70, incl	441	290	12	16

3.3.2 Mechanical property requirements for tubing outside the thickness range of 1.1 shall be as agreed upon by purchaser and producer.

3.3.3 Flattening

Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to eight times the nominal wall thickness.

3.3.3.1 If tubing does not pass the flattening test of 3.3.2, a section of tube not less than 1/2 inch (12.7 mm) in length and embracing one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to six times the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

3.4 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Detrimental imperfections include, but are not limited to, cracks, splits, seams, inclusions, or severe crosshatching (surface breaks) that cannot be removed by lightly hand-sanding, using 180 grit or finer sandpaper.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

3.6 Exceptions

Any exceptions shall be authorized by purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), quality (3.4), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot of tubing.

4.2.2 Periodic Tests

Flattening (3.3.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The vendor of tubing shall furnish with each shipment a report stating that the tubing conforms to the composition and tolerances (and NDT inspection, when required) and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements and periodic test requirements when performed. This report shall include the purchase order number, inspection lot number(s), AMS4088L, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.1 When material produced to this specification is beyond the sizes allowed in the scope or tables, or exceptions authorized by purchaser are taken to the technical requirements listed in Section 3 (see 5.1.1), the report shall contain a statement "This material is certified as AMS4088L(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with ASTM B666/B666M.

5.1.1 When technical exceptions are taken (see 4.4.1), the material shall be identified with AMS4088(EXC).

5.2 Packaging

5.2.1 Tubing shall be oiled, prior to shipment, with a light corrosion-inhibiting oil.

5.2.2 Tubing shall be prepared for shipment in accordance with ASTM B660, and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the tubing to ensure carrier acceptance and safe delivery.