



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4107A

Superseding AMS 4107

Issued 6-15-75
Revised 1-15-77

UNS A97050

ALUMINUM ALLOY DIE FORGINGS
6.2 Zn - 2.2Mg - 2.3Cu - 0.12Zr (7050-T736)
Solution and Precipitation Heat Treated

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of high-strength die forgings and of forging stock.

1.2 Application: Primarily for structural applications requiring superior strength and resistance to stress-corrosion cracking.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn

AMS 2350 - Standards and Test Methods

AMS 2375 - Approval and Control of Critical Forgings

AMS 2630 - Ultrasonic Inspection

AMS 2645 - Fluorescent Penetrant Inspection

AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B342 - Electrical Conductivity by Use of Eddy Currents

ASTM B557 - Tension Testing Wrought and Cast Aluminum and Magnesium Alloy Products

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E34 - Chemical Analysis of Aluminum and Aluminum-Base Alloys

ASTM G47 - Determining Susceptibility to Stress-Corrosion Cracking of High Strength 7XXX Aluminum Alloy Products

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-649 - Aluminum, and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Zinc	5.7	6.7
Copper	2.0	2.6
Magnesium	1.9	2.6
Zirconium	0.08	0.15
Iron	--	0.15
Silicon	--	0.12
Manganese	--	0.10
Titanium	--	0.06
Chromium	--	0.04
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Forgings: Solution and precipitation heat treated.

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Heat Treatment: Forgings shall be solution heat treated by heating to $890^{\circ}\text{F} + 10$ ($477^{\circ}\text{C} \pm 6$), holding at heat for a time commensurate with section thickness but not less than 60 min., and quenching in water at $140^{\circ} - 160^{\circ}\text{F}$ ($60^{\circ} - 71^{\circ}\text{C}$) and precipitation heat treated by heating to $250^{\circ}\text{F} + 10$ ($121^{\circ}\text{C} \pm 6$), holding at heat for $24 \text{ hr} \pm 1$, followed by heating to $350^{\circ}\text{F} + 10$ ($177^{\circ}\text{C} \pm 6$), holding at heat for $12 \text{ hr} \pm 1$, and cooling in air.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Forgings: The following requirements apply to forgings having an as-forged thickness not more than twice the nominal thickness at time of heat treatment:

3.4.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557:

3.4.1.1.1 With Grain Flow: Test specimens, machined from forgings or from prolongations on such forgings with axis of specimen in the area of the gage length within 15 deg (0.262 rad) of parallel to the forging flow lines, shall have properties as specified in Table I.

TABLE I

Nominal Thickness At Time Of Heat Treatment Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
Up to 2, incl	72,000	62,000	7
Over 2 to 4, incl	71,000	61,000	7
Over 4 to 5, incl	70,000	60,000	7
Over 5 to 6, incl	70,000	59,000	7

TABLE I (SI)

Nominal Thickness At Time Of Heat Treatment Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
Up to 51, incl	496	427	7
Over 51 to 102, incl	490	421	7
Over 102 to 127, incl	483	414	7
Over 127 to 152, incl	483	407	7

3.4.1.1.2

Across Grain Flow: Test specimens, machined from forgings or from prolongations on such forgings with the axis of specimen in the area of the gage length deviating more than 15 deg (0.262 rad) from parallel to the forging flow lines, shall have properties as specified in Table II.

TABLE II

Nominal Thickness At Time Of Heat Treatment Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
Up to 2, incl	68,000	56,000	5
Over 2 to 4, incl	67,000	55,000	4
Over 4 to 6, incl	66,000	54,000	3

TABLE II (SI)

Nominal Thickness At Time Of Heat Treatment Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
Up to 51, incl	469	386	5
Over 51 to 102, incl	462	379	4
Over 102 to 152, incl	455	372	3

3.4.1.1.3

Special Purpose Forgings: Tensile test specimens cut from special purpose forgings or from forgings beyond the size and configuration limits covered by this specification shall meet the tensile property requirements specified on the drawing or agreed upon by purchaser and vendor.

3.4.1.2

Hardness: Should be not lower than 135 HB/10/500, 135 HB/14.3/1000, or 140HB/10/1000, determined in accordance with ASTM E10, but forgings shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4.1.3

Conductivity: Shall be as follows, determined in accordance with ASTM B342:

3.4.1.3.1

If the conductivity is 40% IACS (International Annealed Copper Standard) or higher and the yield strength in the parallel grain direction does not exceed the minimum specified in Table I by more than 9000 psi (62.1 MPa), the forgings are acceptable.

3.4.1.3.2

If the conductivity is 40% IACS or higher and the yield strength in the parallel grain direction exceeds the minimum specified in Table I by more than 9000 psi (62.1 MPa), the forgings shall be subjected to additional precipitation heat treatment to meet the requirements of 3.4.1.3.1.

- 3.4.1.3.3 If the conductivity is below 40% IACS, the forgings are unsatisfactory and shall be reprocessed regardless of mechanical property level.
- 3.4.1.4 Stress-Corrosion Resistance: Specimens, cut from forgings processed to meet the requirements of 3.4.1.3 and stressed in the short transverse (perpendicular to grain flow) direction to 50% of the specified minimum longitudinal (parallel to grain flow) yield strength, shall meet the requirements of ASTM G47.
- 3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.4.1.1, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to conduct such tests.
- 3.5 Quality: The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5.1 When specified, forgings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645 and/or to ultrasonic inspection in accordance with AMS 2630. Standards for acceptance shall be as agreed upon by purchaser and vendor.
- 3.6 Tolerances: Unless otherwise specified, tolerances for forging stock shall conform to all applicable requirements of AMS 2201.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests of the product to determine conformance to composition (3.1) requirements; of forgings to determine conformance to tensile property (3.4.1.1), hardness (3.4.1.2), and conductivity (3.4.1.3) requirements; and of forging stock to determine conformance to tolerance (3.6) requirements are classified as acceptance tests.
- 4.2.2 Periodic Tests: Tests of forgings to determine conformance to stress-corrosion resistance (3.4.1.4) requirements and of forging stock to determine ability to develop required properties (3.4.2) are classified as periodic tests.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests.
- 4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be as follows; a lot shall be all forgings of the same configuration or part number heat treated in the same batch furnace load or in a continuous furnace consecutively during an 8-hr period. The maximum lot size for forgings heat treated in a continuous furnace and charged consecutively during continuous furnace operation shall be 2000 lb (908 kg) for forgings weighing 5 lb (2.3 kg) or less shall be 6,000 lb (2724 kg) for forgings weighing over 5 lb (2.3 kg).
- 4.3.1 Acceptance Tests: