

Issued NOV 1968
Revised JUL 2003
Reaffirmed MAY 2008

Superseding AMS 4113D

Aluminum Alloy, Extruded Profiles
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr (6061-T6)
Solution and Precipitation Heat Treated

(Composition similar to A96061)

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of extruded profiles such as angles, channels, tees, zees, I-beams, and H-beams.

1.2 Application:

These products have been used typically for parts requiring moderate strength, especially where such parts require brazing or welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials

AS1990 Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM B 666/B 666M Identification Marking of Aluminum Products

2.3 ANSI Publications:

Available from ANSI, 25 West 43rd Street, New York, NY 10036 or www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - Composition

Element	min	max
Silicon	0.40	0.8
Iron	--	0.7
Copper	0.15	0.40
Manganese	--	0.15
Magnesium	0.8	1.2
Chromium	0.04	0.35
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Extruded and solution and precipitation heat treated to the T6 temper (see AS1990) in accordance with AMS 2772.

3.2.1 Profiles shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

3.3 Properties:

Profiles shall conform to the following requirements, determined on the mill product size in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

Nominal Diameter or Least Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.250, excl	38.0	35.0	8
0.250 and over	38.0	35.0	10

TABLE 2B - Minimum Tensile Properties, SI Units

Nominal Diameter or Least Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.35, excl	262	241	8
6.35 and over	262	241	10

3.4 Quality:

Extruded profiles, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the profiles.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of extruded profiles shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extruded profiles conform to specified requirements.

4.2 Classification of Tests:

Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355.

4.4 Reports:

The vendor of product shall furnish with each shipment a report stating that the product conforms to the chemical composition, tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS 4113E, size, and quantity. This report shall also identify the producer, the product form, and the size of the mill product.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

Shall be in accordance with ASTM B 666/B 666M.

5.2 Packaging:

Extruded profiles shall be prepared for shipment in accordance with ASTM B 660 and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the extruded profiles to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Extruded profiles not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

- 8.1 A change bar (|) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification, including technical revisions. Change bars and (R) are not used in original publications, nor in specifications that contain editorial changes only.