

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4122B

Issued 10-1-45

Revised 12-1-51

ALUMINUM ALLOY BARS, ROLLED 5.6Zn - 2.5Mg - 1.6Cu - 0.3Cr (75S-T6)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Rods, bars, and shapes.
3. **APPLICATION:** Primarily for parts requiring high strength and whose fabrication does not involve welding or forming.

4. **COMPOSITION:**

Zinc	5.1	-	6.1
Magnesium	2.1	-	2.9
Copper	1.2	-	2.0
Chromium	0.18	-	0.40
Iron	0.7	max	
Silicon	0.5	max	
Manganese	0.30	max	
Titanium	0.20	max	
Other Impurities, each	0.05	max	
Other Impurities, total	0.15	max	
Aluminum		remainder	

5. **CONDITION:** Solution and precipitation heat treated.

6. **TECHNICAL REQUIREMENTS:**

6.1 **Tensile Properties:**

Tensile Strength, psi	77,000 min
Yield Strength at 0.2% Offset or at 0.0168 inch in 2 in.	
Extension Under Load (E=10,300,000), psi	66,000 min
Elongation, % in 4D	7 min

- 6.1.1 Tensile properties of material under 0.125 in. or over 3 in. in diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

- 6.2 **Hardness:** Material should have hardness not lower than Brinell 135 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not lower than Brinell 140 using 1000 kg load and 10 mm ball, but shall not be rejected on the basis of hardness if the tensile property requirements are met.

7. **QUALITY:** Material shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."