

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

AMS 4122G

Issued 10-1-45
Revised 1-1-87

Superseding AMS 4122F

ALUMINUM ALLOY BARS AND RODS, ROLLED, DRAWN, OR COLD FINISHED, AND RINGS
5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-T6)
Solution and Precipitation Heat Treated

UNS A97075

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of rolled, drawn, or cold finished bars, rods, and wire, and of flash welded rings.
- 1.2 Application: Primarily for parts requiring high strength where limited formability is acceptable. Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn
- MAM 2201 - Tolerances, Metric, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled, Drawn, or Cold Finished
- AMS 2350 - Standards and Test Methods
- AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings
- MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Measurement
- AMS 4186 - Aluminum Alloy Bars and Rods, Rolled, Drawn, or Cold Finished, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-F), As Fabricated
- AMS 4187 - Aluminum Alloy Bars and Rods, Rolled, Drawn, or Cold Finished, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-0), Annealed

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.2 Aerospace Recommended Practices:

ARP 823 - Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Zinc	5.1	6.1
Magnesium	2.1	2.9
Copper	1.2	2.0
Chromium	0.18	0.28
Iron	--	0.50
Silicon	--	0.40
Manganese	--	0.30
Titanium	--	0.20
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars, Rods, and Wire: Rolled, drawn, or cold finished, as ordered, and solution and precipitation heat treated in accordance with MIL-H-6088.

3.2.2 Flash Welded Rings: Shall be manufactured in accordance with AMS 7488 and solution and precipitation heat treated in accordance with MIL-H-6088 from stock conforming to AMS 4186 or AMS 4187, as ordered.

3.3 Properties: Rods 4 in. (100 mm) and under in diameter; square, hexagonal, and octagonal bar 3-1/2 in. (87.5 mm) and under in thickness; rectangular bar 3 in. (75 mm) and under in thickness and 6 in. (150 mm) and under in width or 10 in. (250 mm) and under in width when thickness is less than 3 in. (75 mm); and flash welded rings within the above limits of radial thickness, as applicable to the stock used, shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties:

Tensile Strength, min	77,000 psi (530 MPa)
Yield Strength at 0.2% offset, min	66,000 psi (455 MPa)
Elongation in 4D, min	7%

3.3.2 Hardness: Should be not lower than 135 HB/10/500 or 140 HB/10/1000 but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.3.3 Tensile property and hardness requirements for product exceeding the size limits of 3.3 shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Bars, rods, and wire shall conform to all applicable requirements of AMS 2201 or MAM 2201.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

4.2.1.1 Composition (3.1) of the product.

4.2.1.2 Tensile properties (3.3.1) of each lot of bars, rods, wire, and flash welded rings.

4.2.1.3 Tolerances (3.5) of bars, rods, and wire.

4.2.2 Periodic Tests: Tests of bars, rods, wire, and flash welded rings to determine conformance to requirements for hardness (3.3.2) and of stock for flash welded rings to determine ability to develop required properties (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

∅

- 4.4.1 The vendor of bars, rods, wire, and stock for flash welded rings shall furnish with each shipment a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4122G, size or part number, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4122G, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars, Rods, and Wire:

- 5.1.1.1 Each straight bar and rod 0.500 in. (12.50 mm) and over in diameter or least width of flat surface shall be marked in a row of characters recurring at intervals not greater than 3 ft (900 mm) with the alloy number and temper, AMS 4122 or applicable Federal specification designation, and manufacturer's identification. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.
- 5.1.1.2 Smaller straight bars, rods, and wire shall be bundled, boxed, or secured on lifts and identified by two durable tags marked with the information of 5.1.1.1 and attached, not farther than 2 ft (600 mm) from each end, to the product in each bundle, box, or lift.
- 5.1.1.3 Coiled bars, rods, and wire and spooled wire shall be identified with the information of 5.1.1.1 marked on a durable tag attached to each coil or directly on one flange of each spool.

5.1.2 Flash Welded Rings: As agreed upon by purchaser and vendor.

5.2 Protective Treatment: The product shall be oiled, prior to shipment, with a tight corrosion-inhibiting oil.

5.3 Packaging: