

**AEROSPACE  
MATERIAL  
SPECIFICATION**

Submitted for recognition as an American National Standard

AMS 4130J  
Superseding AMS 4130H

Issued 3-13-40  
Revised 7-1-85

ALUMINUM ALLOY DIE FORGINGS  
4.4Cu - 0.85Si - 0.80Mn (2025-T6)  
Solution and Precipitation Heat Treated UNS A92025

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of die forgings and forging stock.

1.2 Application: Primarily for complex-shaped parts requiring moderate strength and good forgeability of the material. Certain design and processing procedures may cause these forgings to become susceptible to stress-corrosion cracking; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Cold Finished

MAM 2201 - Tolerances, Metric, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled, Drawn, or Cold Finished

AMS 2350 - Standards and Test Methods

AMS 2375 - Control of Forgings Requiring First-Article Approval

AMS 2645 - Fluorescent Penetrant Inspection

AMS 2808 - Identification, Forgings

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

### 2.1.2 Aerospace Recommended Practices:

ARP 823 - Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

### 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

ASTM B594 - Ultrasonic Inspection of Aluminum-Alloy Products for Aerospace Applications

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys

### 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

#### 2.3.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

### 3. TECHNICAL REQUIREMENTS:

#### 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Copper	3.9	5.0
Silicon	0.50	1.2
Manganese	0.40	1.2
Iron	--	1.0
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Magnesium	--	0.05
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

#### 3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Forgings: Solution and precipitation heat treated in accordance with MIL-H-6088.

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Forgings:

3.3.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557:

3.3.1.1.1 Test Specimens: Specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated forgings, shall have the following properties:

Tensile Strength, min	55,000 psi (380 MPa)
Yield Strength at 0.2% Offset, min	33,000 psi (230 MPa)
Elongation in 4D, min	16%

3.3.1.1.2 Forgings, With Grain Flow: Specimens, machined from forgings not over 4 in. (100 mm) in nominal thickness with the axis of specimen in the area of gage length varying not more than 15 deg from parallel to the forging flow lines, shall have properties as specified in 3.3.1.1.1 except that elongation may be as low as 11%.

3.3.1.1.3 Forgings, Across Grain Flow: Specimens, machined from forgings whose length is not greater than 4 times the thickness with the axis of specimen in the area of gage length varying not more than 15 deg from perpendicular to the forging flow lines, shall have the following properties:

Tensile Strength, psi	52,000 psi (360 MPa)
Yield Strength at 0.2% Offset, min	32,000 psi (220 MPa)
Elongation in 4D, min	8%

3.3.1.2 Hardness: Should be not lower than 100 HB/10/500 or 106 HB/10/1000, determined in accordance with ASTM E10, but forgings shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.3.1.3 Grain Flow: Except in areas which contain end grain, the grain flow shall follow the general contour of the forging, showing no evidence of re-entrant flow.

3.3.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, tensile specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1.1 and 3.3.1.2. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1.1 and 3.3.1.2, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to conduct such tests.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 When specified, forgings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645, to ultrasonic inspection in accordance with ASTM B594, or to both. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5 Tolerances: Forging stock shall conform to all applicable requirements of AMS 2201 or MAM 2201.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

4.2.1.1 Composition (3.1) of the product.

4.2.1.2 Tensile properties of each lot of forgings (3.3.1.1).

4.2.1.3 Tolerances (3.5) of forging stock.

4.2.2 Periodic Tests: Tests to determine conformance to the following requirements are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.2.1 Hardness (3.3.1.2) of forgings.

4.2.2.2 Ability of forging stock to develop required properties (3.3.2).

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be as follows; a lot shall be all forgings of the same part number, size, or nominal cross-section and configuration heat treated in the same batch-furnace load or in a continuous furnace consecutively during an 8-hr period. The maximum lot size for forgings heat treated in a continuous furnace shall be 6000 lb (2700 kg).
- 4.3.1 For Acceptance Tests:
- 4.3.1.1 Composition: At least one sample shall be taken by the producer from each group of ingots poured simultaneously from the same source of molten metal. Complete ingot analysis records shall be available to purchaser at the producer's facility.
- 4.3.1.1.1 Unless compliance with 4.3.1.1 is established, an analysis shall be made for each 6000 lb (2700 kg) or less of alloy comprising the lot except that not more than one analysis shall be required per piece.
- 4.3.1.2 Tensile Properties:
- 4.3.1.2.1 Forgings: At least one separately-forged coupon or one forging prolongation heat treated with each lot of forgings.
- 4.3.1.2.1.1 In lieu of a prolongation or separately-forged coupon, tensile tests shall be conducted on specimens cut, from locations designated on the drawing, from a forging representing each lot.
- 4.3.2 For Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor.
- 4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.
- 4.5 Reports:
- 4.5.1 The vendor of forgings shall furnish with each shipment a report stating that the chemical composition conforms to the requirements of this specification and showing the results of tests on each lot to determine conformance to the other acceptance test requirements of this specification. This report shall include the purchase order number, AMS 4130J, lot number, size or part number, and quantity.
- 4.5.2 The vendor of forging stock shall furnish with each shipment a report stating that the chemical composition of the stock conforms to the requirements of this specification. This report shall include the purchase order number, AMS 4130J, size, and quantity.