

Aluminum Alloy, Die and Hand Forgings, Rolled Rings, and Forging Stock
2.3Cu - 1.6Mg - 1.1Fe - 1.0Ni - 0.18Si - 0.07Ti (2618-T61)
Solution and Precipitation Heat Treated

(Composition similar to UNS A92618)

RATIONALE

AMS4132F results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of die forgings, hand forgings, rolled rings, and forging stock.

1.2 Application

These products have been used typically for rotating parts operating in service up to 450 °F (232 °C) and other parts operating up to 600 °F (316 °C) at low stresses, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2355	Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS2772	Heat Treatment of Aluminum Alloy Raw Materials
AMS2808	Identification, Forgings
AS1990	Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4132F>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM E 1417	Liquid Penetrant Examination

2.3 ANSI Publications

Available from ANSI American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, www.ansi.org.

ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	0.10	0.25
Iron	0.9	1.3
Copper	1.9	2.7
Magnesium	1.3	1.8
Nickel	0.9	1.2
Zinc	--	0.10
Titanium	0.04	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Die Forgings and Rolled Rings, and Hand Forgings 4 Inches (102 mm) and Under in Nominal Thickness

Solution and precipitation heat treated to Temper T61 (See AS1990).

3.2.2 Hand Forgings Over 4 Inches (102 mm) in Nominal Thickness

As forged.

3.2.3 Forging Stock

As ordered by the forging manufacturer.

3.3 Heat Treatment

Die forgings and rolled rings, and hand forgings 4 inches (102 mm) and under in nominal thickness shall be solution and precipitation heat treated in accordance with AMS2772 except that the product shall be quenched in boiling water.

3.4 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced product:

3.4.1 Forgings

3.4.1.1 Tensile Properties

Shall be as follows:

3.4.1.1.1 Die Forgings

3.4.1.1.1.1 Parallel With Grain Flow

Specimens, machined from forgings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with axis of specimen in the area of gage length varying not more than 15 degrees from parallel to the forging flow lines, shall have the properties shown in Table 2. Test results may be identified as longitudinal tensile properties.

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	58.0 ksi (400 MPa)
Yield Strength at 0.2% Offset	48.0 ksi (331 MPa)
Elongation in 4D	4%
in 5D	3%

3.4.1.1.1.2 Perpendicular to Grain Flow

Specimens, machined from forgings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with axis of specimen in the area of gage length varying not more than 15 degrees from perpendicular to the forging flow lines, shall have the properties shown in Table 3. Test results may be identified as transverse tensile properties.

TABLE 3 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	55.0 ksi (379 MPa)
Yield Strength at 0.2% Offset	45.0 ksi (310 MPa)
Elongation in 4D	4%
in 5D	3%

3.4.1.1.2 Hand Forgings

Specimens, machined from forgings having an essentially square or rectangular cross section not exceeding 144 square inches (929 cm²) and heat treated in the indicated thickness, shall have properties as specified in Table 4 provided the as-forged thickness does not exceed 4 inches (102 mm).

TABLE 4A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness at Time of Heat Treatment Inches	Specimen Orientation	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %
Up to 2, incl	Longitudinal	58.0	47.0	7
	Long-Trans.	55.0	42.0	5
Over 2 to 3, incl	Longitudinal	57.0	46.0	7
	Long-Trans.	55.0	42.0	5
	Short-Trans.	52.0	42.0	4
Over 3 to 4, incl	Longitudinal	56.0	45.0	7
	Long-Trans.	53.0	40.0	5
	Short-Trans.	51.0	39.0	4

TABLE 4B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Thickness at Time of Heat Treatment Millimeters	Specimen Orientation	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation % in 4D	Elongation % in 5D
Up to 51, incl	Longitudinal	400	324	7	6
	Long-Trans.	379	290	5	4
Over 51 to 76, incl	Longitudinal	393	317	7	6
	Long-Trans.	379	290	5	4
	Short-Trans.	359	290	4	3
Over 76 to 102, incl	Longitudinal	386	310	7	6
	Long-Trans.	365	276	5	4
	Short-Trans.	352	269	4	3

3.4.1.1.2.1 Short-transverse property requirements of Table 4 apply only to thicknesses 2.375 inches (60.32 mm) and over.

3.4.1.1.3 Rolled Rings

3.4.1.1.3.1 Tangential

Specimens, machined from rolled rings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with the axis of specimen tangential to the ring circumference (approximately parallel to the direction of rolling), shall have the properties shown in Table 5.

TABLE 5 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	55.0 ksi (379 MPa)
Yield Strength at 0.2% Offset	41.0 ksi (283 MPa)
Elongation in 4D	6%
in 5D	5%

3.4.1.1.3.2 Axial

Specimens, machined from rolled rings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with the axis of specimen parallel to the axis of the ring (transverse to direction of rolling), shall have properties as specified in 3.4.1.1.3.1 except that elongation may be as low as 5% in 4D or 4% in 5D.

3.4.1.1.3.3 Test Specimens

Specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated die forgings, shall have the following properties shown in Table 6.

TABLE 6 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength, minimum	58.0 ksi (400 MPa)
Yield Strength at 0.2% Offset, minimum	48.0 ksi (331 MPa)
Elongation in 4D, minimum	6%
in 5D, minimum	5%

3.4.1.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.4.2 Forging Stock

When a sample of stock is forged to a test coupon having a degree of mechanical working not greater than the forging and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1.4. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.4.1.1.4, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to conduct such tests.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Each die forging and rolled ring shall be etched by swabbing or immersing in an aqueous solution of sodium hydroxide, thoroughly rinsing in water, followed by washing in nitric acid or chromic-sulfuric acid solution or equivalent solution which will produce a surface suitable for visual inspection. Surfaces shall be evaluated for defects and, if defects can be removed so that they do not reappear on re-etching and if the required section thickness is maintained, die forgings and rolled rings are acceptable.

3.5.1.1 When approved by purchaser, a sampling plan may be used in lieu of etching each die forging or rolled ring.

3.5.2 When specified, die forgings and rolled rings shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417, to ultrasonic inspection in accordance with ASTM B 594, or both. Standards for acceptance shall be as agreed upon by purchaser.

3.6 Tolerances

Forging stock shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall except for composition be performed on each inspection lot:

4.2.1.1 Composition (3.1) of the product.

4.2.1.2 Tensile properties (3.4.1.1) of each lot of die forgings, hand forgings, and rolled rings and, when specified, fluorescent penetrant and/or ultrasonic inspections (3.5.2) of each lot of die forgings and rolled rings.

4.2.1.3 Visual surface inspection (3.5.1) of each lot of die forgings and rolled rings.

4.2.1.4 Tolerances (3.6) of forging stock.

4.2.2 Periodic Tests

The following requirements are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Grain flow of die forgings (3.4.1.2).

4.2.2.2 Ability of forging stock to develop required properties (3.4.2).

4.3 Sampling and Testing

Shall be in accordance with AMS2355 and 4.3.1. A lot shall be all forgings and rolled rings of the same nominal cross section and configuration heat treated in the same batch-furnace load or quenched from a continuous furnace consecutively during an 8 hour period. The maximum lot size for forgings and rolled rings heat treated in a continuous furnace shall be 6 000 pounds (2 722 kg).

4.3.1 Rolled Rings

At least two tensile specimens shall be taken from a ring or ring prolongation representing the lot; one specimen shall be tangential to the ring OD and the other parallel to the axis of the ring.

4.4 Reports

4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the composition, tolerances, and when specified, fluorescent penetrant or ultrasonic nondestructive tests, and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS4132F, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.2 The vendor of forging stock shall furnish with each shipment a report stating that the composition of the stock conforms to the requirements of this specification. This report shall include the purchase order number, AMS4132F, size, and quantity.