

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4150C

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 3-1-44
Revised 1-15-58

ALUMINUM ALLOY EXTRUSIONS 1Mg - 0.6Si - 0.25Cu - 0.25Cr (6061-T6)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Bars, rods, and shapes.

3. COMPOSITION:

∅	Magnesium	0.8 - 1.2
	Silicon	0.40 - 0.8
	Copper	0.15 - 0.40
	Chromium	0.15 - 0.35
	Iron	0.7 max
	Zinc	0.25 max
	Manganese	0.15 max
	Titanium	0.15 max
	Other Impurities, each	0.05 max
	Other Impurities, total	0.15 max
	Aluminum	remainder

4. CONDITION: Solution and precipitation heat treated.

4.1 ∅ Unless otherwise specified, extrusions shall be supplied with the as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	38,000 min
Yield Strength at 0.2% Offset or at 0.0111 in. in 2 in. Extension Under Load (E = 9,900,000), psi	35,000 min
Elongation, % in 2 in. or 4D	10 min

5.1.1 ∅ For material of such thickness that a standard specimen cannot be taken, or for material thinner than 0.062 in., the test for elongation is not required.

5.1.2 ∅ When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.

5.2 ∅ Hardness: Material should have hardness not lower than Brinell 80 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not lower than Brinell 84 using 1000 kg load and 10 mm ball, but shall not be rejected on the basis of hardness if the tensile property requirements are met.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no attempt to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."