

AERONAUTICAL MATERIAL SPECIFICATION

AMS 4152 F

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

Issued 11-1-41
Revised 2-1-56

ALUMINUM ALLOY EXTRUSIONS 4.5Cu - 1.5Mg - 0.6Mn (2024-T4)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Bars, rods, and shapes.
3. APPLICATION: Primarily for parts requiring good strength and whose fabrication does not involve welding.
4. COMPOSITION:

Copper	3.8 - 4.9
Magnesium	1.2 - 1.8
Manganese	0.30 - 0.9
Iron	0.50 max
∅ Silicon	0.50 max
Zinc	0.25 max
Chromium	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

5. CONDITION: Solution heat treated.

- 5.1 Unless otherwise specified, extrusions shall be supplied with the as-extruded surface finish; light polishing to remove minor surface imperfections is ∅ permissible provided such imperfections can be removed within the dimensional tolerances.

6. TECHNICAL REQUIREMENTS:

- 6.1 Tensile Properties:

Nominal Diameter or Least Thickness or Area Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,500,000)		Elongation % in 4D
		psi, min	Extension Under Load in. in 2 in.	
0.050 to 0.249, incl, all areas	57,000	42,000	0.0120	12
Over 0.249 to 0.719, incl, all areas	60,000	44,000	0.0124	12
Over 0.719 to 1.499, incl, all areas	65,000	46,000	0.0128	10
Over 1.499:				
Area 25 sq in. and under	70,000	52,000	0.0139	10
Area over 25 to 32 sq in., incl	68,000	48,000	0.0131	8

Section 7C of the SAE Technical Board rules provides that: "All technical reports, specifications, standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."