

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS4154A

Issued 10-1-45

Revised 11-1-46

### ALUMINUM ALLOY BARS (EXTRUDED) Zinc Magnesium Copper (75S-T)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **FORM:** Bars, rods, and shapes.

3. **COMPOSITION:**

Zinc	5.10 - 6.10
Magnesium	2.10 - 2.90
Copper	1.20 - 2.00
Chromium	0.15 - 0.40
Manganese	0.10 - 0.30
Iron	0.70 max
Silicon	0.50 max
Titanium	0.20 max
Other impurities, each	0.05 max
Other impurities, total	0.15 max
Aluminum	remainder

4. **CONDITION:** (a) Solution and precipitation heat treated conforming to the following minimum physical properties:

Diameter or Least Thickness or Area	Tensile Strength	Yield Strength at 0.2% Offset or at Extension Indicated		Elongation
		psi	psi	
Under 0.250	78,000	70,000	0.0175	6
0.250 to 4.00, incl				
20 sq. in. max	80,000	70,000	0.0175	6
Over 4.00 to 5.00 incl and over 20 sq. in. to				
25 sq. in., incl	78,000	68,000	0.0171	6
Over 25 sq. in. to				
32 sq. in., incl	75,000	65,000	0.0165	5

**Note:** The physical properties shall be based on the thickness of the portion of the extrusion from which the test specimens are taken and the physical properties of such specimens shall be in accordance with the values shown above.

(b) If sizes other than those shown under (a) are ordered, physical properties shall be as agreed between vendor and purchaser.

Section C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by one engaged in industry or trade is entirely voluntary. There is no agreement to adhere to the SAE standard or recommended practice, and no commitment to copyright or to be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patent infringement which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."