

Issued 1945-10  
Reaffirmed 2008-05  
Revised 2011-05  
Superseding AMS4154N

Aluminum Alloy, Extrusions  
5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-T6, 7075-T6510, 7075-T6511)  
Solution Heat Treated, Stress Relieved by Stretching When Required and Precipitation Heat Treated  
(Composition similar to UNS A97075)

#### RATIONALE

AMS4154P adds coverage for T6510 and T6511 tempers (3.2) to facilitate cancellation of AMS-QQ-A-200/11, AMS4168, and AMS4169, and corrects an error in Table 2.

#### 1. SCOPE

##### 1.1 Form

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing.

##### 1.2 Application

These extrusions have been used typically for parts requiring high strength and whose fabrication does not usually involve welding or forming, but usage is not limited to such applications.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS1990 Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS4154P>**

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B 594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM B 666/B 666M	Identification Marking of Aluminum and Magnesium Products

## 2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036-8002, Tel: 212-642-4900, [www.ansi.org](http://www.ansi.org).

ANSI H 35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H 35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	--	0.40
Iron	--	0.50
Copper	1.2	2.0
Manganese	--	0.30
Magnesium	2.1	2.9
Chromium	0.18	0.28
Zinc	5.1	6.1
Titanium	--	0.20
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminium	remainder	

### 3.2 Condition

Solution heat treated, stress-relieved by stretching to produce a nominal permanent set of 1.5%, but not less than 1% nor more than 3%, and precipitation heat treated to the T6511 or T6510 temper (see AS1900). Heat treatments shall be performed in accordance with AMS2772.

- 3.2.1 The T6511 temper shall be supplied unless T6510 is specified. When T6 is specified, the stress relief by stretching may be omitted and the T6 temper supplied if the stretching is not practical due to the shape of the extrusion.
- 3.2.2 Extrusions supplied in the T6 or T6511 temper may receive minor straightening, after stretching, of an amount necessary to meet the requirements of 3.5.
- 3.2.3 Extrusions supplied in the T6510 temper shall receive no straightening after stretching.
- 3.2.4 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

### 3.3 Properties

Extrusions shall conform to the following requirements, determined in accordance with AMS2355 on the mill product.

#### 3.3.1 Tensile Properties

Shall be as shown in 3.3.1.1 (Table 2) and 3.3.1.2 (Table 3).

##### 3.3.1.1 Longitudinal

TABLE 2A - MINIMUM LONGITUDINAL TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Dimensions Diameter or Thickness (rods, bars, wire, profiles) or Nominal Wall Thickness (tubing) Inches	Nominal Dimensions Cross-Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 inches or 4D %
Up to 0.249, incl	All areas	78.0	70.0	7
Over 0.249 to 0.499, incl	All areas	81.0	73.0	7
Over 0.499 to 2.999, incl	All areas	81.0	72.0	7
Over 2.999 to 4.999, incl	Up to 20, incl	81.0	71.0	7
Over 2.999 to 4.499, incl	Over 20 to 32, incl	78.0	70.0	6
Over 4.499 to 5.000, incl	Up to 32, incl	78.0	68.0	6

TABLE 2B - MINIMUM LONGITUDINAL TENSILE PROPERTIES, SI UNITS

Nominal Dimensions Diameter or Thickness (rods, bars, wire, profiles) or Nominal Wall Thickness (tubing) Millimeters		Nominal Dimensions Cross-Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to	6.32, incl	All areas	538	483	7
Over	6.32 to 12.67, incl	All areas	558	503	7
Over	12.67 to 76.17, incl	All areas	558	496	7
Over	76.17 to 114.27, incl	Up to 129, incl	558	490	7
Over	76.17 to 114.27, incl	Over 129 to 206, incl	538	483	6
Over	114.27 to 127.00, incl	Up to 206, incl	538	469	6

## 3.3.1.2 Long-Transverse; Rods, Bars, and Profiles

TABLE 3A - MINIMUM LONG TRANSVERSE TENSILE PROPERTIES, SI UNITS

Nominal Dimensions Diameter or Thickness Inches		Nominal Dimensions Cross-Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 inches or 4D %
Up to	0.249, incl	Up to 20, incl	76.0	66.0	5
Over	0.249 to 0.499, incl	Up to 20, incl	78.0	68.0	5
Over	0.499 to 0.749, incl	Up to 20, incl	76.0	66.0	4
Over	0.749 to 1.499, incl	Up to 20, incl	74.0	65.0	3
Over	1.499 to 2.999, incl	Up to 20, incl	70.0	61.0	1
Over	2.999 to 4.499, incl	Up to 20, incl	67.0	56.0	1
Over	2.999 to 4.499, incl	Over 20 to 32, incl	65.0	55.0	1

TABLE 3B - MINIMUM LONG TRANSVERSE TENSILE PROPERTIES, SI UNITS

Nominal Dimensions Diameter or Thickness Millimeters		Nominal Dimensions Cross-Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to	6.32, incl	Up to 129, incl	524	455	5
Over	6.32 to 12.67, incl	Up to 129, incl	538	469	5
Over	12.67 to 19.02, incl	Up to 129, incl	524	455	4
Over	19.02 to 38.07, incl	Up to 129, incl	510	448	3
Over	38.07 to 76.17, incl	Up to 129, incl	483	421	1
Over	76.17 to 114.27, incl	Up to 129, incl	462	386	1
Over	76.17 to 114.27, incl	Over 129 to 206, incl	448	379	1