



AEROSPACE MATERIAL SPECIFICATION	AMS4162™	REV. F
	Issued 1968-05 Reaffirmed 2008-05 Revised 2020-07 Superseding AMS4162E	
Aluminum Alloy, Extrusions 6.3Cu - 0.30Mn - 0.18Zr - 0.10V - 0.06Ti (2219-T8511) Solution Treated, Stress Relief Stretched, Straightened, and Precipitation Heat Treated (Composition similar to A92219)		

RATIONALE

AMS4162F deletes use of the Teal Sheets to resolve discrepancies in composition requirements (was 3.1.1), reformats tensile property tables (3.3.1) (formerly Tables 2 and 3), prohibits unauthorized exceptions (3.6), and revises condition (3.2), quality (3.4.1), reports (4.4.1), and identification (5.1.1), and results from a Five-Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing up through 2.999 inches (76.2 mm) in diameter, least thickness, or wall thickness and 25 square inches (161 cm²) or less in cross-sectional area (see 8.6).

1.2 Application

These extrusions have been used typically for structural parts requiring high strength up to 500 °F (260 °C), but usage is not limited to such applications. May be welded in the specified condition but properties are improved by reheat treatment after welding. Reheat treatment after welding, however, may reduce resistance to stress-corrosion cracking.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2020 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4162F>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged or Flash Welded Rings
AMS2772	Heat Treatment of Aluminum Alloy Raw Materials
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products
ASTM B660	Packaging/Packing of Aluminum and Magnesium Products
ASTM B666/B666M	Identification Marking of Aluminum and Magnesium Products
ASTM E10	Brinell Hardness of Metallic Materials
ASTM G47	Determining Susceptibility to Stress Corrosion Cracking of 2XXX and 7XXX Aluminum Alloys

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1/H35.1M	Standard Alloy and Temper Designation System for Aluminum
ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	--	0.20
Iron	--	0.30
Copper	5.8	6.8
Manganese	0.20	0.40
Magnesium	--	0.02
Zinc	--	0.10
Titanium	0.02	0.10
Vanadium	0.05	0.15
Zirconium	0.10	0.25
Other Elements, each	--	0.05
Other Elements, total	--	0.15

3.2 Condition

Solution heat treated, stress-relieved by stretching to produce a nominal permanent set of 1.5%, but not less than 1% nor more than 3%, and precipitation heat treated to the T8511 temper (refer to ANSI H35.1/H335.1M). Heat treatments shall be performed in accordance with AMS2772.

3.2.1 Extrusions may receive minor straightening, after stretching, of an amount necessary to meet the requirements of 3.5.

3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible, provided such imperfections can be removed within specified dimensional tolerances.

3.3 Properties

Extrusions shall conform to the following requirements, determined on the mill produced size in accordance with AMS2355.

3.3.1 Tensile Properties

Shall be as shown in Table 2 for extrusions up through 2.999 inches (76.20 mm) in nominal diameter or least thickness (bars, rods, wire, profiles) or nominal wall thickness (tubing) and 25 square inches (161 cm²) and under in cross-sectional area.

Table 2A - Minimum tensile properties, inch/pound units

Nominal Thickness Inches	Specimen Orientation	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up thru 2.999	Longitudinal	58.0	42.0	6
	Long-Trans.	56.0	39.0	4

Table 2B - Minimum tensile properties, SI units

Nominal Thickness Millimeters	Specimen Orientation	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up thru 76.20	Longitudinal	400	290	6
	Long-Trans.	386	269	4

3.3.1.1 Long-transverse tensile requirements apply only to extrusions from which a test specimen not less than 2.500 inches (63.50 mm) in length can be taken.

3.3.1.2 Mechanical properties for product outside the range covered by 1.1 shall be agreed upon between purchaser and producer.

3.3.2 Stress-Corrosion Resistance

Specimens, cut from extrusions 0.750 inch (19.05 mm) and over in nominal diameter or least thickness, shall exhibit no evidence of stress-corrosion cracking when stressed in the short-transverse (perpendicular to grain flow) direction to 30.0 ksi (207 MPa) when tested in accordance with ASTM G47.

3.4 Quality

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B594. Extrusions 0.500 inch (12.70 mm) and over in nominal thickness, shall meet ultrasonic Class B.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M, except that surface roughness tolerances shall be double those specified therein.

3.6 Exceptions

Any exceptions shall be authorized by purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of extrusions shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), longitudinal tensile properties (3.3.1), ultrasonic inspection when specified (3.4.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests

Long-transverse tensile properties (3.3.1) and stress-corrosion resistance (3.3.2) are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The producer of extrusions shall furnish with each shipment a report stating that the extrusions conform to the chemical composition, ultrasonic inspection when specified, and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number, AMS4162F, size or section identification number, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.1 When material produced to this specification is outside the range specified in 1.1, or has exceptions authorized by purchaser taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS4162F(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with ASTM B666/B666M.

5.1.1 When technical exceptions are taken (see 4.4.1), the material shall be marked with AMS4162(EXC).