

# AERONAUTICAL MATERIAL SPECIFICATIONS

## AMS 4164

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 6-30-60  
Revised

### ALUMINUM ALLOY EXTRUSIONS 4.5Cu - 1.5Mg - 0.6Mn (2024-T3510) Stress-Relief Stretched, Unstraightened

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders
2. FORM: Bars, rods, and shapes.
3. APPLICATION: Primarily for parts subject to excessive warpage during machining due to residual stresses, and for parts requiring good strength and whose fabrication does not involve welding.

4. COMPOSITION:

Copper	3.8 - 4.9
Magnesium	1.2 - 1.8
Manganese	0.30 - 0.9
Iron	0.50 max
Silicon	0.50 max
Zinc	0.25 max
Chromium	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

5. CONDITION: Solution heat treated and stress-relieved by a stretching.
  - 5.1 Unless otherwise specified, extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.
  - 5.2 Material shall be stretched in the solution heat treated condition to produce a nominal permanent set of 1-1/2%, but not less than 1% nor more than 3%.
  - 5.3 Material shall receive no straightening after stretching.
6. TECHNICAL REQUIREMENTS:

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

6.1 Tensile Properties:

Nominal Diameter or Least Thickness or Area Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,500,000)		Elongation % in 2 in. or 4D min
		psi, min	in. in 2 in.	
0.050 to 0.249, incl, all areas	57,000	42,000	0.0120	12
Over 0.249 to 0.749, incl, all areas	60,000	44,000	0.0124	12
Over 0.749 to 1.499, incl, all areas	65,000	46,000	0.0128	10
Over 1.499, Area 25 sq in. and under	70,000	52,000	0.0139	10
Area over 25 to 32 sq in., incl	68,000	48,000	0.0131	8

- 6.1.1 For material of such thickness that a standard specimen cannot be taken, or for material thinner than 0.062 in., the test for elongation is not required.
- 6.1.2 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.
- 6.1.3 The tensile property requirements shall be based on the thickness of the portion of the extrusion from which the tensile test specimens are taken.
- 6.1.4 If sizes other than those shown are ordered, tensile property requirements shall be as agreed upon by purchaser and vendor.
- 6.2 Hardness: Material should have hardness not lower than Brinell 100 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not lower than Brinell 106 using 1000 kg load and 10 mm ball, but shall not be rejected on the basis of hardness if the tensile property requirements are met.
7. QUALITY: Material shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
8. TOLERANCES: Unless otherwise specified, tolerances shall conform to the following:
- 8.1 Bars and Rods: The latest issue of AMS 2205 as applicable.
- 8.2 Shapes: As agreed upon by purchaser and vendor.
9. REPORTS:
- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, size or section identification number, and quantity.