



AEROSPACE MATERIAL SPECIFICATION

AMS4164

REV. H

Issued 1960-06
Revised 2003-10
Reaffirmed 2013-12

Superseding AMS4164G

Aluminum Alloy, Extrusions
4.4Cu - 1.5Mg - 0.60Mn (2024-T3510)
Stress-Relief Stretched, Unstraightened
(Composition similar to UNS A92024)

RATIONALE

AMS4164H has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing.

1.2 Application:

These products have been used typically for parts subject to excessive warpage during machining, and for parts requiring high strength and whose fabrication does not normally involve welding, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these extrusions to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4164H>

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials
ARP823	Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products
AS1990	Aluminum Alloy Tempers

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 594	Ultrasonic Inspection of Aluminum Alloy Wrought Products for Aerospace Applications
ASTM B 660	Packing/Packaging of Aluminum-Alloy Products for Aerospace Application
ASTM B 666/B 666M	Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from ANSI, 25 West 43rd Street, New York, NY 10036 or www.ansi.org.

ANSI H 35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H 35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Solution heat treated in accordance with AMS 2772 and stress-relieved by stretching to produce a nominal permanent set of 1.5%, but not less than 1% nor more than 3%, to the T3510 temper (see AS1990).

3.2.1 Extrusions shall receive no straightening after stretching.

3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

3.3 Properties:

Extrusions shall conform to the following requirements shown in Tables 2 and 3, determined in accordance with AMS 2355 on the mill product.

3.3.1 Tensile Properties: Shall be as shown in Table 2 or Table 3 as applicable.

3.3.1.1 Bars, Rods, Wire and Profiles:

TABLE 2A - Minimum Longitudinal Tensile Properties, Inch/Pound Units

Nominal Diameter or Thickness Inches	Nominal Cross-Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.249, incl	All areas	57.0	42.0	12
Over 0.249 to 0.749, incl	All areas	60.0	44.0	12
Over 0.749 to 1.499, incl	All areas	65.0	46.0	10
Over 1.499	Up to 25, incl	70.0	52.0	10
Over 1.499	Over 25 to 32, incl	68.0	48.0	8

TABLE 2B - Minimum Longitudinal Tensile Properties, SI Units

Nominal Diameter or Thickness Millimeters	Nominal Cross-Sectional Area Square Centimeters	Tensile	Yield Strength	Elongation in
		Strength MPa	at 0.2% Offset MPa	50.8 mm or 4D %
Up to 6.32, incl	All areas	393	290	12
Over 6.32 to 19.02, incl	All areas	414	303	12
Over 19.02 to 38.07, incl	All areas	448	317	10
Over 38.07	Up to 161, incl	483	359	10
Over 38.07	Over 161 to 206, incl	469	331	8

3.3.1.2 Round Tubing:

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

Nominal Wall Thickness Inches	Nominal Cross-Sectional Area Square Inches	Tensile	Yield Strength	Elongation in
		Strength ksi	at 0.2% Offset ksi	2 Inches or 4D %
Up to 0.249, incl	All areas	57.0	42.0	10
Over 0.249 to 0.749, incl	All areas	60.0	44.0	10
Over 0.749 to 1.499, incl	All areas	65.0	46.0	10
Over 1.499	Up to 25, incl	70.0	48.0	10
Over 1.499	Over 25 to 32, incl	68.0	46.0	8

TABLE 3B - Minimum Tensile Properties, SI Units

Nominal Wall Thickness Millimeters	Nominal Cross-Sectional Area Square Centimeters	Tensile	Yield Strength	Elongation in
		Strength MPa	at 0.2% Offset MPa	50.8 mm or 4D %
Up to 6.32, incl	All areas	393	290	10
Over 6.32 to 19.02, incl	All areas	414	303	10
Over 19.02 to 38.07, incl	All areas	448	317	10
Over 38.07	Up to 161, incl	483	331	10
Over 38.07	Over 161 to 206, incl	469	317	8

3.4 Quality:

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

- 3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B 594. Bars and profiles 0.500 inch (12.70 mm) and over in thickness, not exceeding 600 pounds (272 kg) in weight per piece, and not exceeding a width-to-thickness ratio of 10 to 1 shall meet discontinuity Class B.