



AEROSPACE MATERIAL SPECIFICATION

AMS4164™

REV. K

Issued 1960-06
Reaffirmed 2013-12
Revised 2025-03

Superseding AMS4164J

Aluminum Alloy, Extrusions,
4.4Cu - 1.5Mg - 0.60Mn (2024-T3510),
Solution Heat Treated, Cold Worked, Stress-Relieved by Stretching,
Unstraightened
(Composition similar to UNS A92024)

RATIONALE

AMS4164K results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (see 3.3.2 and 8.5), relocate Definitions (see 2.4), and update Applicable Documents (see Section 2), Hardness (see 8.2), and Ordering Information (see 8.6).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing produced with cross-sectional area of 32 square inches (206 cm²), maximum (see 8.6).

1.1.1 Tubing shall be additionally classified as follows:

Type	Description
I	Tubing extruded from hollow billets using die and mandrel
II	Tubing extruded from solid billets using porthole or spider die or similar tooling

When no Type is specified, Type I shall apply.

1.2 Application

These products have been used typically for parts subject to excessive warpage during machining and for parts requiring high strength and whose fabrication does not normally involve welding, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these extrusions to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2025 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4164K/>

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

ARP823 Minimizing Stress-Corrosion Cracking in Wrought High-Strength Aluminum Alloy Products

AS7766 Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products

ASTM B660 Packing/Packaging of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

ASTM E10 Brinell Hardness of Metallic Materials

2.3 ANSI Accredited Publications

Copies of these documents are available online at <https://webstore.ansi.org/>.

ANSI H35.1/H35.1M Standard Alloy and Temper Designation System for Aluminum

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

2.4 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Solution heat treated, cold worked, naturally aged, and stress-relieved by stretching to produce a nominal permanent set of 1.5%, but not less than 1% nor more than 3%, to the T3510 temper (refer to ANSI H35.1/H35.1M). Heat treatment shall be performed in accordance with AMS2772.

3.2.1 Extrusions shall receive no straightening after stretching.

3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

3.3 Properties

Extrusions shall conform to the following requirements shown in Tables 2 and 3, determined in accordance with AMS2355 on the mill product:

3.3.1 Tensile Properties

Shall be as shown in Tables 2 or 3, as applicable.

3.3.1.1 Bars, Rods, Wire, and Profiles

Table 2A - Minimum longitudinal tensile properties, inch/pound units

Nominal Diameter or Thickness Inches	Nominal Cross-Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.249, incl	All areas	57.0	42.0	12
Over 0.249 to 0.749, incl	All areas	60.0	44.0	12
Over 0.749 to 1.499, incl	All areas	65.0	46.0	10
Over 1.499	Up to 25, incl	70.0	52.0	10
Over 1.499	Over 25 to 32, incl	68.0	48.0	8

Table 2B - Minimum longitudinal tensile properties, SI units

Nominal Diameter or Thickness Millimeters	Nominal Cross-Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.32, incl	All areas	393	290	12
Over 6.32 to 19.02, incl	All areas	414	303	12
Over 19.02 to 38.07, incl	All areas	448	317	10
Over 38.07	Up to 161, incl	483	359	10
Over 38.07	Over 161 to 206, incl	469	331	8

3.3.1.2 Round Tubing

Table 3A - Minimum tensile properties, inch/pound units

Nominal Wall Thickness Inches	Nominal Cross-Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.249, incl	All areas	57.0	42.0	10
Over 0.249 to 0.749, incl	All areas	60.0	44.0	10
Over 0.749 to 1.499, incl	All areas	65.0	46.0	10
Over 1.499	Up to 25, incl	70.0	48.0	10
Over 1.499	Over 25 to 32, incl	68.0	46.0	8

Table 3B - Minimum tensile properties, SI units

Nominal Wall Thickness Millimeters	Nominal Cross-Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.32, incl	All areas	393	290	10
Over 6.32 to 19.02, incl	All areas	414	303	10
Over 19.02 to 38.07, incl	All areas	448	317	10
Over 38.07	Up to 161, incl	483	331	10
Over 38.07	Over 161 to 206, incl	469	317	8

3.3.2 Mechanical property requirements for extrusions outside the cross-sectional area limit of 1.1 shall be as agreed upon by the purchaser and producer and reported per 4.4.1 (see 8.6).

3.4 Quality

Extrusions, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B594. Extrusions, 0.50 inch (12.7 mm) and over in nominal diameter (wall thickness for tubes) or least distance between parallel sides, and not exceeding a 10:1 width-to-thickness ratio, shall meet ultrasonic Class B.

3.4.1.1 Acceptance criteria for extrusions exceeding the limitations of 3.4.1 shall be as agreed upon by the purchaser and producer and reported per 4.4.1 (see 8.6).

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.