

UNS A95056

ALUMINUM ALLOY WIRE
5.0Mg - 0.12Mn - 0.12Cr(5056-0)
Annealed

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of wire.

1.2 Application: Primarily for the manufacture of screen for reinforcement of, and to provide electrical conductivity through, rubber gaskets.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

2.3 U. S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

		min	max
∅	Magnesium	4.5	5.6
	Manganese	0.05	0.20
	Chromium	0.05	0.20
	Iron	--	0.40
	Silicon	--	0.30
	Copper	--	0.10
	Zinc	--	0.10
	Other Impurities, each	--	0.05
	Other Impurities, total	--	0.15
	Aluminum	remainder	

3.2 Conditions: Annealed.

3.2.1 When wire is supplied as screen, wire in one direction may be in a condition other than annealed.

3.3 Properties: Wire shall conform to the following requirements; tensile properties shall be determined in accordance with AMS 2355.

3.3.1 Tensile Properties:

Tensile Strength, max	46,000 psi (317 MPa)
Elongation in 2 in. (50 mm) or 4D, min	
Nominal Diameter	
0.125 to 0.375 in., excl	20%
(3.18 to 9.52 mm, excl)	

3.3.1.1 Elongation requirements for wire under 0.125 in. (3.18 mm) or over 0.375 in. (9.52 mm) in nominal diameter shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Wire shall withstand, without cracking, bending at room temperature flat on itself.

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the wire.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2201.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

∅ 4.3 Sampling: Shall be in accordance with AMS 2355.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment three copies of a report stating that the wire conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4182C, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 4182C, contractor or other direct supplier of wire, part number, and quantity. When wire for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of wire to determine conformance to the requirements of this specification, and shall include in the report a statement that the wire conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

Ø 4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification: Wire shall be identified as follows:

5.1.1 Wire, supplied on spools, shall contain 5, 10, 15, or 30 lb (2.28, 4.54, 6.80, or 13.6 kg), as ordered. Each spool shall be marked on one flange of the spool or on a durable tag attached to each spool and showing the nominal size, alloy number and temper, AMS 4182 or applicable Federal or Military specification designation, and manufacturer's identification.

5.1.2 Straight wire shall be bundled, boxed, or secured on lifts and identified by two durable tags marked with the information of 5.1.1 and attached, not farther than 2 ft (610 mm) from each end, to the wire in each bundle, box, or lift.

5.1.3 Coiled wire shall be identified with the information 5.1.1, marked on a durable tag attached to each Ø coil or directly on one flange of each spool.

5.1.4 Wire shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the wire to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.1.5 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-649, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.1.1, 5.1.2, and 5.1.4 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Wire not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi (Ø) symbol is used to indicate technical changes from the previous issue of this specification.

8.2 Dimensions and properties in inch/pound units are primary; dimensions and properties in SI units are shown as the approximate equivalents of the inch/pound units and are not to be construed as standard for extrusions produced to SI dimensions.