

AEROSPACE MATERIAL SPECIFICATION



AMS 4184E

Issued MAY 1948
Revised JUL 2000

Superseding AMS 4184D

Filler Metal, Aluminum Brazing
10Si - 4.0Cu (4145)

UNS A94145

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of wire, sheet, foil, pig, grains, shot, and chips.

1.2 Application:

This material has been used typically for joining aluminum by brazing, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Product
ASTM E 34 Chemical Analysis of Aluminum and Aluminum Alloys

2.2 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2(M) Dimensional Tolerances for Aluminum Mill Products (Metric)

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 34, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Silicon	9.3	10.7
Iron	--	0.8
Copper	3.3	4.7
Manganese	--	0.15
Magnesium	--	0.15
Zinc	--	0.20
Beryllium (3.1.1)	--	0.0008
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.1.1 Beryllium 0.0008 maximum for welding electrode and welding rod only.

3.2 Condition:

Filler metal shall be furnished in the following condition:

3.2.1 Round Wire, Flattened and Slit Wire, and Sheet: Annealed.

3.2.2 Pig, Grains, Shot, and Chips: As fabricated.

3.2.3 Foil: As ordered.

3.3 Quality:

Filler metal, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the filler metal.

3.4 Standard Sizes and Tolerances:

Filler metal shall be supplied in the following standard sizes and to the tolerances shown.

3.4.1 Round Wire: Shall conform to Table 2.

TABLE 2 - Tolerances, Round Wire

Nominal Diameters Inch	Nominal Diameters Millimeters	Tolerances, Plus and Minus Inch	Tolerances, Plus and Minus Millimeters
1/32	0.8	0.001	0.025
1/16	1.6	0.001	0.025
3/32	2.4	0.0015	0.038
1/8	3.2	0.0015	0.038
3/16	4.8	0.0015	0.038
1/4	6.4	0.0015	0.038

3.4.2 Flattened and Slit Wire: Cross-section 0.020 inch \pm 0.001 x 2 inches \pm 0.006 (0.51 mm \pm 0.03 x 51 mm \pm 0.15).

3.4.3 Sheet: Tolerances for nominal thicknesses 0.010, 0.015, and 0.020 inch (0.25, 0.38, and 0.51 mm) shall be as specified in ANSI H35.2 or ANSI H35.2M.

3.4.4 Foil: For coil widths up to 8 inches (203 mm):

3.4.4.1 For thickness 0.006 to 0.99 inch (0.15 to 2.51 mm) inclusive, thickness tolerance shall be \pm 0.0010 inch (0.025 mm).

3.4.4.2 For thickness 0.0059 and under, thickness tolerance shall be +15% of the nominal thickness.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of filler metal shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the filler metal conforms to the specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and, except for composition, shall be performed on each lot.

4.3 Sampling and Testing:

Shall be in accordance with the following; a lot shall be all filler metal produced from a single furnace charge:

4.3.1 Composition: At least one sample from each group of ingots poured simultaneously from the same source of molten metal.

4.3.1.1 Unless compliance with 4.3.1 is established, an analysis shall be made for each 6000 pounds (2722 kg) or less of filler metal comprising a lot.

4.4 Reports:

The vendor of filler metal shall furnish with each shipment a report stating that the filler metal conforms to the chemical composition and other technical requirements. This report shall include the purchase order number, lot number, AMS 4184E, form and size or part number, and quantity.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 Filler metal shall be identified as agreed upon by purchaser and vendor.

5.1.2 Each container or package shall be permanently and legibly marked with not less than the following information:

FILLER METAL, ALUMINUM BRAZING

AMS 4184E

LOT NUMBER _____

MANUFACTURER'S IDENTIFICATION _____

NOMINAL DIMENSIONS _____

WEIGHT _____

5.2 Packaging:

5.2.1 Filler metal shall be suitably wrapped, sealed, and boxed or otherwise packaged for protection against injury and contamination, during shipment and storage, under normal dry storage conditions.

5.2.2 Packages of filler metal shall be prepared for shipment in accordance with ASTM B 660, commercial practice, and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the filler metal to ensure carrier acceptance and safe delivery.