

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS 4189G

Issued JAN 1976
Revised MAR 2003
Cancelled AUG 2007

Superseded by AWS A5.10, ER4643

Aluminum Alloy Welding Wire
4.1Si -0.20 Mg (4643)

(Composition similar to UNS A94643)

RATIONALE

AMS 4189F has been designated Cancelled and Superseded because equivalent technical requirements are provided by AWS A5.10.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of August, 2007, and has been superseded by AWS A5.10, ER4643. The requirements of the latest issue of AWS A5.10, ER4643 shall be fulfilled whenever reference is made to the cancelled AMS 4189F. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications, noting that it has been superseded by AWS A5.10, ER4643.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of SAE AMS 4189G

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

SAENORM.COM : Click to view the full PDF of ams4189g

**AEROSPACE
MATERIAL
SPECIFICATION**



AMS 4189G

Issued JAN 1976
Revised MAR 2003
Cancelled AUG 2007

Superseded by AWS A5.10, ER4643

**Aluminum Alloy, Welding Wire
4.1 Si - 0.20Mg (4643)**

(Composition similar to UNS A94643)

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-metal-arc or gas-tungsten-arc welding of heavy sections of aluminum alloys of similar composition to produce joints having inherently low dilution ratio of base-metal to weld-metal, and where the weldment may require solution and/or precipitation heat treatment, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- | | |
|----------|---|
| AMS 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings |
| MAM 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Rings, Metric (SI) Units |
| AMS 2813 | Packaging and Marking of Packages of Welding Wire, Standard Method |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.1 (Continued):

| | |
|----------|--|
| AMS 2814 | Packaging and Marking of Packages of Welding Wire, Premium Quality Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded |
| AMS 2816 | Identification, Welding Wire, Tab Marking Method |
| AMS 2819 | Identification, Welding Wire, Direct Color Code System |
| ARP1876 | Weldability Test for Weld Filler Metal Wire |
| ARP4926 | Alloy Verification and Chemical Composition Inspection of Welding Wire |

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

| Element | min | max |
|-----------------------|-----------|----------------|
| Silicon | 3.6 | 4.6 |
| Iron | -- | 0.8 |
| Copper | -- | 0.10 |
| Manganese | -- | 0.05 |
| Magnesium | 0.10 | 0.30 |
| Zinc | -- | 0.10 |
| Titanium | -- | 0.15 |
| Beryllium | -- | 0.0008 (8 ppm) |
| Other Elements, each | -- | 0.05 |
| Other Elements, total | -- | 0.15 |
| Aluminum | remainder | |

3.1 .1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to chemical composition requirements, and the facility employs procedures to ensure traceability of wire to the originally analyzed source.

3.2 Condition:

As drawn, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3 Fabrication:

3.3.1 Butt welding is permissible provided both ends to be joined are identified by chemical analysis or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.3.2 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Weldability:

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Sizes and Diameter Tolerances, Inch/Pound Units

| Form | Nominal Diameter Inch | Tolerance | Tolerance |
|-------------|---|--------------|---------------|
| | | Inch Plus | Inch Minus |
| Cut Lengths | 0.047, 0.062, 0.079, 0.094, 0.098, 0.125, 0.156, 0.188, 0.197, 0.250 | 0.003 | 0.003 |
| Spools | 0.030, 0.035, 0.039, 0.047 | 0.001 | 0.002 |
| Spools | 0.062, 0.079, 0.094, 0.098, 0.125 | 0.002 | 0.002 |

TABLE 2B - Sizes and Diameter Tolerances, SI Units

| Form | Nominal Diameter Millimeter | Tolerance | Tolerance |
|-------------|---|--------------------|---------------------|
| | | Millimeter Plus | Millimeter Minus |
| Cut Lengths | 1.19, 1.57, 2.00, 2.39, 2.50, 3.18, 3.96, 4.78, 5.00, 6.35 | 0.08 | 0.08 |
| Spools | 0.76, 0.89, 1.00, 1.19 | 0.025 | 0.05 |
| Spools | 1.57, 2.00, 2.39, 2.50, 3.18 | 0.05 | 0.05 |

3.6.2 Length: Cut lengths shall be furnished in 36-inch (914-mm) lengths unless 27-inch (686-mm) or 18-inch (457-mm) lengths are ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.