

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

Issued MAY 1948
Revised JUL 1996

Superseding AMS 4190E

ALUMINUM ALLOY WELDING WIRE 5.2Si (4043)

UNS A94043

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-metal-arc or gas-tungsten-arc welding of aluminum alloys of similar composition, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

AMS 2813 Packaging and Marking of Packages of Welding Wire, Standard Method

AMS 2814 Packaging and Marking of Packages of Welding Wire, Premium Quality

AMS 2816 Identification, Welding Wire, Tab Marking Method

AMS 2819 Identification, Welding Wire, Direct Color Code System

ARP 1876 Weldability Test for Weld Filler Metal Wire

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Silicon	4.5	6.0
Iron	--	0.8
Copper	--	0.30
Titanium	--	0.20
Zinc	--	0.10
Manganese	--	0.05
Magnesium	--	0.05
Beryllium	--	0.0008
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements, and the facility employs procedures to ensure traceability of wire to the originally analyzed source.

3.2 Condition:

As drawn, in a temper and with a surface finish which will provide proper feeding of the wire in machine-welding equipment.

3.3 Fabrication:

3.3.1 Butt welding is permissible provided both ends to be joined are identified by chemical analysis or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.3.2 Drawing compounds, oxides, dirt, oil, and other foreign material shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Weldability:

Melted wire shall flow smoothly and evenly during welding and shall, produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Sizes and Diameter Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance	
		Inch Plus	Inch Minus
Cut Lengths	0.047, 0.062, 0.094	0.0015	0.0015
Cut Lengths	0.125, 0.156, 0.188, 0.250	0.003	0.003
Spools	0.030, 0.035, 0.047	0.001	0.002
Spools	0.062, 0.094, 0.125	0.002	0.002

TABLE 2B - Sizes and Diameter and Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance	
		Millimeter Plus	Millimeter Minus
Cut Lengths	1.19, 1.57, 2.39	0.038	0.038
Cut Lengths	3.18, 3.96, 4.78, 6.35	0.08	0.08
Spools	0.76, 0.89, 1.19	0.025	0.05
Spools	1.57, 2.39, 3.18	0.05	0.05

3.6.2 Lengths: Cut lengths shall be furnished in 36 inch (914 mm) lengths unless 27 inch (686 mm) or 18 inch (457 mm) lengths are ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Composition (3.1) and sizes and tolerances (3.6) are acceptance tests and shall be performed on each inspection lot.
- 4.2.2 Periodic Tests: Weldability (3.4) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

The vendor of wire shall furnish with each shipment a report stating that the wire conforms to the chemical composition and other technical requirements. This report shall include the purchase order number, inspection lot number, AMS 4190F, nominal size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

- 5.1 Wire shall be supplied either on spools in one continuous length for machine welding and in cut lengths for manual welding, as ordered.

5.1.1 Wire on each spool shall be of one continuous length from the same heat of alloy. Packages of (R) cut lengths shall not contain wire from more than one lot of alloy.

5.2 Wire furnished on spools shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching, shall be wound so as to avoid producing kinks, waves, and sharp bends, and shall be free to unwind without restriction caused by overlapping or wedging.

5.3 An 8 inch (203 mm) length of wire shall be made accessible at one end of each spool for alloy analysis, if required.

5.4 Identification:

Shall be by tab marking in accordance with AMS 2816 unless color coding in accordance with AMS 2819 or other method is specified by purchaser.

5.5 Packaging and Marking:

Shall be by standard method in accordance with AMS 2813 unless premium quality method in accordance with AMS 2814 or other method is specified by purchaser.