



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4191™</b>	<b>REV. K</b>
	Issued 1962-06 Noncurrent 2008-01 Reaffirmed 2015-10 Revised 2024-03  Superseding AMS4191J	
Aluminum Alloy, Welding Wire, 6.3Cu - 0.30Mn - 0.18Zr - 0.15Ti - 0.10V (2319) (Composition similar to UNS A92319)		

### RATIONALE

AMS4191K results from a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (see 3.7, 4.4.1, 5.3.1, 5.4.1, and 8.4), relocate Definitions (see 2.2), update Applicable Documents (see Section 2), Length (see 3.6.2), and Ordering Information (see 8.5), and allow the use of the immediate prior specification revision (see 8.3).

#### 1. SCOPE

##### 1.1 Form

This specification covers an aluminum alloy in the form of welding wire (see 8.5).

##### 1.2 Application

This wire has been used typically as filler metal for gas-metal-arc or gas-tungsten-arc welding of aluminum alloys of similar composition where the joint is capable of being heat treated to a strength level comparable to that of the parent metal, but usage is not limited to such applications.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2813 Packaging and Marking of Packages of Welding Wire, Standard Method

AMS2814 Packaging and Marking of Packages of Welding Wire, Premium Quality

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
SAE WEB ADDRESS: <http://www.sae.org>

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS4191K>

AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition, Inspection of Welding Wire
AS7766	Terms Used in Aerospace Metals Specifications

## 2.2 Definitions

Terms used in AMS are defined in AS7766.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Wire Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

**Table 1 - Composition**

Element	Min	Max
Silicon	--	0.20
Iron	--	0.30
Copper	5.8	6.8
Manganese	0.20	0.40
Magnesium	--	0.02
Zinc	--	0.10
Titanium	0.10	0.20
Beryllium	--	0.0008 (8 ppm)
Vanadium	0.05	0.15
Zirconium	0.10	0.25
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements, and the facility employs procedures to ensure traceability of wire to the originally analyzed source.

### 3.2 Condition

As drawn, in a temper and with a surface finish which will provide proper feeding of the wire in machine-welding equipment.

### 3.3 Fabrication

3.3.1 Butt welding is permissible provided both ends to be joined are identified by chemical analysis or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.3.2 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

### 3.4 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

### 3.5 Quality

Wire, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

### 3.6 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

#### 3.6.1 Diameter

Tolerances shall be as shown in Table 2.

**Table 2A - Sizes and diameter tolerances, inch/pound units**

Form	Nominal Diameter Inches	Tolerance	Tolerance
		Inches Plus	Inches Minus
Cut Lengths	0.047, 0.062, 0.079, 0.094, 0.098, 0.125, 0.156, 0.188, 0.197, 0.250	0.003	0.003
Spools	0.030, 0.035, 0.039, 0.047	0.001	0.002
Spools	0.062, 0.079, 0.094, 0.098, 0.125	0.002	0.002

**Table 2B - Sizes and diameter tolerances, SI units**

Form	Nominal Diameter Millimeters	Tolerance	Tolerance
		Millimeters Plus	Millimeters Minus
Cut Lengths	1.19, 1.57, 2.00, 2.39, 2.50, 3.18, 3.96, 4.78, 5.00, 6.35	0.08	0.08
Spools	0.76, 0.89, 1.00, 1.19	0.025	0.05
Spools	1.57, 2.00, 2.39, 2.50, 3.18	0.05	0.05

#### 3.6.2 Length

Cut lengths shall be furnished in 18-, 27-, or 36-inch (457-, 686-, or 914-mm) lengths, or other lengths when specified by the purchaser, and shall not vary more than +0, -0.5 inch (+0, -13 mm) from the length ordered (see 8.5).

### 3.7 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of wire shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

Composition (see 3.1), sizes and tolerances (see 3.6), and alloy verification (see 5.2) are acceptance tests and shall be performed on each inspection lot.

#### 4.2.2 Periodic Tests

Weldability (see 3.4) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

#### 4.3 Sampling and Testing

Shall be in accordance with AMS2355.

#### 4.4 Reports

The producer of wire shall furnish with each shipment a report stating that the wire conforms to the composition and other technical requirements. This report shall include the purchase order number, inspection lot number, AMS4191K, nominal size, and quantity.

4.4.1 When material produced to this specification is beyond the sizes allowed in the scope or tables, or other exceptions are taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS4191K(EXC) because of the following exceptions:" and the specific exceptions shall be listed (see 5.3.1 and 5.4.1)

#### 4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

### 5. PREPARATION FOR DELIVERY

#### 5.1 Wire

Wire shall be supplied either on spools in one continuous length for machine welding or cut in lengths for manual welding as ordered. Wire on each spool or in each package of cut lengths shall be from the same heat of alloy.

5.1.1 Wire furnished on spools shall be closely wound in layers but adjacent turns within a layer need not be necessarily touching, shall be wound so as to avoid producing kinks, waves, and sharp bends, and shall be free to unwind without restriction caused by overlapping or wedging.

#### 5.2 Alloy Verification

Wire on each spool or in each package of cut lengths shall be alloy verified by a method acceptable to the purchaser. The alloy verification procedures of ARP4926 are recommended.

5.2.1 An 8-inch (203-mm) length of wire shall be made accessible at one end of each spool for alloy analysis, if required.

#### 5.3 Identification

Shall be by tab marking in accordance with AMS2816 unless color coding in accordance with AMS2819 or other method is specified by the customer.

5.3.1 When technical exceptions are taken (see 4.4.1), the material shall be identified with AMS4191(EXC) if tab marking in accordance with AMS2816 is used, or AMS4191F(EXC) if color coding in accordance with AMS2819 is used.

#### 5.4 Packaging and Marking

Shall be by standard method in accordance with AMS2813 unless premium quality method in accordance with AMS2814 or other method is specified by the purchaser.

5.4.1 When technical exceptions are taken (see 4.4.1), the material packaging shall be identified with AMS4191K(EXC).