



AEROSPACE MATERIAL SPECIFICATION	AMS4193™	REV. E
	Issued 1970-11 Reaffirmed 2012-03 Revised 2023-08	
Superseding AMS4193D		
Aluminum Alloy, Sheet, and Plate 4.4Cu - 1.5Mg - 0.60Mn (2024-T861) Solution Heat Treated, Cold Worked, and Precipitation Heat Treated (Composition similar to UNS A92024)		

RATIONALE

AMS4193E results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (see 3.3.1.1, 3.6, 4.4.1, and 8.4), relocate Definitions (see 2.4), update Applicable Documents (see Section 2), and allow the use of the immediate prior specification revision (see 8.3).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of flat sheet and plate 0.020 to 0.500 inch (0.51 to 12.70 mm) and under in nominal thickness (see 8.5).

1.2 Application

These products are used primarily for structural parts requiring good strength. These products, when reheat treated by the user, may not have the tensile properties shown.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4193E>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355	Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings
AMS2772	Heat Treatment of Aluminum Alloy Raw Materials
ARP823	Minimizing Stress-Corrosion Cracking in Wrought, High-Strength Aluminum Alloy Products
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ANSI Accredited Publications

Copies of these documents are available online at <https://webstore.ansi.org/>.

ANSI H35.1/H35.1M	Alloy and Temper Designation System for Aluminum
ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

2.3 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B660	Packaging/Packing of Aluminum and Magnesium Products
ASTM B666/B666M	Identification Marking of Aluminum and Magnesium Products

2.4 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the following percentages by weight, determined in accordance with AMS2355:

Table 1 - Composition

Element	Min	Max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Solution heat treated, cold reduced approximately 6% in thickness, and precipitation heat treated to the T861 temper (refer to ANSI H35.1/H35.1M). Solution and precipitation heat treatment shall be in accordance with AMS2772. The recommended precipitation heat aging treatment is 365 to 385 °F (185 to 196 °C) for 8 hours.

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill product:

3.3.1 Tensile Properties

Shall be as specified in Table 2:

Table 2A - Minimum tensile properties, inch/pound units

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inch or 4D %
0.020 to 0.062, incl	70.0	62.0	3
Over 0.062 to 0.249, incl	71.0	66.0	4
Over 0.249 to 0.500, incl	70.0	64.0	4

Table 2B - Minimum tensile properties, SI units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.51 to 1.57, incl	483	427	3
Over 1.57 to 6.32, incl	490	455	4
Over 6.32 to 12.70, incl	483	441	4

3.3.1.1 Mechanical property requirements for product outside of the range covered by 1.1 shall be agreed upon between the purchaser and producer and reported per 4.4.1 (see 8.5).

3.4 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

Composition (see 3.1), tensile properties (see 3.3.1), and tolerances (see 3.5) are classified as acceptance tests and, except for composition, shall be performed on each lot.

4.3 Sampling

Shall be in accordance with AMS2355.

4.4 Reports

The producer of the product shall furnish with each shipment a report stating that the product conforms to the composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS4193E, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.1 When material produced to this specification is beyond the sizes allowed in the scope of tables, or other exceptions are taken to the technical requirements listed in Section 3 (see 5.1.1), the report shall contain a statement "This material is certified as AMS4193E(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with ASTM B666/B666M.

5.1.1 When technical exceptions are taken (see 4.4.1), the material shall be marked with AMS4193(EXC).

5.2 Protective Treatment

Product shall be protected from damage during storage and shipment by a method determined by the producer unless specified by the purchaser. Examples of typical methods include but are not limited to interleaving with paper or oiling of the surface.

5.3 Packaging

The product shall be prepared for shipment in accordance with ASTM B660 and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A producer shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Product not conforming to this specification, or to modifications authorized by the purchaser, will be subject to rejection.