

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4222D

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 12-1-42
Revised 6-15-59

ALUMINUM ALLOY CASTINGS, SAND
4Cu - 2Ni - 1.5Mg (142-T77)
Solution Treated and Overaged

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for air-cooled cylinder heads.

3. COMPOSITION:

Copper	3.5 - 4.5
Nickel	1.7 - 2.3
Magnesium	1.2 - 1.8
Titanium	0.07 - 0.18
Iron	0.8 max
Silicon	0.6 max
Manganese	0.10 max
Zinc	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

3.1 If boron is present in the amount of 0.001% or more, the titanium content may be as low as 0.02%.

4. CONDITION: Solution heat treated and overaged.

5. TECHNICAL REQUIREMENTS:

5.1 Castings: Castings shall be produced in lots from metal conforming to Section 3. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of small amounts of grain refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or until the composition of a sample taken after the last addition to the melt has been found to conform to Section 3.

5.1.1 A melt shall be the metal withdrawn from a batch furnace charge of 2000 lb or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 lb or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.

5.1.2 A lot shall consist of castings poured from a single melt in not more than 8 consecutive hours.

5.2 Cast Test Specimens: Tensile test specimens, and chemical analysis specimens when required, shall be cast as follows and, when requested, shall be supplied with the castings.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no requirement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against infringement of patents."

- 5.2.1 Tensile Test Specimens: Shall be cast with each lot of castings, shall be standard (0.5 in. diameter at the reduced parallel section), and shall be cast to size in molds made with the regular foundry mix of green sand, without using chills. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated, and during such treatment shall be heated to the same maximum temperature and held for approximately the same length of time as the molten metal for castings. The temperature of the metal during pouring of the specimens shall be not lower than that during pouring of the castings.
- 5.2.2 Chemical Analysis Specimens: When required by purchaser, shall be cast from each melt and shall be of size and shape agreed upon by purchaser and vendor.
- 5.3 Heat Treatment: All castings and tensile test specimens shall be heat treated as follows:
- 5.3.1 Tensile test specimens from each lot, together with production castings, shall be heated to 960 - 970 F for the proper time for solution treatment and cooled in air. At least one set of tensile test specimens shall be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than 3 hours.
- 5.3.2 Tensile test specimens from each lot, together with production castings shall, after solution treatment as in 5.3.1, be heated uniformly to 625 - 675 F, held at heat for not less than 2 hr and cooled in air. At least one set of tensile test specimen shall be put into a batch-type furnace with each load of casting or into a continuous furnace at intervals of not longer than 3 hours.
- 5.4 Tensile Properties:
- 5.4.1 Tensile Test Specimens:
- | | |
|------------------------|------------|
| Tensile Strength, psi | 21,500 min |
| Elongation, % in 2 in. | 1 min |
- 5.4.2 Specimens Cut from Castings:
- 5.4.2.1 When tensile properties of actual castings are determined for acceptance, not less than 4, and preferably 10, tensile test specimens shall be cut from thick and thin sections. The average value of all specimens selected shall conform to the following:
- | | |
|-----------------------|------------|
| Tensile Strength, psi | 16,000 min |
|-----------------------|------------|
- 5.4.2.1.1 Conformance to these requirements may be used as basis for acceptance of castings.
- 5.4.2.2 When specified on the order, tensile test specimens taken in locations indicated on the drawing, from a casting chosen at random to represent the lot, shall have the properties indicated on the drawing for each specimen.
- 5.5 Hardness of Castings: Except at sprues and risers, the castings shall have hardness of Brinell 65 - 85 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 70 - 90 using 1000 kg load and 10 mm ball.