

Submitted for recognition as an American National Standard

ALUMINUM ALLOY WELDING WIRE
4.5Cu - 0.70Ag - 0.30Mn - 0.25Mg - 0.25Ti
For Welding 201 Type Alloys

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of welding wire.

1.2 Application: Primarily for use as filler metal for gas-metal-arc and gas-tungsten-arc welding of aluminum alloy castings having similar composition (201.0, A201.0, and B201.0) and requiring in the weld zone response to heat treatment, properties, and corrosion resistance comparable to those of the castings.

1.3 Classification: Wire supplied to this specification is classified as follows:

- Type 1 - As Extruded and Sized
- Type 2 - As Drawn

1.3.1 Unless a specific type is ordered, either type may be supplied.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 Aerospace Material Specifications:

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

AMS 2813 - Packaging of Welding Wire, Standard Method

AMS 2815 - Identification, Welding Wire, Line Code System

AMS 2816 - Identification, Welding Wire, Color Code System

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Copper	4.0	5.0
Silver	0.40	1.0
Manganese	0.20	0.40
Magnesium	0.15	0.35
Titanium	0.15	0.35
Iron	--	0.10
Silicon	--	0.05
Beryllium	--	0.0008
Other Impurities, each	--	0.03
Other Impurities, total	--	0.10
Aluminum		remainder

3.2 Condition: Wire may be made by any method unless a specific method is specified but shall be in a temper which will provide proper feeding of the wire in machine welding equipment.

3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.2.2 Oxides, dirt, and drawing compounds shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.3 Properties: Wire shall conform to the following requirements:

3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances: Wire shall be supplied in the sizes and to the tolerances of Table I unless drawn wire is specified, in which case wire shall conform to the tolerances of Table II.

3.5.1 Diameter:

3.5.1.1 Extruded Wire:

TABLE I

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.045, 0.062, 0.078, 0.094, 0.125	0.007	0.007
Spools	0.030, 0.035, 0.045, 0.062, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	1.15, 1.55, 1.95, 2.35, 3.10	0.18	0.18
Spools	0.75, 0.90, 1.15, 1.55, 2.35	0.05	0.05

3.5.1.2 Drawn Wire:

TABLE II

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.045, 0.062, 0.078, 0.094, 0.125	0.003	0.003
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.094	0.002	0.002

TABLE II (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	1.15, 1.55, 1.95, 2.35, 3.10	0.08	0.08
Spools	0.75, 0.90, 1.15	0.02	0.05
Spools	1.55, 2.35	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 36-in. (900-mm) lengths and shall not vary more than +0, -1 in. (-25 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1) and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each lot and stating that the wire conforms to the other acceptance test requirements of this specification. This report shall include the purchase order number, AMS 4233, lot number, nominal size, and quantity from each lot.

4.4.2 When castings or parts requiring use of this welding wire are supplied, the casting supplier or part or assembly manufacturer shall inspect each lot of wire to determine conformance to the requirements of this specification and shall furnish with each shipment a report stating that the wire conforms. This report shall include the purchase order number, AMS 4233, casting or part number, and quantity.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Layer Winding: Wire furnished on spools shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching; shall be wound so as to avoid producing kinks, waves, and sharp bends; and shall be free to unwind without restriction caused by overlapping or wedging. The outside end of the spooled wire shall be so treated that it may be readily located. An 8-in. (200-mm) length of wire shall be made accessible at both ends of each spool for alloy verification.

5.1.1 Wire on each spool shall be of one continuous length from the same lot of alloy. Butt welding is permissible provided both ends to be joined are verified and the weld will not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment. Packages of cut lengths shall not contain wire from more than one lot of alloy.