



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4236

Issued 7-15-80

Revised

ALUMINUM ALLOY CASTINGS, PREMIUM GRADE
4.6Cu - 0.35Mn - 0.25Mg - 0.22Ti (A206.0-T4)
Solution Heat Treated and Naturally Aged

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of sand, permanent mold, and composite mold castings.
- 1.2 Application: Primarily for components requiring high strength combined with good ductility and impact strength. Certain design and processing procedures (See 8.4) may cause these castings to become susceptible to stress-corrosion cracking.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2646 - Contrast Dye Penetrant Inspection
AMS 2694 - Repair Welding of Aerospace Castings
AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM E10 - Brinell Hardness of Metallic Materials
ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys
ASTM E155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings Series III
ASTM G44 - Alternate Immersion Stress Corrosion Testing in 3.5% Sodium Chloride Solution

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Copper	4.2	5.0
Manganese	0.20	0.50
Magnesium	0.15	0.35
Titanium	0.15	0.30
Iron	--	0.10
Zinc	--	0.10
Silicon	--	0.05
Nickel	--	0.05
Tin	--	0.05
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: Solution heat treated and naturally aged.
- 3.3 Casting: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt has been found to conform to 3.1. The type of mold for castings is not restricted.
- 3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 lb (900 kg) or less as melted for pouring castings or when permitted by purchaser, a melt shall be 4000 lb (1800 kg) or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.
- 3.3.2 A lot shall be all castings poured from a single melt in not more than 8 consecutive hours and solution treated in the same heat treatment batch.
- 3.4 Cast Test Specimens: Chemical analysis specimens, and tensile test specimens when required, shall be cast as follows:
- 3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of a size and shape agreed upon by purchaser and vendor.
- 3.4.2 Tensile Test Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B557 with 0.500 in. (12.50 mm) diameter at the reduced parallel gage section, and shall be cast to size in molds representative of the practice used for castings. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated and, during such treatment, shall be heated to the same maximum temperature and held for approximately the same time as the molten metal for the castings. The temperature of the metal during pouring of the specimens shall be not lower than that during the pouring of the castings.
- 3.5 Heat Treatment: All castings and representative tensile test specimens shall be solution heat treated and naturally aged in such a manner as to ensure conformance to the requirements of 3.6 (See 8.2). At least one set of tensile test specimens shall, during solution heat treatment, be put into a batch-type furnace with each load of casting or into a continuous furnace at intervals of not longer than 3 hours.
- 3.6 Properties: Castings and representative tensile test specimens produced in accordance with 3.4.2 shall conform to the following requirements (See 8.3):

3.6.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557; conformance to the requirements of 3.6.1.1 shall be used as basis for acceptance of castings except when purchaser specifies that the requirements of 3.6.1.2 apply:

3.6.1.1 Specimens Cut From Castings: When tensile properties of actual castings are determined for acceptance, the average of not less than 4, and preferably 10, specimens cut from thick and thin sections of the casting shall be as follows:

3.6.1.1.1 Designated Casting Areas:

Tensile Strength, min	50,000 psi (345 MPa)
Yield Strength at 0.2% Offset, min	30,000 psi (207 MPa)
Elongation in 4D, min	10%

3.6.1.1.2 Casting Areas Other than Designated Areas:

Tensile Strength, min	45,000 psi (310 MPa)
Yield Strength at 0.2% Offset, min	26,000 psi (180 MPa)
Elongation in 4D, min	8%

3.6.1.1.3 When properties other than those of 3.6.1.1.1 or 3.6.1.1.2 are required, tensile specimens as in 4.3.3 taken in locations indicated on the drawing, from a casting chosen at random to represent the lot, shall have the properties indicated on the drawing for such specimens. Property requirements for such specimens may be designated in accordance with AMS 2360.

3.6.1.2 Separately-Cast Test Specimens:

Tensile Strength, min	50,000 psi (345 MPa)
Yield Strength at 0.2% Offset, min	30,000 psi (207 MPa)
Elongation in 4D, min	10%

3.6.2 Hardness of Castings: Castings, except at sprue and riser locations, should have hardness of 85 - 115 HB/10/500, 85 - 115 HB/14.3/1000, or 90 - 120 HB/10/1000, determined in accordance with ASTM E10, but castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.6.1.1 are met.

3.6.3 Stress-Corrosion Resistance: Specimens as in 4.3.5, cut from castings processed to meet the requirements of 3.6.1 and 3.6.2 and tested in accordance with ASTM G44 at a stress of 75% of the specified minimum yield strength, shall meet the requirements of ASTM G44.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned.

3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645 and/or to contrast dye penetrant inspection in accordance with AMS 2646.

3.7.4 Radiographic, fluorescent penetrant, contrast dye penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E155 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

3.7.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser, designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties of specimens cut from castings (3.6.1.1) or, when specified, tensile properties of separately-cast specimens (3.6.1.2), and quality (3.7) are classified as acceptance tests and shall be performed to represent each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for hardness (3.6.2) and stress-corrosion resistance (3.6.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a casting to a purchaser, when a change in material or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 from each melt or a casting from each lot.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.3 Not less than four tensile test specimens machined from castings from each lot except when purchaser specifies use of separately-cast specimens. Specimens shall conform to ASTM B557 and shall be either 0.500 in. (12.50 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. If specimen locations are not shown on the drawing, not less than four specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.

4.3.4 Three tensile test specimens in accordance with 3.4.2 from each lot, when purchaser specifies use of separately-cast specimens.

4.3.5 Specimens for stress-corrosion tests shall be tensile test specimens taken from the same areas of castings as for tensile tests of specimens cut from castings. Whenever practicable, specimens shall be not less than 0.250 in. (6.25 mm) in diameter at the reduced parallel gage section.

4.4 Approval: