

SAE-AMS4281

ADOPTION NOTICE

SAE-AMS4281, "Castings, Permanent Mold, 5.0SI 1.2CU 0.50MG, Solution and Precipitated Heat Treated," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commanding Officer, Naval Air Warfare Center Aircraft Division, Systems Requirements Department, Highway 540, Lakehurst, NJ 08733-5100. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:  
 Army - MR  
 Navy - AS  
 Air Force - 11

Adopting Activity  
 Navy - AS

SAENORM.COM : Click to view the full PDF of SAE-AMS4281

AREA MECA

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

AMS 4281E

Issued 7-1-45  
Revised 10-1-89

Superseding AMS 4281D

Submitted for recognition as an American National Standard

ALUMINUM ALLOY CASTINGS, PERMANENT MOLD  
5.0Si - 1.2Cu - 0.50Mg (355.0-T6)  
Solution and Precipitation Heat Treated

UNS A03550

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of permanent mold castings.
- 1.2 Application: Primarily for parts requiring moderate strength up to 300°F (149°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods  
AMS 2360 - Room Temperature Tensile Properties of Castings  
AMS 2635 - Radiographic Inspection  
AMS 2645 - Fluorescent Penetrant Inspection  
AMS 2646 - Contrast Dye Penetrant Inspection  
AMS 2694 - Repair Welding of Aerospace Castings  
AMS 2804 - Identification, Castings

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM B 557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

ASTM B 557M - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)

ASTM B 660 - Packaging/Packing of Aluminum and Magnesium Products

ASTM E 10 - Brinell Hardness of Metallic Materials

ASTM E 34 - Chemical Analysis of Aluminum and Aluminum Alloys

ASTM E 155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

### 3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 54, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Silicon	4.5	5.5
Copper	1.0	1.5
Magnesium	0.40	0.6
Iron (3.1.1)	--	0.6
Manganese (3.1.1)	--	0.50
Zinc	--	0.35
Titanium	--	0.25
Chromium	--	0.25
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.1.1 If iron content exceeds 0.45%, manganese content shall be not less than one half the iron content.

3.2 Condition: Solution and precipitation heat treated.

3.3 Castings: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

- 3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 pounds (907 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 pounds (1814 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.
- 3.3.2 A lot shall be all castings poured from a single melt in not more than eight consecutive hours and solution and precipitation heat treated in a heat treat batch.
- 3.4 Cast Test Specimens: Chemical analysis specimens and tensile specimens shall be cast as follows:
- 3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of any suitable size and shape.
- 3.4.2 Tensile Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B 557 or ASTM B 557M with 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, and shall be cast to size in permanent molds. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated and, during such treatment, shall be heated to the same maximum temperature and held for approximately the same time as the molten metal for the castings. The temperature of the metal during pouring of the specimens shall be not lower than that during pouring of the castings.
- 3.5 Heat Treatment: All castings and representative tensile specimens shall be solution and precipitation heat treated in accordance with MIL-H-6088; at least one set of specimens shall, during each stage of heat treatment, be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than three hours.
- 3.6 Properties: Castings and separately-cast tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements:
- 3.6.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B 557 or ASTM B 557M; conformance to the requirements of 3.6.1.1 shall be used as the basis for acceptance of castings except when purchaser specifies that 3.6.1.2 applies:
- 3.6.1.1 Separately-Cast Specimens:
- |  |                      |
|--|----------------------|
| Tensile Strength, minimum              | 37,000 psi (255 MPa) |
| Yield Strength at 0.2% Offset, minimum | 23,000 psi (159 MPa) |
| Elongation in 4D, minimum              | 1.5%                 |
- 3.6.1.2 Specimens Cut from Castings: Shall be as follows, determined on specimens as in 4.3.4:
- |  |                      |
|--|----------------------|
| Tensile Strength, minimum              | 27,000 psi (191 MPa) |
| Yield Strength at 0.2% Offset, minimum | 17,000 psi (117 MPa) |
| Elongation in 4D, minimum              | 0.4%                 |

3.6.1.2.1 When properties other than those of 3.6.1.2 are required, tensile specimens taken from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot, shall have the properties indicated on the drawing for such specimens. Property requirements may be designated in accordance with AMS 2360.

3.6.2 Hardness: Castings, except at sprue and riser locations, should have hardness of 80 - 110 HB/10/500 or 85 - 115 HB/10/1000, determined in accordance with ASTM E 10, but the castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.6.1.2 are met.

### 3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned.

3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645, to contrast dye penetrant inspection in accordance with AMS 2646, or to both.

3.7.4 Radiographic, fluorescent penetrant, contrast dye penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E 155 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be reworked by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings reworked by welding in accordance with AMS 2694.

3.7.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage, unless specified or allowed by written permission of purchaser, designating the method to be used.

## 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests for all technical requirements are acceptance tests and shall be performed on each melt or lot as applicable.

4.2.1.1 Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Shall be in accordance with the following; the number of specimens to be sampled shall be the minimum number of specimens tested:

4.3.1 At least one chemical analysis specimen in accordance with 3.4.1 from each melt, a casting from each lot, or both.

4.3.2 Three separately-cast tensile specimens in accordance with 3.4.2 representing each lot except when properties of specimens machined from castings are required.

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.4 One or more castings from each lot when properties of specimens machined from castings are required. Specimens shall conform to ASTM B 557 or ASTM B 557M and shall be either 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. For determining conformance to the requirements of 3.6.1.2, if specimen locations are not shown on the drawing, not less than four tensile specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.

#### 4.4 Approval:

4.4.1 Sample castings from new or reworked molds and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.