



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4333™</b>	<b>REV. E</b>
	Issued 1988-10 Revised 2022-06	
Superseding AMS4333D		
<p style="text-align: center;">Aluminum Alloy, Die Forgings 6.2Zn - 2.3Cu - 2.2Mg - 0.12Zr (7050-T7452) Solution Heat Treated, Compression Stress-Relieved, and Overaged (Composition similar to UNS A97050)</p>		

RATIONALE

AMS4333E is the result of a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (3.3.1.1.3, 3.6, 4.4.2, 8.6); update applicable documents (Section 2, 3.2.1, 8.3), stress-corrosion susceptibility factor (SCF) (3.3.1.2.2), and ordering information (8.7); and to allow the use of the immediate prior specification revision (8.5).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of die forgings 4.000 inches (102 mm) and under in nominal thickness and of forging stock of any size (see 8.7).

1.2 Application

These forgings have been used typically for machined structural parts subject to warpage during machining and requiring high strength and resistance to stress-corrosion cracking, but usage is not limited to such application.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

- AMS2355      Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings
- AMS2772      Heat Treatment of Aluminum Alloy Raw Materials
- AMS2808      Identification, Forgings
- AS7766        Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:**    Tel:    877-606-7323 (inside USA and Canada)  
   Tel:    +1 724-776-4970 (outside USA)  
   Fax:    724-776-0790  
   Email: CustomerService@sae.org  
**SAE WEB ADDRESS:**                    http://www.sae.org

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS4333E/>

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products
ASTM B645	Linear-Elastic Plane Strain Fracture Toughness Testing of Aluminum Alloys
ASTM B660	Packaging/Packing of Aluminum and Magnesium Products
ASTM E399	Linear Elastic Plane-Strain Fracture Toughness of Metallic Materials
ASTM E1417/E1714M	Liquid Penetrant Testing

## 2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1/H35.1M	Standard Alloy and Temper Designation System for Aluminum
ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

**Table 1 - Composition**

Element	Min	Max
Silicon	--	0.12
Iron	--	0.15
Copper	2.0	2.6
Manganese	--	0.10
Magnesium	1.9	2.6
Chromium	--	0.04
Zinc	5.7	6.7
Titanium	--	0.06
Zirconium	0.08	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

### 3.2 Condition

#### 3.2.1 Die Forgings

Solution heat treated in accordance with AMS2772, stress-relieved by compressing to produce a 1 to 5% permanent set, and overaged to the T7452 temper (refer to ANSI H35.1/H35.1M) (see 8.2).

#### 3.2.2 Forging Stock

As ordered by the forging manufacturer.

### 3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size.

#### 3.3.1 Die Forgings

##### 3.3.1.1 Tensile Properties (see 8.4)

###### 3.3.1.1.1 With Grain Flow

Specimens, machined from forgings or from prolongations on such forgings, with axis of specimen in area of gage length varying not more than 15 degrees from parallel to the forging flow lines, shall have the properties shown in Table 2.

**Table 2A - Minimum tensile properties, inch/pound units**

Nominal Thickness at Time of Heat Treatment Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %
Up to 2.000, incl	72.0	60.0	9
Over 2.000 to 4.000, incl	71.0	59.0	8

**Table 2B - Minimum tensile properties, SI units**

Nominal Thickness at Time of Heat Treatment Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D or 50.8 mm %
Up to 51, incl	496	414	9
Over 51 to 102, incl	490	407	8

###### 3.3.1.1.2 Across Grain Flow

Specimens, machined from forgings or from prolongations on such forgings, with axis of specimen in area of gage length varying not more than 15 degrees from perpendicular to the forging flow lines, shall have properties shown in Table 3.

**Table 3A - Minimum tensile properties, inch/pound units**

Nominal Thickness at Time of Heat Treatment Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %
Up to 2.000, incl	68.0	55.0	5
Over 2.000 to 4.000, incl	67.0	53.0	4

**Table 3B - Minimum tensile properties, SI units**

Nominal Thickness at Time of Heat Treatment Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D or 50.8 mm %
Up to 51, incl	469	379	5
Over 51 to 102, incl	462	365	4

3.3.1.1.3 Mechanical property requirements for product outside of the range covered by 1.1 shall be agreed upon between purchaser and producer and reported in 4.4.2 (see 8.7).

## 3.3.1.1.4 Special Purpose Forgings

Tensile specimens cut from special purpose forgings shall meet the tensile property requirements specified on the drawing or as agreed upon by purchaser and producer.

## 3.3.1.2 Corrosion Resistance

Resistance to stress-corrosion cracking and to exfoliation-corrosion of the forging heat lot is acceptable if the conditions of 3.3.1.2.1 and 3.3.1.2.2 are met.

## 3.3.1.2.1 Electrical Conductivity

Shall be not lower than 38.0% IACS (International Annealed Copper Standard) (22.0 MS/m).

## 3.3.1.2.2 Stress-Corrosion Susceptibility Factor (SCF)

Shall be not greater than 32.0 (220), determined by subtracting the electrical conductivity, AA.A percent IACS (12 times BB.B MS/m) from the with the grain flow yield strength, XX.X ksi (YYY MPa).

Examples:

Inch/Pound Units	72.0 ksi - 38.5% IACS = 33.5	Unacceptable
	68.0 ksi - 40.2% IACS = 27.8	Acceptable
SI Units	496 MPa - 12 x 22.3 MS/m = 228.4	Unacceptable
	469 MPa - 12 x 23.3 MS/m = 189.4	Acceptable

3.3.1.2.3 Forgings not conforming to 3.3.1.2.1 and 3.3.1.2.2 may be given additional overaging and retested to determine conformance to 3.3.1.1, 3.3.1.2.1, and 3.3.1.2.2.

## 3.3.1.3 Stress-Corrosion Resistance

Specimens, not less than 0.750 inch (19.05 mm) in thickness cut from forgings, shall show no evidence of stress-corrosion cracking when stressed in the short-transverse direction at 35.0 ksi (241 MPa).

## 3.3.1.4 Fracture Toughness

When specified, plane strain fracture toughness shall be tested in accordance with ASTM E399 and ASTM B645 for forgings 1.000 to 4.000 inches (25.40 to 101.60 mm), inclusive, in nominal thickness. A valid  $K_{Ic}$  meeting the requirements of ASTM E399 or a  $K_Q$  "useable for lot release" in accordance with ASTM B645 shall meet or exceed the values specified in Table 4.

**Table 4 - Minimum  $K_{Ic}$  or  $K_Q$  "useable for lot release" fracture toughness**

Nominal Thickness Inches	Nominal Thickness Millimeters	Specimen Orientation	Minimum $K_{Ic}$ or $K_Q$ ksi $\sqrt{\text{inches}}$	Minimum $K_{Ic}$ or $K_Q$ MPa $\sqrt{\text{m}}$
1.000 to 3.500, incl	25.40 to 88.90, incl	L-T	27	30
		T-L	19	21
		S-L	19	21
Over 3.500 to 4.000, incl	88.90 to 101.60, incl	L-T	25	27
		T-L	19	21
		S-L	19	21

### 3.3.2 Forging Stock

When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1. If specimens taken from the stock prior to forging and after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to use unforged coupons when performing lot conformance testing.

### 3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from conditions detrimental to usage of the product.

3.4.1 When specified, each die forging shall be subjected to ultrasonic inspection in accordance with ASTM B594 and shall meet Class B acceptance criteria.

3.4.2 When specified, each die forging shall be subjected to fluorescent penetrant testing in accordance with ASTM E1417/E1417M. Forgings shall be free from surface defects such as seams, laps, bursts, and quench cracks.

3.4.3 Grain flow of die forgings, except in areas which contain end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

### 3.5 Tolerances

Forging stock shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

### 3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.2.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of forgings shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

The following requirements are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.1.1 Composition (3.1) of the product.

4.2.1.2 Tensile properties (3.3.1.1), corrosion resistance (3.3.1.2), and, when specified, fracture toughness (3.3.1.4), ultrasonic soundness (3.4.1), and fluorescent penetrant inspection (3.4.2).

4.2.1.3 Tolerances (3.5) of forging stock.

#### 4.2.2 Periodic Tests

The following requirements are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.2.2.1 Stress-corrosion resistance (3.3.1.3) of forgings.

4.2.2.2 Ability of forging stock to develop required properties (3.3.2).