

HONEYCOMB CORE, ALUMINUM ALLOY, CORROSION INHIBITED
For Sandwich Construction
5052, 350 (175)

1. SCOPE:

1.1 Form: This specification covers one type of honeycomb core made of aluminum alloy and supplied in the form of blocks, slices, or other configurations as ordered. The core is treated to increase corrosion resistance.

1.2 Application: Primarily for use in sandwich construction for short-term exposure up to 350°F (175°C) or for long term exposure up to 200°F (95°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 4004 - Aluminum Alloy Foil, 2.5Mg - 0.25Cr (5052-H191)

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B117 - Salt Spray (Fog) Testing

ASTM C273 - Shear Test in Flatwise Plane of Flat Sandwich Constructions
or Sandwich Cores

ASTM C365 - Flatwise Compressive Strength of Sandwich Cores

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 4348A

2.3.1 Federal Standards:

FED-STD-595 - Color

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material:

3.1.1 Metal: Shall be AMS 4004 (5052-H191) aluminum alloy foil of the thickness $\bar{\theta}$ specified on the part drawing or purchase order except that maximum foil thickness shall be as specified in Table I.

3.1.2 Adhesive: The adhesive system used for node-to-node attachment shall be such that the resultant core meets the requirements specified herein.

3.2 Configuration: The core material shall consist of strips of aluminum alloy foil treated for corrosion protection, bonded together such that cells approximately hexagonal in shape are formed when fully expanded (See Fig. 1).

3.2.1 Designation: Core shall be designated according to the following numbering system:

- a. Nominal density, lb per cu ft (kg/m^3)
- b. Cell size, in. (mm)
- c. Foil thickness, ten-thousandths in. (μm)
- d. "N" for nonperforated or "P" for perforated
- e. Alloy
- f. Adhesive, option of supplier, unless otherwise specified

Example: Core with a nominal density of 4.3 lb per cu ft (69 kg/m^3) with a 1/4 in. (6.2 mm) cell size, 0.0020 in. ($50 \mu\text{m}$) foil thickness, nonperforated, made of AMS 4004 alloy, and bonded with required adhesive shall be numbered as follows:

4.3 - 1/4 20N (5052) (XXXX) in inch/pound units
69 - 6.2 50N (5052) (XXXX) in SI units

- 3.2.2 Perforations: When perforated core is specified, the perforations shall be approximately 0.005 in. (0.12 mm) in diameter and spaced to vent each cell into at least three adjacent cells at least once per 1/4 in. (6.2 mm) of core thickness. When thicknesses less than 1/4 in. (6.2 mm) are furnished, there shall be at least one perforation per cell into each of three adjacent cells.
- 3.2.3 Cell Pitch: Shall be 1.733 times the nominal cell size, +20%, - 10%, measured by taking the average distance between 10 nodes along a ribbon for 6 different ribbons.
- 3.3 Condition: Core shall be clean and free of contamination, and treated for corrosion resistance; it shall be supplied in the expanded form, unless otherwise specified.
- 3.4 Properties: Core having nominal dimensions as specified in Table I shall conform to the following requirements; tests shall be conducted on the core supplied and in accordance with specified test methods. Properties of core having nominal dimensions other than specified in Table I shall be as agreed upon by purchaser and vendor.
- 3.4.1 Flatwise Compressive Strength: The minimum individual values shall be as specified in Table I, determined in accordance with 4.5.1.
- 3.4.2 Plate Shear Strength and Plate Shear Modulus: Shall be as specified in Table I, determined in accordance with ASTM C273 at $77^{\circ}\text{F} \pm 5$ ($25^{\circ}\text{C} \pm 3$), using a 0.625-in. (16-mm) thick specimen.
- 3.4.3 Node Bond Strength: Shall be not less than 30 lb (135 N) at $77^{\circ}\text{F} \pm 5$ ($25^{\circ}\text{C} \pm 3$) and not less than 15 lb (65 N) at $350^{\circ}\text{F} \pm 5$ ($175^{\circ}\text{C} \pm 3$), determined in accordance with 4.5.2. In case of partial delamination at the minimum specified load, the delamination shall be less than 10% of the total stress section of the core slice.
- 3.4.4 Core Density: Shall be within $\pm 10\%$ of the nominal specified density, determined in accordance with 4.5.3.
- 3.4.5 Corrosion Resistance: Core specimens shall show a weight loss not greater than 125 mg per sq ft (1345 mg/m^2) of exposed foil area, determined in accordance with 4.5.4.
- 3.5 Quality: The core, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the core.
- 3.5.1 Cleanliness: The core shall be free from corrosion, oil, and other contamination detrimental to bonding.

AMS 4348A

- 3.5.2 Discoloration: A change in color of core material shall be acceptable provided the color change occurs in a line parallel to "L" (Fig. 1), indicative of a change in foil material where more than one foil coil is used in the manufacture of a core block.
- 3.5.3 Flatness: Expanded core shall make total facing contact with a flat surface under uniform pressure without resulting in any damage that would cause core rejection.
- 3.5.4 Double Foils: Expanded core splices which have double foils (two ribbons bonded together which cause uneven expansion in the "L" direction (Fig. 1) shall be acceptable if the double foils are not more frequent than 1 in any 8 in. (200 mm).
- 3.5.5 Mismatched Nodes: The c/d ratio (See Fig. 2) of mismatched nodes shall be 0.00 to 0.25.
- 3.5.6 Visual Imperfections: The following maximum requirements apply for imperfections observed in any randomly selected 12-in. (300-mm) diameter circle.

Type of Imperfection	Maximum Number for Cell Size, Inch (mm), Shown				
	1/8 (3.2)	5/32 (4.0)	3/16 (4.8)	1/4 (6.4)	3/8 (9.5)
Mismatched Nodes	70	55	40	25	10
Loose Metal or Flakes (See 3.5.6.1)	35	28	20	12	5
Split Cell Walls	0	0	0	0	0
Buckled Cell Walls	0	0	0	0	0
Unbonded Nodes	2	2	2	2	2

3.5.6.1 Flakes are excess metal attached to foil edges which do not interfere with measurements of core thickness.

3.6 Sizes and Tolerances:

3.6.1 Size: Core shall be supplied in the size ordered with core dimensions as shown in Fig. 1, where,

T = Thickness, depth, or height dimension measured parallel to the core cell size

L = Longitudinal or ribbon (length) dimension measured along the direction of a ribbon

W = Width dimension measured normal to the ribbon direction

3.6.2 Core Thickness: Shall be ± 0.005 in. (± 0.12 mm) for machined slices up to 4.0 in. (100 mm) in nominal thickness, ± 0.062 in. (± 1.55 mm) for machined slices over 4 in. (100 mm) in nominal thickness, and $+0.25$ in. ($+6.2$ mm), -0.00 for raw block.

- 3.6.3 "L" and "W": Length and width of unexpanded core shall be as ordered, +0.25 in. (+6.2 mm), -0; for expanded core, tolerances shall be +2 in. (+50 mm), -0.
- 3.6.4 Average Cell Size: The cell size of any 10 adjacent cells shall vary not more than +10% from nominal, determined by taking the average distance between node bonds along the "W" dimension (Fig. 1) for at least 60 cells selected at random in groups containing 10 adjacent cells.
- 3.6.5 Ribbon Direction: All ribbons shall be parallel to each other within 10 degrees. The ribbon direction shall be determined by measuring the angle between one line through two nodes on the same ribbon ("L" direction), 12 in. (300 mm) apart, and another line in the principal ribbon direction (See Fig. 1).

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of core shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the core conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for \emptyset flatwise compressive strength (3.4.1), node bond strength (3.4.3), and density (3.4.4) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a core to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be in accordance with the following:
- 4.3.1 Acceptance Tests: Each block or 2% of the slices, selected at random, from each lot; a lot shall be all slices cut from a single block:
- 4.3.2 Preproduction Tests: As agreed upon by purchaser and vendor.

AMS 4348A

4.4 Approval:

- 4.4.1 Sample core shall be approved by purchaser before core for production use is supplied, unless such approval be waived by purchaser. Results of tests on production core shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production core which are essentially the same as those used on the approved sample core. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample core. Production core made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

- 4.5.1 Flatwise Compressive Strength: Shall be determined at $77^{\circ}\text{F} \pm 5$ ($25^{\circ}\text{C} \pm 3$) in accordance with ASTM C365, Method A for stabilized specimens and Method B for bare specimens. Test specimens shall be nominally 0.625 in. (16 mm) thick by 3.00 in. ± 0.25 (75 mm ± 6.2) square. The test machine loading faces shall be approximately 4 in. (100 mm) square. Spherical loading blocks, preferably the suspended self-aligning type, shall transfer the load at 0.0020 in. ± 0.0005 (0.050 mm ± 0.012) per minute. At least 6 specimens shall be tested for each product. The flatwise compressive strength shall be computed by dividing the maximum load by the cross-sectional area of the specimen. Report all values.
- 4.5.2 Node Bond Strength: A core slice, nominally 0.625 x 5 x 10 in. (16 x 125 x 250 mm), shall be tested in a suitable tension fixture by mounting, without causing cell distortion, at opposite ends of the "W" dimension (See Fig. 3) with round pins. Pins shall be as large as cell size permits and shall engage all cells of a continuous row. Opposite pins shall be in a mirror image alignment at a distance as near to 8 in. (200 mm) as this mounting method permits. The fixture shall be slotted to allow horizontal pin movement. A steady loading rate of 1.00 in. ± 0.05 (25 mm ± 1.2) per min. shall be maintained. Specimens shall be brought to temperature equilibrium before testing; elevated temperature tests shall be conducted at the specified temperature after holding at that temperature for 15 min. ± 1 .
- 4.5.3 Core Density: Shall be determined on blocks and slices from their weight and dimensions to an accuracy within 1%. Thickness shall be measured with an accuracy of 0.001 in. (0.02 mm) and width and length with an accuracy of 0.010 in. (0.25 mm). Measurements shall be made using a dial gage capable of applying a 10-lb (45-N) force over a 1.5 in. (38 mm) diameter area. Density shall be calculated in lb per cu ft (kg/m^3).

4.5.4 Corrosion Resistance: Representative specimens shall be 5 in. \pm 1/16 (125 mm \pm 1.5) long (longitudinal direction "L" (See Fig. 1)), 6 in. \pm 1/16 (150 mm \pm 1.5) wide (transverse direction "W"), and 0.625 in. \pm 0.010 (16.00 mm \pm 0.25) thick "T". The core specimens shall be weighed, using an analytical balance, to the nearest milligram. Specimens shall be dried at 350°F \pm 10 (175°C \pm 3) in an electric drying oven for 16 hr \pm 0.25 and allowed to cool to room temperature before weighing. The test specimen shall be subjected to a 5% salt spray test in accordance with ASTM B117 except that the cell axis (W-L axis) shall be supported or suspended horizontal approximately 90 deg from vertical. At the end of 30 days exposure, the specimens shall be removed and rinsed thoroughly in clear, running water for at least 5 minutes. Immediately following rinsing, the specimens shall be stripped by immersion in a phosphoric-chromic acid solution for 5 min. \pm 0.25 at 212°F \pm 2 (100°C \pm 1). The solution shall consist of the following:

Phosphoric acid, 85% H ₃ PO ₄	103 mL
Chromic acid	76 g
Water, to make	1 gal (3.785 L)

The specimens shall be removed from the solution, rinsed in distilled or deionized water for at least 5 min., dried at 225°F \pm 5 (105°C \pm 3) for 30 - 40 min., cooled to room temperature, and reweighed. The stripping solution shall be discarded after 1 gal (4L) of the solution has dissolved 20 g of oxides or coating. Compute the weight loss as in 4.5.4.1 in Inch/Pound Units or as in 4.5.2.2 in SI Units:

4.5.4.1 Inch/Pound Units:

$$M = \frac{36C(O-A)}{TLW}$$

Where, M = Weight loss per sq ft of exposed foil area in milligrams

C = Nominal cell size, inch (1/8, 5/32, 3/16, 1/4, 3/8)

T = Thickness measurement in direction of cell axis, inch

L = Ribbon length direction, inches

W = Transverse direction, inches

O = Original weight of specimen before exposure in milligrams

A = Final weight of specimen after stripping in milligrams

AMS 4348A

4.5.4.2 SI Units:

$$M = \frac{26507C (O-A)}{TLW}$$

Where, M = Weight loss per m² of exposed foil area in milligrams

C = Nominal cell size, millimetres (3.2, 4.0, 4.8, 6.4, 9.5)

T = Thickness measurement in direction of cell axis, millimetres

L = Ribbon length direction, millimetres

W = Transverse direction, millimetres

O = Original weight of specimen before exposure in milligrams

A = Final weight of specimen after stripping in milligrams

4.6 Reports:

4.6.1 The vendor of core shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the core conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 4348A, product designation, size, quantity, block or lot number, and, when requested, the foil lot number.

4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4348A, contractor or other direct supplier of core, supplier's material designation, part number, and quantity. When core for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of core to determine conformance to the requirements of this specification and shall include in the report either a statement that the core conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the core may be based on the results of testing three additional specimens, cut from the same block, for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the core represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 Color Identification: Each block or slice of core shall be identified on the edges by parallel stripes: One 2-in. (50-mm) wide red stripe to identify 350°F (175°C) core, one 0.5-in. (12-mm) wide black stripe to identify 5052 alloy, and a 0.5-in. (12-mm) wide colored stripe along side the black stripe to identify the density range. The colors of the stripes shall be as specified in Table II and shall approximately match the color numbers of FED-STD-595. The group of parallel identification stripes shall be repeated at intervals not greater than 2 ft (600 mm). The color shall be produced by adding a dye to an adhesive which is compatible with the core. Stripes shall be painted or sprayed on the edges of core blocks or slices. The dye shall retain its color through the curing cycles, shall be noncorrosive, and shall have no adverse effect on the curing or the strength of the adhesive used for construction of the core or the adhesive used with the core in fabricating sandwich components.

5.1.2 Labeling: Each piece of core and each interior and exterior container shall be identified with not less than the following information, applied to a durable tag or label, using characters of such size as to be legible and which will not be obliterated by normal handling.

CORE, HONEYCOMB, ALUMINUM ALLOY, CORROSION INHIBITED, 5052-H191
AMS 4348A

CORE DESIGNATION _____
PURCHASE ORDER NUMBER _____
MANUFACTURER'S DESIGNATION _____
BLOCK OR CORE LOT NUMBER _____
PART NUMBER OR SIZE (T x L x W) _____
QUANTITY _____

5.2 Packaging:

5.2.1 Core shall be packaged and shipped in outer containers in such a manner as to ensure that the core, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any other normal hazard.

5.2.2 Containers shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging and transportation of the core to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.3 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-794, Level A or Level C, as specified in the request for procurements. Commercial packaging as in 5.2.1 and 5.2.2 will be acceptable if it meets the requirements of Level C.

AMS 4348A

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Core not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.
8. NOTES:
 - 8.1 Marginal Indicia: The phi (\emptyset) symbol is used to indicate technical changes from the previous issue of this specification.
 - 8.2 Dimensions and properties in inch/pound units and the Fahrenheit temperatures are primary; dimensions and properties in SI units and the Celsius temperatures are shown as the approximate equivalents of the primary units and are presented only for information.
 - 8.3 For direct U.S. Military procurement, purchase documents should specify not less than the following:

Title, number, and date of this specification
Cell size and density of core desired
Size of core slices or blocks desired
Quantity of core desired
Applicable level of packaging (See 5.2.3)
 - 8.4 Similar Specifications: This specification is the equivalent of MIL-C-7438F, Amendment 1, Grade B, Class 2, dated 1 February 1977.
 - 8.5 Core meeting the requirements of this specification has been classified under Federal Supply Classification (FSC) 5680.

This specification is under the jurisdiction of AMS Committee "C" (NOMETCOM).

TABLE I

Cell Size Inch	Nominal Core Dimensions			Density lb per cu ft	Plate Shear Strength psi, min		Plate Shear Modulus psi, min, avg		Compression Strength psi, min		
	Foil Thickness Designated Inch	Maximum Inch	Direction of Test W		Direction of Test L	W	L	W	L	Bare	Stabilized
1/8	0.0007	0.0011	90	155	16000	31000	200	215			
	0.0010	0.0015	168	285	25000	51000	375	405			
	0.0015	0.0022	272	455	37000	77000	650	680			
	0.0020	0.0029	400	670	50000	112000	1000	1100			
5/32	0.0007	0.0011	70	120	12000	24000	150	160			
	0.0010	0.0015	125	215	20000	41000	285	300			
	0.0015	0.0022	215	370	31000	64000	490	535			
	0.0020	0.0029	328	540	42000	91000	770	800			
0.0025	0.0034	420	690	52000	115000	1070	1180				
3/16	0.0007	0.0011	46	80	9000	17000	90	100			
	0.0010	0.0015	90	155	16000	31000	200	215			
	0.0015	0.0022	160	280	24000	50000	360	385			
	0.0020	0.0029	244	410	34000	70000	560	600			
0.0025	0.0034	328	540	42000	91000	770	800				
0.0030	0.0042	400	670	50000	112000	1000	1100				
1/4	0.0007	0.0011	32	60	6000	13000	60	70			
	0.0010	0.0015	57	100	11000	21000	120	130			
	0.0015	0.0022	105	180	18000	35000	240	250			
	0.0020	0.0029	155	265	24000	48000	350	370			
0.0025	0.0034	200	360	30000	62000	500	510				
0.0030	0.0042	265	445	36000	75000	630	660				
0.0040	0.0053	390	650	49000	108000	970	1050				
3/8	0.0007	0.0011	20	32	4000	7000	20	20			
	0.0010	0.0015	32	60	6000	13000	60	70			
	0.0015	0.0022	57	100	11000	21000	120	130			
	0.0020	0.0029	85	145	15000	30000	190	200			
0.0025	0.0034	115	200	20000	40000	270	285				
0.0030	0.0042	150	255	23000	47000	335	355				
0.0040	0.0053	228	380	32000	66000	500	535				
0.0050	0.0065	300	500	39000	84000	700	750				

TABLE I (SI)

Cell Size mm	Nominal Core Dimensions		Density kg/m ³	Plate Shear Strength MPa, min		Plate Shear Modulus MPa, min, avg		Compression Strength MPa, min			
	Foil Thickness Designated μm	Maximum μm		Direction of Test		Direction of Test		W	L	Bare	Stabilized
				W	L	W	L				
3.2	17.5	27.5	50	0.621	1.069	110	214	1.379	1.482		
	25.0	37.5	72	1.158	1.965	172	352	2.586	2.792		
	37.5	55.0	98	1.875	3.137	255	531	4.482	4.689		
	50.0	72.5	130	2.758	4.620	345	772	6.895	7.584		
4.0	17.5	27.5	42	0.483	0.827	83	165	1.034	1.103		
	25.0	37.5	61	0.862	1.482	138	283	1.965	2.068		
	37.5	55.0	85	1.482	2.551	214	441	3.379	3.689		
	50.0	72.5	110	2.262	3.723	290	627	5.309	5.516		
62.5	85.0	135	2.896	4.758	359	793	7.378	8.136			
4.8	17.5	27.5	32	0.317	0.552	62	117	0.621	0.690		
	25.0	37.5	50	0.621	1.069	110	214	1.379	1.482		
	37.5	55.0	70	1.103	1.931	165	345	2.482	2.655		
	50.0	72.5	91	1.682	2.827	234	483	3.861	4.137		
62.5	85.0	110	2.262	3.723	290	627	5.309	5.516			
75.0	105.0	130	2.758	4.620	345	772	6.895	7.584			
6.4	17.5	27.5	26	0.221	0.414	41	90	0.414	0.483		
	25.0	37.5	37	0.393	0.690	76	145	0.827	0.896		
	37.5	55.0	55	0.724	1.241	124	241	1.655	1.724		
	50.0	72.5	69	1.069	1.827	165	331	2.413	2.551		
62.5	85.0	83	1.379	2.482	207	427	3.448	3.516			
75.0	105.0	96	1.827	3.068	248	517	4.344	4.551			
100.0	132.5	126	2.689	4.482	338	745	6.688	7.240			
9.5	17.5	27.5	16	0.138	0.221	28	48	0.138	0.138		
	25.0	37.5	26	0.221	0.414	41	90	0.414	0.483		
	37.5	55.0	37	0.393	0.690	76	145	0.827	0.896		
	50.0	72.5	48	0.586	1.000	103	207	1.310	1.379		
62.5	85.0	59	0.793	1.379	138	276	1.862	1.965			
75.0	105.0	67	1.034	1.758	159	324	2.310	2.448			
100.0	132.5	86	1.572	2.620	221	455	3.448	3.689			
125.0	162.5	104	2.069	3.448	269	579	4.826	5.171			