



# AEROSPACE MATERIAL SPECIFICATIONS

## AMS 4377D

Superseding AMS 4377C

Issued 8-15-58

Revised 5-1-68

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

### MAGNESIUM ALLOY SHEET AND PLATE 3.0Al - 1.0Zn (AZ31B-H24)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for moderate strength parts requiring rigidity and low density. Special care is necessary to prevent corrosion.
3. **COMPOSITION:**

	min	max
Aluminum	2.5	3.5
Zinc	0.7	1.3
Manganese	0.20	--
Silicon	--	0.10
Copper	--	0.05
Calcium	--	0.04
Iron	--	0.005
Nickel	--	0.005
Other Impurities, total	--	0.30
Magnesium	remainder	

4. **CONDITION:**
  - 4.1 **Material 0.500 In. and Under in Thickness:** Cold rolled, partially annealed, and pickled.
  - 4.2 **Material Over 0.500 In. Thick:** Cold rolled and partially annealed.
5. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

5.1 **Tensile Properties:**

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 6,500,000)		Elongation % in 2 in. or 4D, min
		psi, min	Extension Under Load in. in 2 in.	
0.016 to 0.249, incl	39,000	29,000	0.0129	6
Over 0.249 to 0.374, incl	38,000	26,000	0.0120	8
Over 0.374 to 0.500, incl	37,000	24,000	0.0114	8
Over 0.500 to 1.000, incl	36,000	22,000	0.0108	8
Over 1.000 to 2.000, incl	34,000	20,000	0.0102	8
Over 2.000 to 3.000, incl	34,000	18,000	0.0095	8

- 5.1.1 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.
- 5.1.2 If sizes other than those shown are ordered, tensile property requirements shall be as agreed upon by purchaser and vendor.

SAE Technical Board rules provide that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard, recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.2 Compressive Properties: Material 0.063 in. and over in thickness shall be capable of meeting the following requirements. Specimens shall be tested in the longitudinal direction in accordance with the issue of ASTM E9 specified in the latest issue of AMS 2350.

Nominal Thickness Inches	Yield Strength at 0.2% Offset psi, min
0.063 to 0.249, incl	24,000
Over 0.249 to 0.374, incl	20,000
Over 0.374 to 0.500, incl	16,000
Over 0.500 to 1.000, incl	13,000
Over 1.000 to 2.000, incl	10,000
Over 2.000 to 3.000, incl	9,000

- 5.2.1 If sizes other than those shown are ordered, compressive properties shall be as agreed upon by purchaser and vendor.
6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202. Flatness tolerances for material over 2.000 in. in thickness shall be as agreed upon by purchaser and vendor.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, thickness, size, and quantity.
- 8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
9. IDENTIFICATION: Unless otherwise specified, each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4377 or applicable Federal or Military specification designation, inspection lot number, manufacturer's identification, and nominal thickness in inches. An inspection lot shall be material of the same alloy, temper, section, and size traceable to a heat treatment lot or lots and subjected to inspection at one time. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling.
- 9.1 Flat Sheet and Plate Under 6 In. Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet. The inspection lot number may appear in the row marking or may appear at only one location on the piece.