

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 4377F
Superseding AMS 4377E

Issued 8-15-58
Revised 7-1-84

MAGNESIUM ALLOY SHEET AND PLATE
3.0Al - 1.0Zn (AZ31B-H24)
Cold Rolled, Partially Annealed

UNS M11311

1. SCOPE:

1.1 Form: This specification covers a magnesium alloy in the form of sheet and plate.

1.2 Application: Primarily for parts requiring a combination of moderate strength and rigidity with low density. Special care is necessary to prevent corrosion.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate
AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E9 - Compression Testing of Metallic Materials at Room Temperature

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 4377F

2.3.1 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
Aluminum	2.5	3.5
Zinc	0.7	1.3
Manganese	0.20	--
Silicon	--	0.05
Copper	--	0.05
Calcium	--	0.04
Iron	--	0.005
Nickel	--	0.005
Other Impurities, total	--	0.30
Magnesium		remainder

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Product 0.500 In. (12.50 mm) and Under in Nominal Thickness: Cold rolled, partially annealed, and pickled.

3.2.2 Product Over 0.500 In. (12.50 mm) in Nominal Thickness: Cold rolled and partially annealed.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1, determined in accordance with AMS 2355.

TABLE I

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
0.016 to 0.249, incl	39,000	29,000	6
Over 0.249 to 0.374, incl	38,000	26,000	8
Over 0.374 to 0.500, incl	37,000	24,000	8
Over 0.500 to 1.000, incl	36,000	22,000	8
Over 1.000 to 2.000, incl	34,000	20,000	8
Over 2.000 to 3.000, incl	34,000	18,000	8

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D %, min
0.40 to 6.25, incl	270	200	6
Over 6.25 to 9.35, incl	260	180	8
Over 9.35 to 12.50, incl	255	165	8
Over 12.50 to 25.00, incl	250	150	8
Over 25.00 to 50.00, incl	235	140	8
Over 50.00 to 75.00, incl	235	125	8

3.3.1.1 Tensile property requirements for product under 0.016 (0.40 mm) or over 3.000 in. (75.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Compressive Properties: Product 0.063 in. (1.60 mm) and over in nominal thickness shall meet the requirements of Table II and 3.3.2.1, determined in accordance with ASTM E9 in the longitudinal direction.

TABLE II

Nominal Thickness Inches	Yield Strength at 0.2% Offset psi, min
0.063 to 0.249, incl	24,000
Over 0.249 to 0.374, incl	20,000
Over 0.374 to 0.500, incl	16,000
Over 0.500 to 1.000, incl	13,000
Over 1.000 to 2.000, incl	10,000
Over 2.000 to 3.000, incl	9,000

TABLE II (SI)

Nominal Thickness Millimetres	Yield Strength at 0.2% Offset MPa, min
1.60 to 6.25, incl	165
Over 6.25 to 9.35, incl	140
Over 9.35 to 12.50, incl	110
Over 12.50 to 25.00, incl	90
Over 25.00 to 50.00, incl	70
Over 50.00 to 75.00, incl	60

3.3.2.1 Compressive property requirements for product under 0.063 in. (1.60 mm) or over 3.000 in. (75.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

AMS 4377F

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for compressive properties (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4377F, lot number, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4377F, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

- 5.1 **Identification:** Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4377 or applicable Federal specification designation, inspection lot number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.
- 5.1.1 **Flat Sheet and Plate Under 6 In. (150 mm) Wide:** Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm). The inspection lot number may appear in the row marking or may appear at only one location on each piece.
- 5.1.2 **Flat Sheet and Plate 0.375 In. (9.50 mm) and Under Thick, 6 to 60 In. (150 to 1500 mm), Incl, Wide, and 36 to 200 In. (900 to 5000 mm), Incl, Long:** Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced approximately 6 in. (150 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the alloy number and temper and AMS 4377 or applicable Federal specification designation. The inspection lot number may be included in the rows with the alloy, temper, and specification designations or may appear at only one location on each piece.
- 5.1.3 **Flat Sheet and Plate Over 0.375 In. (9.50 mm) Thick, or Over 60 In. (1500 mm) Wide, or Over 200 In. (5000 mm) Long:** Shall be marked as in 5.1.2 or, at vendor's discretion, shall be marked in one or two rows of characters recurring at intervals not greater than 3 ft (900 mm) and running around the periphery of the piece. If one row is used, it shall show all the information of 5.1 except that the inspection lot number may be omitted. If two rows are used, one row shall show the alloy number and temper and AMS 4377 or applicable Federal specification designation; the second row shall show the manufacturer's identification and nominal thickness. The inspection lot number may be included in the line with the manufacturer's identification and nominal thickness or may appear at only one location on each piece.
- 5.1.3.1 If peripheral marking is applied to the full piece as produced but partial sheets or plates are supplied, an arrow shall also be applied near one corner indicating the direction of rolling.
- 5.1.4 **Coiled Sheet:** Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the sheet is wound on cores, the tag or label may be attached to the core.